



Illinois Department of Transportation

2300 South Dirksen Parkway / Springfield, Illinois / 62764

3/1/2005

SUBJECT: FAI Route 90/94
Project IM-094-3(383)058
Section 2004-074RS
Cook County
Contract No. 62813
Item No. 6, 3/11/05 Letting
Addendum A

NOTICE TO PROSPECTIVE BIDDERS: ;

Attached is an addendum to the plans or proposal. This addendum involves revised and/or added material.

1. Revised pages 25 & 82 of the Special Provisions.
2. Revised page ii of the Table of Contents

Prime contractors must utilize the enclosed material when preparing their bid and must include any Schedule of Prices changes in their bidding proposal.

Bidders using computer-generated bids are cautioned to reflect any and all Schedule of Prices changes, if involved, into their computer programs.

Very truly yours,

Michael L. Hine
Engineer of Design
and Environment

A handwritten signature in black ink, appearing to read 'Ted B. Walschleger' followed by 'P.E.' in a smaller font.

By: Ted B. Walschleger, P. E.
Engineer of Project Management

cc: Diane O'Keefe; Roger Driskell; Jim White; Design & Environment File

Tk/cah

FAI ROUTE 90/94 (DAN RYAN EXPRESSWAY)
SECTION: (2004-074RS)
COOK COUNTY

EXPANSION JOINTS (BDE).....	24
FLAGGER VESTS (BDE)	24
FREEZE-THAW RATING (BDE).....	25
HAND VIBRATOR (BDE).....	25
FURNISHED EXCAVATION (BDE)	26
STORM WATER POLLUTION PREVENTION PLAN.....	27
CONTRACTOR CERTIFICATION STATEMENT	40
INLET FILTERS (BDE).....	42
CURING AND PROTECTION OF CONCRETE CONSTRUCTION (BDE)	43
DISADVANTAGED BUSINESS ENTERPRISE PARTICIPATION (BDE).....	50
COARSE AGGREGATE FOR TRENCH BACKFILL, BACKFILL AND BEDDING (BDE).....	57
CONCRETE ADMIXTURES (BDE).....	62
BITUMINOUS BASE COURSE / WIDENING SUPERPAVE	66
PARTIAL PAYMENTS (BDE).....	71
PAVEMENT THICKNESS DETERMINATION FOR PAYMENT (BDE)	72
PAYMENTS TO SUBCONTRACTORS (BDE).....	78
PERSONAL PROTECTIVE EQUIPMENT (BDE).....	78
PORTABLE CHANGEABLE MESSAGE SIGNS (BDE).....	79
PORTLAND CEMENT (BDE).....	80
PORTLAND CEMENT CONCRETE (BDE).....	80
PRECAST CONCRETE PRODUCTS (BDE)	80
PREFORMED RECYCLED RUBBER JOINT FILLER (BDE)	81
RAP FOR USE IN BITUMINOUS CONCRETE MIXTURES (BDE)	82
SELF-CONSOLIDATING CONCRETE FOR PRECAST PRODUCTS (BDE)	85
STABILIZED SUBBASE AND BITUMINOUS SHOULDERS SUPERPAVE (BDE)	87
SUBGRADE PREPARATION (BDE).....	92
SUPERPAVE BITUMINOUS CONCRETE MIXTURES (BDE)	92
SURFACE TESTING OF PAVEMENTS (BDE).....	98
TRAFFIC CONTROL DEFICIENCY DEDUCTION (BDE).....	104
TRUCK BED RELEASE AGENT (BDE).....	105
WORK ZONE TRAFFIC CONTROL DEVICES (BDE).....	105
STEEL COST ADJUSTMENT (BDE)	107

Revised 3/1/2005

Standards Institute specification ANSI/ISEA 107-1999 for Conspicuity Class 2 garments and approved flagger traffic control signs conforming to Standard 702001 and Article 702.05(e).”

Revise Article 701.04(c)(6) of the Standard Specifications to read:

“(6) Nighttime Flagging. The flagger station shall be lit by additional overhead lighting other than streetlights. The flagger shall be equipped with a fluorescent orange or fluorescent orange and fluorescent yellow/green garment meeting the requirements of the American National Standards Institute specification ANSI/ISEA 107-1999 for Conspicuity Class 2 garments.”

FREEZE-THAW RATING (BDE)

Effective: November 1, 2002

Revise the first sentence of Article 1004.02(f) of the Standard Specifications to read:

“When coarse aggregate is used to produce portland cement concrete for base course, base course widening, pavement, driveway pavement, sidewalk, shoulders, curb, gutter, combination curb and gutter, median, paved ditch or their repair using concrete, the gradation permitted will be determined from the results of the Department’s Freeze-Thaw Test.”

HAND VIBRATOR (BDE)

Effective: November 1, 2003

Add the following paragraph to Article 1103.17(a) of the Standard Specifications:

“The vibrator shall have a non-metallic head for areas containing epoxy coated reinforcement. The head shall be coated by the manufacturer. The hardness of the non-metallic head shall be less than the epoxy coated reinforcement, resulting in no damage to the epoxy coating. Slip-on covers will not be allowed.”

Revised 3/1/2005

RAP FOR USE IN BITUMINOUS CONCRETE MIXTURES (BDE)

Effective: January 1, 2000

Revised: April 1, 2002

Revise Article 1004.07 to read:

"1004.07 RAP Materials. RAP is reclaimed asphalt pavement resulting from cold milling or crushing of an existing dense graded hot-mix asphalt pavement. RAP must originate from routes or airfields under federal, state or local agency jurisdiction. The Contractor shall supply documentation that the RAP meets these requirements.

- (a) Stockpiles. The Contractor shall construct individual, sealed RAP stockpiles meeting one of the following definitions. No additional RAP will be allowed on top of the pile after the pile has been sealed.
- (1) Homogeneous. Homogeneous RAP stockpiles shall consist of RAP from Class I/ Superpave, or equivalent mixtures only and represent the same aggregate quality, but shall be at least C quality or better, the same type of crushed aggregate (either crushed natural aggregate, ACBF slag, or steel slag), similar gradation and similar AC content. If approved by the Engineer, combined single pass surface/binder millings may be considered "homogenous", with a quality rating dictated by the lowest coarse aggregate quality present in the mixture. Homogenous stockpiles shall meet the requirements of Article 1004.07(d). Homogeneous RAP stockpiles not meeting these requirements may be processed (crushing and screening) and retested.
 - (2) Conglomerate. Conglomerate RAP stockpiles shall consist of RAP from Class I/ Superpave, or equivalent mixtures only. The coarse aggregate in this RAP shall be crushed aggregate only and may represent more than one aggregate type and/or quality but shall be at least C quality or better. This RAP may have an inconsistent gradation and/or asphalt cement content prior to processing. All conglomerate RAP shall be processed prior to testing by crushing to where all RAP shall pass the 16 mm (5/8 in.) or smaller screen. Conglomerate RAP stockpiles shall not contain steel slag or other expansive material as determined by the Department. Conglomerate RAP stockpiles shall meet the requirements of Article 1004.07(d).
 - (3) Conglomerate "D" Quality (DQ). Conglomerate DQ RAP stockpiles shall consist of RAP containing coarse aggregate (crushed or round) that is at least D quality or better. This RAP may have an inconsistent gradation and/or asphalt content.

Revised 3/1/2005