

TIME: 4:00 PM

DATE: 12/27/05

FILENAME: s:\051781-000\184\426\micro\sheet files\pavm\augusta\augusta.cores.dgn

F.A. RTE.	SECTION	COUNTY	TOTAL SHEETS	SHEET NO.
	97-00226-00-PP	COOK	80	66
STA.	TO STA.			
FED. ROAD DIST. NO.		ILLINOIS FED. AID PROJECT		
CONTRACT NO.: 83898				

SEP-26-2006 11:21 VILLAGE OF OAK PARK 788 848 2529 P.13/21

ETL FLOOD
 Engineering Laboratories, Inc.
 1945 E. 87th St.
 Chicago, IL 60617
 Phone 773-721-2200
 Fax 773-721-2266

LOG OF BORING - No. B-11
 Tuesday, December 27, 2005

PROJECT: 2006 Capital Improvements
 CLIENT: Village of Oak Park

DEPTH (FT.)	SAMPLE		DESCRIPTION OF MATERIAL	UNCONF. COMPRESS. STRENGTH TSP - C
	NUMBER	TYPE		
			ELEVATION OF SURFACE 1.00 Asphalt Pavement (7")	
			(FILL)	
			CA-6 Crushed Stone Base (10")	
			(FILL)	
			Brown and Gray Silty Clay	
			(CL-ML)	
			End of Boring SE of East of Alley Between East and Columbian on Augusta	

WATER LEVEL: N/A FT. AT ND HRS. BORING STARTED: October 21, 2005
 N/A FT. AT AC HRS. BORING COMPLETED: October 21, 2005

SEP-26-2006 11:21 VILLAGE OF OAK PARK 788 848 2529 P.12/21

ETL FLOOD
 Engineering Laboratories, Inc.
 1945 E. 87th St.
 Chicago, IL 60617
 Phone 773-721-2200
 Fax 773-721-2266

LOG OF BORING - No. B-10
 Tuesday, December 27, 2005

PROJECT: 2006 Capital Improvements
 CLIENT: Village of Oak Park

DEPTH (FT.)	SAMPLE		DESCRIPTION OF MATERIAL	UNCONF. COMPRESS. STRENGTH TSP - C
	NUMBER	TYPE		
			ELEVATION OF SURFACE 1.00 Asphalt Pavement (4.5")	
			(FILL)	
			Concrete Pavement (8")	
			(FILL)	
			CA-6 Crushed Stone Base (5.5")	
			(FILL)	
			Brown and Gray Silty Clay	
			(CL-ML)	
			End of Boring Intersection of Augusta and East	

WATER LEVEL: N/A FT. AT ND HRS. BORING STARTED: October 22, 2005
 N/A FT. AT AC HRS. BORING COMPLETED: October 22, 2005

SEP-26-2006 11:22 VILLAGE OF OAK PARK 788 848 2529 P.14/21


ETL FLOOD
 Engineering Laboratories, Inc.
 1945 E. 87th St.
 Chicago, IL 60617
 Phone 773-721-2200
 Fax 773-721-2266

LOG OF BORING - No. B-12
 Tuesday, December 27, 2005

PROJECT: 2006 Capital Improvements
 CLIENT: Village of Oak Park

DEPTH (FT.)	SAMPLE		DESCRIPTION OF MATERIAL	UNCONF. COMPRESS. STRENGTH TSP - C
	NUMBER	TYPE		
			ELEVATION OF SURFACE 1.00 Asphalt Pavement (2.5")	
			(FILL)	
			Concrete Pavement (7.5")	
			(FILL)	
			CA-6 Crushed Stone Base (6")	
			(FILL)	
			Brown Silty Clay	
			(CL-ML)	
			End of Boring 50' East of Augusta and Columbian	

WATER LEVEL: N/A FT. AT ND HRS. BORING STARTED: October 21, 2005
 N/A FT. AT AC HRS. BORING COMPLETED: October 21, 2005

	REVISIONS		ILLINOIS DEPARTMENT OF TRANSPORTATION
	NAME	DATE	
AUGUSTA STREET PAVEMENT CORES			SCALE: VERT. HORIZ. DATE 1/9/2007
DRAWN BY			
CHECKED BY JDM			