

35500d

355.00d

Designer Note: Use whenever temporary pavement is called for on the plans. The intent is to allow the Contractor the option as to the most economical type of pavement to provide. Use with District Special Provision "Hot-Mix Asphalt Base Course" (355.02) or "Hot-Mix Asphalt Base Course Widening" (356.02d).

The Designer should calculate design thicknesses for concrete and bituminous pavements using BDE Manual Sections 54-4.02 and 54-5.02 and insert the thickness into the special provision:

X = thickness in inches (millimeters) of Hot-Mix Asphalt Base Course

Y = thickness in inches (millimeters) of PCC Base Course

### **TEMPORARY PAVEMENT**

Effective October 1, 1995    Revised April 23, 2010

This item shall include all materials, labor and equipment necessary to construct temporary pavement in accordance with applicable sections of the Standard Specifications except as herein specified.

The Contractor shall have the option of constructing temporary pavement made of (X) hot-mix asphalt base course or (Y) PCC base course.

Hot-Mix Asphalt base course shall be placed in accordance with applicable portions of Section 355. Material for Hot-Mix Asphalt base course shall be Hot-Mix Asphalt Binder Course IL-19.0 in accordance with Sections 406 and 407. PCC base course shall be in accordance with Section 353.

This work will be paid for at the contract unit price per Square Yard (Square Meter) for TEMPORARY PAVEMENT which price shall be payment in full for all materials, labor and equipment including bituminous and aggregate prime coat necessary to perform the work as herein specified.

Removal of Temporary Pavement will be paid for separately in accordance with Section 440 of the Standard Specifications.