

Designer Note: Use this special when using the material listed to fill cracks in existing parapets as required by the Bridge Maintenance Engineer.

SURFACE FILLER, SPECIAL (GALLON)

Effective April 23, 2010

This work shall consist of filling cracks over 1/32" and other surface defects such as popouts with a gun-grade elastomeric sealant prior to overcoating with "Protective Coat, Special".

Material. The material shall be a 1-component, polyurethane-based, non-sag elastomeric sealant that meets ASTM C-920, Type S, Grade NS, Class 100/50, use T, NT, G, M.

The surface filler material shall be as recommended by the Manufacturer for the "Protective Coat, Special" and shall be compatible with the protective coating applied to the concrete parapet as specified in the Special Provision for "Protective Coat, Special".

Construction. All cracks and surface defects to be repaired shall be sound, dry, and clean of any foreign material. Preparation, filling, and tooling shall be according to the Manufacturer's specifications. Curing time shall be as recommended by the manufacturer, but a minimum of one day cure time shall be allowed prior to overcoating with "Protective Coat, Special".

A manufacturer's technical representative shall be present on the first day of surface filling operations to ensure correct interpretation of the Manufacturer's specifications.

Method Measurement. The surface filler will be measured for payment in Gallons used in place to the nearest 0.1 Gallon.

Basis of Payment. The surface filler will be paid for at the contract unit price per Gallons for SURFACE FILLER, SPECIAL (GALLON), which price shall include the furnishing of all materials, crack and surface defect preparation, and the application of the surface filler as specified.