



Illinois Department of Transportation

2300 South Dirksen Parkway / Springfield, Illinois / 62764

March 1, 2005

SUBJECT: FAI Route 90/94
Project IM-094-3(379)057)
Section 2004-070RS
Cook County
Contract No. 62809
Item No. 2, March 11, 2005 Letting
Addendum A

NOTICE TO PROSPECTIVE BIDDERS: :

Attached is an addendum to the plans or proposal. This addendum involves revised and/or added material.

1. Revised pages 55 & 68 of the Special Provisions.
2. Revised page ii of the Table of Contents/

Prime contractors must utilize the enclosed material when preparing their bid and must include any Schedule of Prices changes in their bidding proposal.

Bidders using computer-generated bids are cautioned to reflect any and all Schedule of Prices changes, if involved, into their computer programs.

Very truly yours,

Michael L. Hine
Engineer of Design
and Environment

A handwritten signature in cursive script, reading "Ted B. Walschleger" followed by a small "P.E." to the right.

By: Ted B. Walschleger, P. E.
Engineer of Project Management

cc: Diane O'Keefe; Roger Driskell; Jim White; Design & Environment File

TBW:TK:jc

CONCRETE ADMIXTURES (BDE).....	34
CURING AND PROTECTION OF CONCRETE CONSTRUCTION (BDE).....	38
DISADVANTAGED BUSINESS ENTERPRISE PARTICIPATION (BDE).....	45
EROSION AND SEDIMENT CONTROL DEFICIENCY DEDUCTION (BDE).....	52
EXPANSION JOINTS (BDE).....	52
FLAGGER VESTS (BDE).....	53
FREEZE-THAW RATING (BDE).....	53
HAND VIBRATOR (BDE).....	53
INLET FILTERS (BDE).....	54
PARTIAL PAYMENTS (BDE).....	56
PAVEMENT THICKNESS DETERMINATION FOR PAYMENT (BDE).....	57
PAYMENTS TO SUBCONTRACTORS (BDE).....	63
PERSONAL PROTECTIVE EQUIPMENT (BDE).....	64
PORTABLE CHANGEABLE MESSAGE SIGNS (BDE).....	65
PORTLAND CEMENT (BDE).....	66
PORTLAND CEMENT CONCRETE (BDE).....	66
PRECAST CONCRETE PRODUCTS (BDE).....	67
PREFORMED RECYCLED RUBBER JOINT FILLER (BDE).....	67
SELF-CONSOLIDATING CONCRETE FOR PRECAST PRODUCTS (BDE).....	68
SUBGRADE PREPARATION (BDE).....	70
SURFACE TESTING OF PAVEMENTS (BDE).....	70
TRAFFIC CONTROL DEFICIENCY DEDUCTION (BDE).....	76
WORK ZONE TRAFFIC CONTROL DEVICES (BDE).....	77
STEEL COST ADJUSTMENT (BDE).....	79
STORM WATER POLLUTION PREVENTION PLAN.....	82
CONTRACTOR CERTIFICATION STATEMENT.....	95

Revised 03-01-2005

(3) Geotextile Fabric Bag. The sediment bag shall be constructed of an inner filter bag and an outer reinforcement bag.

a. Inner Filter Bag. The inner filter bag shall be constructed of a polypropylene geotextile fabric with a minimum silt and debris capacity of 0.06 cu m (2.0 cu ft). The bag shall conform to the following requirements:

Inner Filter Bag		
Material Property	Test Method	Minimum Avg. Roll Value
Grab Tensile Strength	ASTM D 4632	45 kg (100 lb)
Grab Tensile Elongation	ASTM D 4632	50%
Puncture Strength	ASTM D 4833	29 kg (65 lb)
Trapezoidal Tear	ASTM D 4533	20 kg (45 lb)
UV Resistance	ASTM D 4355	70% at 500 hours
Actual Open Size	ASTM D 1420	212 μ m (No. 70 sieve US)
Permittivity	ASTM D 4491	2.0/sec
Water Flow Rate	ASTM D 4491	5900 Lpm/sq m (145 gpm/sq ft)

b. Outer Reinforcement Bag. The outer reinforcement bag shall be constructed of polyester mesh material that conforms to the following requirements:

Outer Reinforcement Bag		
Material Property	Test Method	Value
Content	ASTM D 629	Polyester
Weight	ASTM D 3776	155 g/sq m (4.55 oz/sq yd) \pm 15%
Whales (holes)	ASTM D 3887	7.5 \pm 2 holes/25 mm (1 in.)
Chorses (holes)	ASTM D 3887	15.5 \pm 2holes/25 mm (1 in.)
Instronball Burst	ASTM D 3887	830 kPa (120 psi) min.
Thickness	ASTM D 1777	1.0 \pm 0.1 mm (0.040 \pm 0.005 in.)

(4) Certification. The manufacturer shall furnish a certification with each shipment of inlet filters, stating the amount of product furnished, and that the material complies with these requirements.”

80104

Revised 03-01-2005

Revise Article 637.02(d) of the Standard Specifications to read:

“(d) Preformed Expansion Joint Filler.....1051”

Add the following Article to Section 1051 of the Standard Specifications:

“1051.10 Preformed Recycled Rubber Joint Filler. Preformed recycled rubber joint filler shall consist of ground tire rubber, free of steel and fabric, combined with ground scrap or waste polyethylene. It shall not have a strong hydrocarbon or rancid odor and shall meet the physical property requirements of ASTM D 1752. Water absorption by volume shall not exceed 5.0 percent.”

80084

SELF-CONSOLIDATING CONCRETE FOR PRECAST PRODUCTS (BDE)

Effective: July 1, 2004

Definition. Self-consolidating concrete is a flowable mixture that does not require mechanical vibration for consolidation.

Usage. Self-consolidating concrete may be used for precast concrete products. The design and testing of a self-consolidating concrete mixture shall be according to Section 1020 of the Standard Specifications except as modified herein.

Materials. Materials shall conform to the following requirements:

- (a) Self-Consolidating Admixtures. The self-consolidating admixture system shall consist of either a high range water-reducing admixture only or a high range water-reducing admixture combined with a separate viscosity modifying admixture. The one or two component admixture system shall be capable of producing a flowable concrete that does not require mechanical vibration.

Revised 03-01-2005