

| F.A.P. RTE. | SECTION | COUNTY | TOTAL SHEETS | SHEET NO. |
|----------------|---------|-----------|-----------------|--------------|
| 7169 | * | CHAMPAIGN | 12 | 3 |

CONTRACT NO. 70461
 • 05 CONTRACT MAINT 2005-12

GENERAL NOTES

G. N. -100
 ENGLISH UNITS OF MEASUREMENT SHALL GOVERN OVER AND SUPERSEDE ANY METRIC UNITS SHOWN
 IN THIS CONTRACT. WHERE INCLUDED, METRIC UNITS ARE FOR INFORMATION ONLY.

G. N. -406H
 MIXTURE REQUIREMENTS

The following mixture requirements are applicable for this project:

| | |
|---------------------|----------------|
| Location | MARKET STREET. |
| MIXTURE USE | SURFACE |
| AC/PG | SBS PG 70-22 |
| RAP % (Max) | 0 |
| Design Air Voids | 4.0% @ Ndes=90 |
| Mix Comp(Gradation) | IL 9.5 |
| Friction Aggregate | Mix D |

G. N. -443 SPL
 STRIP REFLECTIVE CRACK CONTROL TREATMENT SHALL BE PLACED AT THE TWO WIDENING
 CRACKS AND ON THE CENTERLINE AS DIRECTED BY THE ENGINEER.

G. N. -703A
 SHORT TERM PAVEMENT MARKING SHALL BE APPLIED TO THE PAVEMENT AFTER ANY OF THE FOLLOWING:
 COLD MILLING AND/OR PLACING BITUMINOUS MATERIALS (PRIME COAT), LEVELING BINDER
 (MACHINE METHOD), BINDER AND SURFACE COURSES. SHORT TERM PAVEMENT MARKING PLACED ON THE
 SURFACE, SHALL COINCIDE WITH THE FINAL PAVEMENT STRIPING. SHORT TERM PAVEMENT MARKING
 PLACED PRIOR TO THE SURFACE SHALL COINCIDE WITH THE EXISTING PAVEMENT MARKINGS. USE 4
 FEET PER 40 FEET (OR 10% PER STATION).

G. N. -1004.01
 COARSE AGGREGATE GRADATION CA-10 MAY BE USED WHENEVER COARSE AGGREGATE CA-6 IS SPECIFIED
 IN THE STANDARD SPECIFICATIONS.

G. N. -1004.03
 REVISE ARTICLE 1004.03 (c) NOTE 5/ OF THE STANDARD SPECIFICATIONS TO READ:

'5/ GRADATION CA-16 SHALL BE USED IN LIEU OF CA-13 WHEN THE SURFACE COURSE
 IS LESS THAN 1 3/4
 INCHES IN THICKNESS. CA-13 OR CA-16 MAY BE USED WHEN THE SURFACE COURSE IS 1 3/4 INCHES
 OR MORE IN THICKNESS.'