



Illinois Department of Transportation

2300 South Dirksen Parkway / Springfield, Illinois / 62764

April 16, 2015

SUBJECT: FAP Route 535 (IL 60)
Section 2014-084B
Lake County
Contract No. 62A32
Item No. 33, April 24, 2015 Letting
Addendum A

NOTICE TO PROSPECTIVE BIDDERS:

Attached is an addendum to the plans or proposal. This addendum involves revised and/or added material.

1. Revised page i of the Table of Contents to the Special Provisions
2. Revised pages 21 & 29 of the Special Provisions

Prime contractors must utilize the enclosed material when preparing their bid and must include any Schedule of Prices changes in their bidding proposal.

Bidders using computer-generated bids are cautioned to reflect any and all Schedule of Prices changes, if involved, into their computer programs.

Very truly yours,

John D. Baranzelli, P.E.
Acting Engineer of Design and Environment

A handwritten signature in cursive script, reading "Ted B. Walschleger" with a small "P.E." to the right.

By: Ted B. Walschleger, P. E.
Engineer of Project Management

cc: John Fortmann, Region 1, District 1; Laura Mlacnik; Tim Kell;
D. Carl Puzey; Estimates

MS/kf

TABLE OF CONTENTS

LOCATION OF IMPROVEMENT	1
DESCRIPTION OF IMPROVEMENT	1
STATUS OF UTILITIES TO BE ADJUSTED	2
TRAFFIC CONTROL PLAN	2
WORK RESTRICTIONS	3
CONCRETE REMOVAL	3
MAINTENANCE OF ROADWAYS	4
TRAFFIC CONTROL AND PROTECTION (ARTERIALS).....	4
GROUND TIRE RUBBER (GTR) MODIFIED ASPHALT BINDER (D-1)	4
HEAT OF HYDRATION CONTROL FOR CONCRETE STRUCTURES (D-1)	6
HMA MIXTURE DESIGN REQUIREMENTS (D-1)	6
PUBLIC CONVENIENCE AND SAFETY	21
RECLAIMED ASPHALT PAVEMENT AND RECLAIMED ASPHALT SHINGLES (D-1).....	22
PRUNING FOR SAFETY AND EQUIPMENT CLEARANCE	32
PROTECTION OF EXISTING TREES	33
GRADING AND SHAPING FORESLOPES	36
EROSION CONTROL BLANKET	36
TRAFFIC SIGNAL SPECIFICATIONS.....	36
TEMPORARY SOIL RETENTION SYSTEM	96
AUTOMATED FLAGGER ASSISTANCE DEVICES (BDE).....	98
CONCRETE END SECTIONS FOR PIPE CULVERTS (BDE)	99
CONSTRUCTION REQUIREMENTS	100
CONSTRUCTION AIR QUALITY – DIESEL RETROFIT (BDE)	101
CONTRACT CLAIMS (BDE).....	103
DISADVANTAGED BUSINESS ENTERPRISE PARTICIPATION (BDE).....	104
EQUAL EMPLOYMENT OPPORTUNITY (BDE).....	114
FRICITION AGGREGATE (BDE)	117
HOT-MIX ASPHALT - DENSITY TESTING OF LONGITUDINAL JOINTS (BDE)	120
HOT MIX ASPHALT – PRIME COAT (BDE)	121
PAVED SHOULDER REMOVAL (BDE)	125
PAVEMENT PATCHING (BDE).....	126
PAVEMENT STRIPING - SYMBOLS (BDE).....	127

Revised 4/16/15

PUBLIC CONVENIENCE AND SAFETY

Effective: May 1, 2012

Revised: July 15, 2012

Add the following to the end of the fourth paragraph of Article 107.09:

“If the holiday is on a Saturday or Sunday, and is legally observed on a Friday or Monday, the length of Holiday Period for Monday or Friday shall apply.”

Revised 4/16/15

- (4) Use in HMA Binder Mixtures (High and Low ESAL), HMA Base Course, and HMA Base Course Widening. FRAP stockpiles for use in HMA binder mixtures (High and Low ESAL), HMA base course, and HMA base course widening shall be FRAP in which the coarse aggregate is Class C quality or better.
- (5) Use in Shoulders and Subbase. FRAP stockpiles for use in HMA shoulders and stabilized subbase (HMA) shall be FRAP, Restricted FRAP, conglomerate, or conglomerate DQ.
- (b) RAS. RAS meeting Type 1 or Type 2 requirements will be permitted in all HMA applications as specified herein.
- (c) FRAP and/or RAS Usage Limits. Type 1 or Type 2 RAS may be used alone or in conjunction with FRAP in HMA mixtures up to a maximum of 5.0% by weight of the total mix.

When FRAP is used alone or FRAP is used in conjunction with RAS, the percent of virgin asphalt binder replacement (ABR) shall not exceed the amounts indicated in the table below for a given N Design.

Max Asphalt Binder Replacement for FRAP with RAS Combination

HMA Mixtures ^{1/2/4/}	Maximum % ABR		
	Binder/Leveling Binder	Surface	Polymer Modified ^{3/}
30L	50	40	30
50	40	35	30
70	40	30	30
90	40	30	30
4.75 mm N-50			40
SMA N-80			30

- 1/ For HMA "All Other" (shoulder and stabilized subbase) N-30, the percent asphalt binder replacement shall not exceed 50% of the total asphalt binder in the mixture.
- 2/ When the binder replacement exceeds 15 percent for all mixes, except for SMA and IL-4.75, the high and low virgin asphalt binder grades shall each be reduced by one grade (i.e. 25 percent binder replacement using a virgin asphalt binder grade of PG64-22 will be reduced to a PG58-28). When constructing full depth HMA and the ABR is less than 15 percent, the required virgin asphalt binder grade shall be PG64-28.

Revised 4/16/15