

Rubblization Pavement and Subsurface Investigation - Eastbound FAI 64

Section: (41-3-1)RS-1;(41-8)RS-2

Contract 78276

| Station | Location | | | | | Thickness, in. | | | Subbase condition | | | Subgrade IBV | | | | | Soil Information | | | | | | |
|---------|----------|----|----|----|----|----------------|-------|---------|-------------------|----------|-------|--------------|-------|--------|--------|--------|------------------|------|------|------|------|-----|--------------------|
| | PS | 3L | 2L | DL | DS | AC Overlay | PCC | Subbase | Sound | SI Deter | Deter | 0-6" | 6-12" | 12-18" | 18-24" | 24-30" | Classification | Sand | Silt | Clay | LL | PI | % H ₂ O |
| 2351+00 | | | | X | | 4 | 8 | 3 3/4 | BAM | | | 12.0 | 16.0 | 17.0 | 17.0 | | SICI A-6(12) | 8 | 70 | 22 | 33.3 | 138 | 18 |
| " " | | | | | X | 9 1/2 | | 4 | | AGG | | 4.0 | 5.5 | 14.0 | 14.0 | 17.0 | | | | | | | |
| 2360+00 | | | | X | | 4 | 8 | 3 3/4 | BAM | | | 5.5 | 4.0 | 5.5 | 8.5 | | | | | | | | |
| " " | | | | | X | 11 | | 4 | | AGG | | 5.5 | 8.5 | 12.0 | 17.0 | | | | | | | | |
| 2370+00 | | | | X | | 3 3/4 | 8 1/2 | 4 1/4 | BAM | | | 16.0 | 14.0 | 8.5 | 8.5 | | | | | | | | |
| " " | | | | | X | 13 1/2 | | | | | | 7.0 | 7.0 | 12.0 | 10.0 | 10.0 | | | | | | | |
| 2380+00 | | | | X | | 3 1/2 | 8 1/4 | 3 1/2 | BAM | | | 5.5 | 4.0 | 4.0 | 4.0 | | | | | | | | |
| " " | | | | | X | 12 3/4 | | | | | | 4.0 | 5.5 | 4.0 | 4.0 | 4.0 | | | | | | | |
| 2390+00 | | | | X | | 3 3/4 | 7 3/4 | 4 | BAM | | | 14.0 | 8.5 | 5.5 | 7.0 | | | | | | | | |
| " " | | | | | X | 13 | | | | | | 7.0 | 7.0 | 10.0 | 8.5 | 8.5 | | | | | | | |
| 2398+50 | | | | X | | 3 1/4 | 7 3/4 | 5 | BAM | | | 20.0 | 30.0 | 20.0 | 10.0 | | | | | | | | |
| " " | | | | | X | 14 | | | | | | 12.0 | 27.0 | 23.0 | 20.0 | | | | | | | | |