

**GENERAL NOTES (CONTINUED)**

ROUTE		SECTION	COUNTY	SHEET	
F.A.P.	VAR.	*	PEORIA	TOTAL	NO.
MKD.	IL 90			100	69

**HOT-MIX ASPHALT MIXTURE REQUIREMENTS**

\* (108X, 130, 102)RS-3; 129RS-4, 101RS-2

MIXTURE USE(S):	CLASS D PATCHES
AC/PG:	PG 64-22
RAP % (MAX)**:	25%
DESIGN AIR VOIDS:	4.0% @ N=50
MIXTURE COMPOSITION: (GRADATION MIXTURE)	IL 19.0
FRICTION AGGREGATE:	N.A.

\*\* IF RAP OPTION IS SELECTED, THE ASPHALT CEMENT GRADE MAY NEED TO BE ADJUSTED; THIS WILL BE DETERMINED BY THE ENGINEER.

MIXTURE USE(S):	SURFACE COURSE	POLYMERIZED LEVELING BINDER 3/4"	HMA SHOULDER (TOP LIFT/ INCIDENTAL HMA SURFACING
AC/PG:	PG 64-22	SBS or SBR 70-22	PG 64-22
RAP % (MAX)**:	15%	0%	15%
DESIGN AIR VOIDS:	4.0% @ N=50	3.0% @ N=50	4.0% @ N=50
MIXTURE COMPOSITION: (GRADATION MIXTURE)	IL 9.5 or IL 12.5	IL 4.75	IL 9.5 OR IL 12.5
FRICTION AGGREGATE:	Mixture D (dolomite only)	N.A.	Mixture C

\*\* IF RAP OPTION IS SELECTED, THE ASPHALT CEMENT GRADE MAY NEED TO BE ADJUSTED; THIS WILL BE DETERMINED BY THE ENGINEER.

**GENERAL NOTES  
(CONTINUED),  
JOB SPECIFIC NOTES**

For Information Only