



Illinois Department of Transportation

2300 South Dirksen Parkway / Springfield, Illinois / 62764

May 29, 2014

SUBJECT: CH 9 (Wringe Road)
Project BROS-0027(041)
Section 10-00097-00-BR
Clinton County
Contract No. 97556
Item 216
June 13, 2014 Letting
Addendum (A)

NOTICE TO PROSPECTIVE BIDDERS:

Due to clarify information necessary to revise the following:

1. Page 7 of the Special Provisions.

Prime contractors must utilize the enclosed material when preparing their bid and must include any Schedule of Prices changes in their bidding proposal.

Bidders using computer-generated bids are cautioned to reflect any and all Schedule of Prices changes, if involved, into their computer programs.

Very truly yours,

John Baranzelli, P.E.
Acting Engineer of Design and Environment

A handwritten signature in cursive script, reading "Ted B. Walschleger P.E.".

By: Ted B. Walschleger, P.E.
Engineer of Project Management

The hot-mix asphalt mixtures shall meet the requirements as shown in the following table.

20 YR. ESAL'S: 0.9

MIXTURE USE	SURFACE
AC/PG	PG 64-22
RAP % (MAX)	0%
DESIGN AIR VOIDS	4.0% @ Ndes=50
MIX COMPOSITION (GRADATION MIXTURE)	IL 9.5 or IL 12.5
FRICTION AGG	MIXTURE C

20. PORTLAND CEMENT MORTAR FAIRING COURSE:

This work shall be done in accordance with Section 583 of the Standard Specifications except as modified by this special provision.

Non-shrink grout meeting the requirements of Section 1024 shall be used instead of Portland Cement.

While grouting the longitudinal joints between the beams, the contractor shall also place additional non-shrink grout along the precast, prestressed concrete deck beams as required for fairing out any unevenness between the deck beams such that the finished surface shall slope not less than 1:6 (V:H) and shall be feathered smoothly into the deck beam surface. The finish shall be free of depressions or sharp edges.

This work will not be paid for separately but shall be included in the contract unit price per square foot for PRECAST PRESTRESSED CONCRETE DECK BEAMS (21" Depth).

21. GROUTING OF STONE DUMPED RIPRAP:

This work shall consist of the furnishing and placing of Class SC concrete to fill the voids of stone dumped riprap as shown on the plans, as specified herein and as directed by the Engineer. Class SC concrete shall conform to the requirement of Article 1020.04 of the Standard Specifications. Class SC concrete shall consist of a Class SI concrete mix design with a 10% additional cement, and the slump shall be from 3 to 5 inches. Materials testing will not be required for this item or its components.

This work shall conform to the requirements of Section 503 of the Standard Specifications except that forming will not be required. The concrete shall completely cover the riprap. The surface of the concrete needs only to be finished with a come-along or other straight edge tool such that the surface of the concrete is free from ridges, grooves, ruts, footprints and any other indenture which can hold water. Indentures, which hold water, shall be grouted, and significant ridges or grooves shall be removed as directed by the Engineer. Payments shall be at the contract unit price per cubic yard for GROUTING OF STONE DUMPED RIPRAP.