#### STATE OF ILLINOIS DEPARTMENT OF TRANSPORTATION



\*\*(38-4)RS-2, (38-4)BR3 CONTRACT NO. 66757

Sheet 8 of 11 Sheets

#### NOTES

Bar splicer assemblies shall be of an approved type and shall develop in tension at least 125 percent of the yield strength of the lapped reinforcement bars.

Splicer rods shall be of minimum 60 ksi yield strength, threaded or coiled full length. All reinforcement bars shall be lapped and tied to the splicer rods or dowel bars. Bar splicer assemblies shall be epoxy coated according to the requirements for reinforcement bars.


Other systems of similar design may be submitted to the Engineer for approval. Approval shall be based on certified test results from an approved testing laboratory that the proposed bar splicer assembly satisfies the following requirements:

Minimum Capacity (Tension in kips) =  $1.25 \times fy \times A_t$ 

Minimum \*Pull-out Strength = 0.66 x fy x A<sub>1</sub> (Tension in kips)

Where fy = Yield strength of lapped reinforcement bars in ksi.  $A_t$  = Tensile stress area of lapped reinforcement bars. \* = 28 day concrete

BAR SPLICER ASSEMBLIES				
	0 11 0 1	Strengt	h Requirements	
Bar Size to be Spliced	Splicer Rod or Dowel Bar Length	Min. Capacity kips - tension	Min. Pull-Out Strength kips - tension	
#4	1'-8''	14.7	7.9	
#5	2'-0''	23.0	12.3	
#6	2'-7''	33.1	17.4	
#7	3′-5″	45.1	23.8	
#8	4′-6′′	58.9	31.3	
#9	5′-9′′	75.0	39.6	
#10	7'-3''	95.0	50.3	
#11	9′-0′′	117.4	61.8	




# STANDARD


Bar Size	No. Assemblies Required	Location
#6	74	Top Slab
#6	48	Walls
#5	72	Bot. Slab

BAR SPLICER ASSEMBLY DETAILS I-57 OVER DANFORTH TOWNSHIP DRAINAGE DITCH F.A.I. ROUTE 57 SECTION (38-4)RS-2, (38-4)BR3 IROQUOIS COUNTY STATION 507+51.00 S.N. 038-2019










## BAR SPLICER ASSEMBLY ALTERNATIVES

\*\*Heavy Hex Nuts conforming to ASTM A 563, Grade C, D or DH may be used.




## INSTALLATION AND SETTING METHODS


"A" :Set bar splicer assembly by means of a template bolt. "B" :Set bar splicer assembly by nailing to wood forms or cementing to steel forms. (E) : Indicates epoxy coating.



6'-0"



# FOR INTEGRAL OR SEMI-INTEGRAL ABUTMENTS



Bar Splicer for #5 bar
Min. Capacity = 23.0 kips - tension
Min. Pull-out Strength = 12.3 kips - tension
No. Required =

DESIGNED	-	S.F.	м.
CHECKED	-	J.A.	м.
DRAWN	-	S.A.I	Ρ.
CHECKED	-	S.F.M. &	J.A.M.
BSD-1			5-16-0

Bar Splicer for #5 bar Min. Capacity = 23.0 kips - tension Min. Pull-out Strength = 12.3 kips - tension No. Required =