



SECTION B-B
PROJECTED PERPENDICULAR
TO CENTERLINE

REQUIRED COLD MILLED SURFACE TEXTURE

1. COLD MILLING SHALL CONSIST OF TWO PROCESSES:
CUTTING WITH CARBIDE TEETH MOUNTED ON A ROTATING
DRUM, AND PLANING WITH A MOLDBOARD MOUNTED
IMMEDIATELY BEHIND THE CUTTING DRUM.

2. OTHER SIMILAR PATTERNS WILL BE ACCEPTABLE IF THEY CONSIST OF A SMOOTH, FLAT PLANED SURFACE INTERSPERSED WITH A PATTERN OF DISCONTINOUS LONGITUDINAL STRIATIONS.

DESIGNER NOTE:

TO BE USED WITH RECURRING CHECK SHEET "HMA SURFACE CORRECTION"

440-2