



Illinois Department of Transportation

Memorandum

To: *

From: Rich Dotson *RJD*

Subject: **Special Provision Changes**

Date: October 9, 2012

The following special provisions have been revised for the January 18, 2013 and March 8, 2013 lettings. Please revise your special provision books as indicated.

Recurring Special Provisions

Revised Designer Notes to add Checksheet #32 which moved from the BDE Specials to the Recurring Specials with updated sheets for January 1, 2013.

Interim Special Provisions

ISP Number	Description
Alphabetic ISP Index (Revised)	Remove existing alphabetic index and insert revised index.
Numerical ISP Index (Revised)	Remove existing numeric index and insert revised index.

The following BDE Special Provisions have been deleted from the BDE Checksheet and have been moved to the January 1, 2013 Recurring Special Provision, or incorporated into other BDE Specials. Please remove these from your ISP books.

ISP Number	Special Provision Title	New Location
202.07a	"Agreement to Plan Quantity (BDE)"	Article 202.07
442.00	"Calcium Chloride Accelerator for Class PP-2 Concrete (BDE)"	Recurring CS #28
107.00	"Construction Air Quality – Diesel Vehicle Emissions Control (BDE)"	Articles 105.03 and 107.41
107.37	"Construction Air Quality – Idling Restrictions (BDE)"	Articles 105.03 and 107.41
202.07	"Digital Terrain Modeling for Earthwork Calculations (BDE)"	Recurring CS #32
603.02	"Drainage and Inlet Protection Under Traffic (BDE)"	Articles 603.02 and 603.07
701.13	"Flagger at Side Roads and Entrances (BDE)"	Articles 701.13 and 701.20
702.00c	"Impact Attenuators (BDE)"	Section 643
702.00d	"Impact Attenuators, Temporary (BDE)"	Section 706

ISP Number	Special Provision Title <i>(continued)</i>	New Location
503.02	"Metal Hardware Cast into Concrete (BDE)"	Articles 503.02, 504.02, and 1006.13
108.00	"Payrolls and Payroll Records (BDE)"	Recurring CS #5
420.00	"Portland Cement Concrete Inlay or Overlay (BDE)"	Recurring CS #29
420.07	"Portland Cement Concrete Sidewalk (BDE)"	Article 424.07
1020.01	"Self-Consolidating Concrete for Cast-In-Place Construction (BDE)"	The following special provisions: Portland Cement Concrete, QC/QA of Concrete Mixtures and Placing and Consolidating Concrete The following special provisions: Portland Cement Concrete, QC/QA of Concrete Mixtures and Placing and Consolidating Concrete
1020.00	"Self-Consolidating Concrete for Precast and Precast Prestressed Products (BDE)"	The following special provisions: Portland Cement Concrete, QC/QA of Concrete Mixtures and Placing and Consolidating Concrete
642.05	"Shoulder Rumble Strips (BDE)"	Article 642.05
701.15	"Sidewalk, Corner or Crosswalk Closure (BDE)"	Articles 701.03, 701.15, and 1106.02
406.21	"Surface Testing of Pavements (Section 406 overlay portion will remain a special provision and will now be called "Surface Testing of HMA Overlays".) (BDE)"	Articles 407.09, 407.12, 420.10, 420.20, and 1101.10
610.09	"Type G Inlet Box (BDE)"	Article 610.09

Interim Special Provisions	
ISP Number	Description
303.00 (Revised)	"Aggregate Subgrade Improvement (BDE)" Revised to include reference to a BMPR memo about using RAP for aggregate applications.
312.26 (Revised)	"Portland Cement Concrete (BDE)" Revised to include self-consolidating concrete for CIP construction and precast BDE specials.
406.03 (New)	"Surface Testing of Hot-Mix Asphalt Overlays (BDE)" Most of this special was moved into the 2013 Supplemental Specifications so it was renamed.
503.06 (New)	"Placing and Consolidating Concrete (BDE)" Incorporates placement and consolidation requirements for two BDE specials that were combined into the BDE special "Portland Cement Concrete."
542.00 (New)	"Concrete End Sections for Pipe Culverts (BDE)" Creates method of payment for the new longer end sections.
542.01 (New)	"Traversable Pipe Grate (BDE)" Creates method of payment for the pipe grates that can be used on the new end sections in the clear zone.

Interim Special Provisions (Continued)

ISP Number	Description
543.00 (New)	"Insertion Lining of Culverts (BDE)" Revised to allow metal liners.
643.00 (Revised)	"High Tension Cable Median Barrier (BDE)" Revised to improve reliability of barrier.
780.03 (Revised)	"Grooving for Recessed Pavement Markings (BDE)" Revised to correct typo.
780.13 (Revised)	"Polyurea Pavement Markings (BDE)" Revised to clarify pay items.
1006.09 (New)	"Anchor Bolts (BDE)" Adds the option of using a different bolt and cleans up redundant language.
1020.16 (Revised)	"Quality Control/Quality Assurance of Concrete Mixtures (BDE)" Revised to include minor revisions and language from two deleted BDE specials.
1031.00 (Revised)	"Reclaimed Asphalt Pavement and Reclaimed Asphalt Shingles (BDE)" Revised to reference BMPR memo about using RAP for aggregate.
1040.03 (New)	"Drain Pipe, Tile, Drainage Mat, and Wall Drain (BDE)" Revises material requirements to include NTPEP compliance.
1082.01 (New)	"Fabric Bearing Pads (BDE)" Brings IDOT specifications in line with industry standards.
1088.01 (New)	"Coated Galvanized Steel Conduit (BDE)" Allows alternates to PVC as a coating material.
1106.02i (Revised)	"Movable Traffic Barrier (BDE)" Revised to fit with the inclusion of BDE special, "Impact Attenuators, Temporary."
1106.02k (Revised)	"Temporary Water Filled Barrier (BDE)" Revised to fit with the inclusion of BDE special, "Impact Attenuators, Temporary."

District Special Provisions & General Notes

District Number	Description
Alphabetic District Index (Revised)	Remove existing alphabetic index and insert revised index.
Numerical District Index (Revised)	Remove existing numeric index and insert revised index.
561.00 (Revised)	"Steel Casings, (*) Inches" Revised designer note and removed metric references.
561.01 (Revised)	"Steel Casings, (*) Inches" Revised to match industry standards.

General Notes

No changes.

RD:tdp:kme\mgr1\winword\progdev\special provisions\interim spec provs\specprovchnngsmemo.doc

Attachment(s)

cc: *N. Jack	Team 2	Team 6	Team 10	Monmouth Campus
K. Emert	Team 3	Team 7	Team 11	Local Roads (M. Augspurger)
T. Phillips	Team 4	Team 8	Geometrics	Materials (H. Shoup)
Team 1	Team 5	Team 9	Bridge (T. Inglis)	

**Special Provisions Generated Checklist
Generated 10/9/12 11:23 AM**

January 18, 2013 and March 8, 2013 Lettings

SPECIAL PROVISIONS CHECK LIST
Generated - 10/9/12 11:23 AM

Designer: _____ FAP: _____
 Contract No.: _____ Section: _____
 County: _____

Note: Specials that go in every contract have already been marked with an "√" for you.

√	Dir	File Name	Spec Title	Spec Dates
	BRG\	APSLRP-1.DOC	Approach Slab Repair	E 3/13/97
	DES\	<u>100400.doc</u>	Aggregate Optimization of Class PV Mix for Slipform Paving	E 8/3/12
	DES\	<u>100401.doc</u>	Coarse Aggregate Fill	E 4/29/11
	DES\	<u>100402.doc</u>	Concrete Superstructure Aggregate Optimization	E 8/4/06 R 8/3/12
	DES\	<u>100403b.doc</u>	Coarse Aggregate for Bituminous Courses, Class A	E 6/29/93 R 1/1/07
	DES\	<u>100404.doc</u>	Aggregate Quality	E 7/1/90 R 9/23/96
	DES\	<u>103004.doc</u>	Hot-Mix Asphalt - Mixture Design Verification and Production	E 8/3/12
	DES\	<u>10500.doc</u>	Construction Station Layout	E 7/30/10
	DES\	<u>10506.doc</u>	Prestage Site Construction Meetings	E 6/1/92
	DES\	<u>10507.doc</u>	Removal of Abandoned Underground Utilities	E 1/15/96 R 11/21/96
	DES\	<u>10507a.doc</u>	Status of Utilities/Utilities To Be Adjusted	E 1-21-05
	DES\	<u>10700a.doc</u>	Nationwide 404 Permit Requirements	E 1/22/01 R 8/2/02
√	DES\	<u>10731.doc</u>	Location of Underground State Maintained Facilities	E 8/3/07 R 7/31/09
	DES\	<u>10732.doc</u>	Right-of-Way Restrictions	E 7/1/94
	DES\	<u>10803.doc</u>	Delayed Start of Multiple Contracts	E 11/1/01
	DES\	<u>10805a.doc</u>	Date of Completion	E 3/1/90 R 4/28/08
	DES\	<u>10805b.doc</u>	Date of Completion (Plus Working Days)	E 3/1/90 R 7/1/94
	DES\	<u>110303.doc</u>	PCC Automatic Batching Equipment	E 4/23/10
	DES\	<u>20400.doc</u>	Borrow and Furnished Excavation	E 3/7/00 R 4/27/07
	DES\	<u>20500.doc</u>	Geotechnical Reinforcement	E 6/10/93 R 1/1/07
	DES\	<u>20504.doc</u>	Embankment (Restrictions)	E 1/21/05 R 8/3/07
	DES\	<u>20505.doc</u>	Embankment	E 7/1/90 R 8/3/07
	DES\	<u>20505a.doc</u>	Embankment (Small Embankment)	E 10/1/99 R 1/1/07
	DES\	<u>25000.doc</u>	Seeding, Minor Areas	E 7/1/90 R 1/1/07
	DES\	<u>25006a.doc</u>	Mowing	E 12/11/01 R 1/1/12
	DES\	<u>25006b.doc</u>	Mowing	E 12/11/01 R 1/1/12
	DES\	<u>25300.doc</u>	Tree Whip Mixture	E 8/15/91 R 4/25/08
	DES\	<u>25300b.doc</u>	Seedling Mixture A	E 5/5/00 R 11/1/08
	DES\	<u>28100.doc</u>	Grout for Use With Riprap	E 7/30/10
	DES\	<u>28104.doc</u>	Stone Dumped Riprap*	E 4/15/91 R 1/1/07
	DES\	<u>28106.doc</u>	Stone Riprap	E 11/5/10
	DES\	<u>28303.doc</u>	Aggregate Ditch	E 4/15/91 R 10/15/01
	DES\	<u>30101.doc</u>	Proof Rolling	E 4/23/04 R 1/1/07
	DES\	<u>30103.doc</u>	Subgrade Treatment	E 7/1/90 R 4/28/08
	DES\	<u>30200.doc</u>	Soil Modification	E 7/1/90 R 7/30/10
	DES\	<u>31100.doc</u>	Rock Fill	E 10/15/95 R 4/28/08

SPECIAL PROVISIONS CHECK LIST
Generated - 10/9/12 11:23 AM

Designer:
 Contract No.:

FAP:
 Section:
 County:

DES\	<u>31101.doc</u>	Subbase Granular Material	E 11/5/04
DES\	<u>35500d.doc</u>	Temporary Pavement	E 10/1/95 R 4/23/10
DES\	<u>40600.doc</u>	Clean Existing Pavement Edge Joint	E 1/3/00 R 1/1/07
DES\	<u>40601.doc</u>	Anti-Strip Additive for Hot-Mix Asphalt	E 7/30/10
DES\	<u>40602.doc</u>	Hot-Mix Asphalt - Prime Coat	E 4/29/11
DES\	<u>40604a.doc</u>	Hot-Mix Asphalt Surface Course Surface Tests	E 11/1/03 R 1/1/07
DES\	<u>40613.doc</u>	Payment for Use of Material Transfer Device	E 4/23/10
DES\	<u>40706.doc</u>	Bituminous Prime Coat for Hot-Mix Asphalt Pavement (Full-Depth)	E 8/3/07 R 4/23/10
DES\	<u>40713.doc</u>	Grooved-in Rumble Strip	E 11/16/07 R 7/30/10
DES\	<u>42020.doc</u>	Railroad Approach Pavement	E 10/1/95 R 1/1/07
DES\	<u>42401.doc</u>	Sidewalk Drains	E 3/1/91 R 1/1/07
DES\	<u>42402.doc</u>	Temporary Sidewalks	E 3/1/91 R 2/1/96
DES\	<u>44001.doc</u>	Bridge Wearing Surface Removal	E 7/1/90 R 1/1/07
DES\	<u>44003.doc</u>	Protection of Frames and Lids of Utility Structures	E 3/6/91 R 1/1/07
DES\	<u>44003a.doc</u>	Hot-Mix Asphalt Surface Removal, *** (** mm)	E 3/1/93 R 7/31/09
DES\	<u>44003b.doc</u>	Hot-Mix Asphalt Surface Removal, *** (** mm)	E 2/5/93 R 7/31/09
DES\	<u>44003c.doc</u>	Center Joint Repair System	E 3/1/91 R 1/1/07
DES\	<u>44003d.doc</u>	Pavement Drainage After Cold Milling	E 3/15/96 R 1/1/07
DES\	<u>44003e.doc</u>	Pavement Patching with Hot-Mix Asphalt Surface Removal	E 3/1/97 R 1/1/07
DES\	<u>44003f.doc</u>	Hot-Mix Asphalt Concrete Milling Material	E 11/1/03 R 8/3/07
DES\	<u>44200.doc</u>	Class (*) Patches, Type (**),(***) "	E 1/1/99 R 11/1/07
DES\	<u>44300.doc</u>	Reflective Crack Control Treatment	E 3/1/96 R 1/1/07
DES\	<u>45100.doc</u>	Crack and Joint Sealing	E 6/15/97 R 1/1/07
DES\	<u>48205.doc</u>	Hot-Mix Asphalt Shoulder Resurfacing Required to be Constructed Simultaneously with Mainline Paving	E 4/23/10
DES\	<u>48206.doc</u>	Hot-Mix Asphalt Shoulder Resurfacing Constructed Simultaneously with Mainline Paving	E 1/22/01 R 1/1/07
DES\	<u>50103.doc</u>	Concrete Headwall Removal	E 7/1/90
DES\	<u>50104.doc</u>	Concrete Handrail Removal	E 7/1/90 R 1/1/07
DES\	<u>50300.doc</u>	Bin-Type Retaining Wall	E 7/1/90 R 1/1/07
DES\	<u>50301.doc</u>	Concrete Wearing Surface	E 7/1/90 R 1/1/07
DES\	<u>50302.doc</u>	Surface Filler, Special (Gallon)	E 4/23/10
DES\	<u>50312.doc</u>	Plug Existing Deck Drains	E 1/1/96 R 3/22/01
DES\	<u>50312a.doc</u>	Floor Drain Extension	E 3/22/01
DES\	<u>50317.doc</u>	Bridge Floor Finishing Machine	E 5/1/95 R 1/1/07
DES\	<u>50319.doc</u>	Protective Coat, Special	E 4/23/10
DES\	<u>52100b.doc</u>	Jack and Reposition Bearings	E 11/15/93 R 1/1/09

SPECIAL PROVISIONS CHECK LIST
Generated - 10/9/12 11:23 AM

Designer: _____
 Contract No.: _____

FAP: _____
 Section: _____
 County: _____

DES\	<u>52100c.doc</u>	Jacking and Cribbing	E 1/1/94 R 1/1/07
DES\	<u>54200.doc</u>	Seepage Collar	E 12/1/96
DES\	<u>54201.doc</u>	Remove and Relay Pipe Culverts	E 7/1/90 R 1/1/07
DES\	<u>54204.doc</u>	Pipe Culverts	E 7/1/90 R 1/1/07
DES\	<u>54204e.doc</u>	Backfill - Pipe Culverts	E 10/15/95 R 1/1/07
DES\	<u>55000.doc</u>	Storm Sewer, (Water Main Quality Pipe)	E 1/1/11 R 1/1/12
DES\	<u>55002.doc</u>	Storm Sewer (Special)	E 7/1/90 R 1/1/07
DES\	<u>55007.doc</u>	Backfill, Building Removal	E 8/20/91 R 1/1/07
DES\	<u>55200.doc</u>	Steel Pipe Culvert, Special (Jacked) * inches (* mm)	E 7/1/94 R 1/1/07
DES\	<u>55201.doc</u>	(*Storm Sewer/Pipe Culvert) Jacked in Place, ** inches (** mm)	E 7/1/94 R 1/1/07
DES\	<u>56100.doc</u>	Steel Casings * Inches	E 7/1/90 R 1/1/13
DES\	<u>56101.doc</u>	Steel Casings * Inches	E 7/1/90 R 1/1/13
DES\	<u>60101.doc</u>	Pipe Underdrain	E 8/1/03
DES\	<u>60200a.doc</u>	Inlets, Type G-1	E 10/1/95 R 1/1/07
DES\	<u>60200b.doc</u>	Inlets, Type G-1, Special	E 10/1/95 R 1/1/07
DES\	<u>60200c.doc</u>	Inlets, Type G-1, Double, Special	E 10/1/95 R 1/1/07
DES\	<u>60200d.doc</u>	Inlet Manhole, Type G-1, 4' (1.2 m) Diameter	E 10/1/95 R 1/1/07
DES\	<u>60200e.doc</u>	Inlet-Manhole, Type G-1, 4' (1.2 m) Diameter, Special	E 10/1/95 R 1/1/07
DES\	<u>60200f.doc</u>	Inlet-Manhole, Type G-1, 5' (1.5 m) Diameter	E 10/1/95 R 1/1/07
DES\	<u>60200g.doc</u>	Inlet-Manhole, Type G-1, 5' (1.5 m) Diameter, Special	E 10/1/95 R 1/1/07
DES\	<u>60200h.doc</u>	Inlet-Manhole, Type G-1, 5' (1.5 m) Diameter, Double, Special	E 10/1/95 R 1/1/07
DES\	<u>60200i.doc</u>	Inlet-Manhole, Type G-1, 8' (2.4 m) Diameter, Double, Special	E 10/1/95 R 1/1/07
DES\	<u>60200j.doc</u>	Manhole to be Adjusted with New Type G-1 Frame and Grate	E 10/1/95 R 1/1/07
DES\	<u>60200k.doc</u>	Temporary Inlet Drainage Treatment	E 1/1/97
DES\	<u>60200l.doc</u>	Inlets, Type G-2	E 11/1/03 R 1/1/07
DES\	<u>60200m.doc</u>	Inlets, Type G-1, Double	E 7/31/09
DES\	<u>60504.doc</u>	Filling Existing Inlets	E 7/1/90 R 7/1/94
DES\	<u>60504a.doc</u>	Filling Existing Culverts	E 10/15/95 R 1/1/07
DES\	<u>60504b.doc</u>	Filling Existing Drainage Structures	E 10/15/95 R 1/1/07
DES\	<u>60608.doc</u>	Island Pavement Constructed on Existing Pavement	E 1/1/97 R 1/1/07
DES\	<u>60612.doc</u>	Drainage Holes	E 7/1/90 R 1/1/07
DES\	<u>63000.doc</u>	Erosion Control Curb	E 4/1/91 R 1/1/07
DES\	<u>63001.doc</u>	Guardrail Aggregate Erosion Control	E 2/1/93 R 1/1/07
DES\	<u>63008.doc</u>	Steel Plate Beam Guardrail, Type A, 6.75 Foot Posts	E 7/31/09 R 4/27/12
DES\	<u>63104.doc</u>	Traffic Barrier Terminals, Type 1, Special (Flared) or (Tangent)	E 7/31/09

SPECIAL PROVISIONS CHECK LIST
Generated - 10/9/12 11:23 AM

Designer: _____ FAP: _____
 Contract No.: _____ Section: _____
 County: _____

	DES\	<u>63107.doc</u>	Traffic Barrier Terminals, Type 6	E 7/31/09
	DES\	<u>63111c.doc</u>	Traffic Barrier Terminals	E 2/1/96 R 11/5/04
	DES\	<u>63114.doc</u>	Traffic Barrier Terminals, Type 2	E 7/31/09
	DES\	<u>63200.doc</u>	Guard Post Removal	E 7/1/90 R 1/1/07
	DES\	<u>63500.doc</u>	Flexible Delineator Maintenance	E 5/5/92 R 1/1/94
	DES\	<u>63501.doc</u>	Flexible Delineators	E 10/1/95 R 1/1/07
	DES\	<u>66704.doc</u>	Permanent Survey Marker, Type 1, Bridge Placement	E 7/1/90 R 3/11/11
	DES\	<u>66802.doc</u>	Permanent Survey Ties	E 4/1/91 R 4/27/12
	DES\	<u>67005.doc</u>	Equipment Vault for Nuclear Testing Equipment	E 6/24/93 R 7/1/94
	DES\	<u>68000.doc</u>	Railroad Track Removal	E 11/1/94 R 1/1/07
	DES\	<u>68000a.doc</u>	Railroad Ties Removal and Disposal	E 11/1/94 R 10/1/95
	DES\	<u>68300.doc</u>	Mortared Stone Wall	E 3/1/91 R 1/1/07
√	DES\	<u>70100.doc</u>	Traffic Control Plan	E R
	DES\	<u>70106.doc</u>	Speeding Penalty	E 1/21/05
	DES\	<u>70108b.doc</u>	Traffic Control and Protection Standard 701331 (Special)	E 10/15/95 R 7/31/09
	DES\	<u>70114.doc</u>	Width Restriction Signing	E 11/1/07 R 1/1/12
	DES\	<u>70120.doc</u>	Traffic Control and Protection BLR 21 and BLR 21 (Special)	E 4/25/08
	DES\	<u>70121.doc</u>	Traffic Control and Protection BLR 22 and BLR 22 (Special)	E 4/25/08 R 7/31/09
	DES\	<u>70122.doc</u>	Traffic Control and Protection Standard 701606 (Special)	E 7/31/09
	DES\	<u>70300.doc</u>	Pavement Marking Removal/Work Zone Pavement Marking Removal	E 4/29/05
	DES\	<u>70400.doc</u>	Temporary Concrete Barrier, State Owned and Temporary Concrete Barrier Terminal Sections, State Owned	E 5/1/91 R 1/1/07
	DES\	<u>70400a.doc</u>	Temporary Concrete Barrier Reflectors	E 1/21/05
	DES\	<u>78000.doc</u>	Thermoplastic Pavement Marking Equipment	E 7/1/90 R 1/1/07
	DES\	<u>78007.doc</u>	Preformed Plastic Pavement Markings	E 7/31/09
	DES\	<u>78100.doc</u>	Temporary Raised Reflective Pavement Marker	E 10/1/95 R 1/1/07
	DES\	<u>81000.doc</u>	Conduit, Pushed or Trenched	E 10/1/91 R 1/1/07
	DES\	<u>81500.doc</u>	Trench & Backfill, Special for Conduit Installation Beneath Bituminous Shoulders	E 3/21/94 R 1/1/07
	DES\	<u>86300.doc</u>	Terminal Facility	E 3/21/94 R 1/1/07
	DES\	<u>87300.doc</u>	Electric Cable in Conduit, Lead-In, No. 18	E 3/21/94 R 10/15/01
	DES\	<u>88600.doc</u>	Detector Loop, Special for Traffic Counters	E 3/21/94 R 1/1/07
	DES\	<u>88600a.doc</u>	Detector Loops, Type 1	E 3/1/96 R 8/3/07

BDE Special Provisions Checklist

January 18, 2013 and March 8, 2013 Lettings

Note: Specials that go in every contract have already been marked with an "X" for you.

Designer: _____
 Contract No.: _____
 Letting: _____

FAP: _____
 Section: _____
 County: _____

BDE SPECIAL PROVISIONS
 For the January 18 and March 8, 2013 Lettings

The following special provisions indicated by an "x" are applicable to this contract and will be included by the Project Development and Implementation Section of the BD&E. An * indicates a new or revised special provision for the letting.

<u>File Name</u>	<u>#</u>	<u>Special Provision Title</u>	<u>Effective</u>	<u>Revised</u>
80240	1	<input type="checkbox"/> Above Grade Inlet Protection	July 1, 2009	Jan. 1, 2012
80099	2	<input type="checkbox"/> Accessible Pedestrian Signals (APS)	April 1, 2003	Jan. 1, 2007
80192 5 <input type="checkbox"/> Automated Flagger Assistance Device Jan. 1, 2008				
80173	6	<input type="checkbox"/> Bituminous Materials Cost Adjustments	Nov. 2, 2006	Jan. 1, 2012
80241	7	<input type="checkbox"/> Bridge Demolition Debris	July 1, 2009	
80276	8	<input type="checkbox"/> Bridge Relief Joint Sealer	Jan. 1, 2012	Aug. 1, 2012
50261	9	<input type="checkbox"/> Building Removal-Case I (Non-Friable and Friable Asbestos)	Sept. 1, 1990	April 1, 2010
50481	10	<input type="checkbox"/> Building Removal-Case II (Non-Friable Asbestos)	Sept. 1, 1990	April 1, 2010
50491	11	<input type="checkbox"/> Building Removal-Case III (Friable Asbestos)	Sept. 1, 1990	April 1, 2010
50531	12	<input type="checkbox"/> Building Removal-Case IV (No Asbestos)	Sept. 1, 1990	April 1, 2010
80292	13	<input type="checkbox"/> Coarse Aggregate in Bridge Approach Slabs/Footings	April 1, 2012	
80198 15 <input type="checkbox"/> Completion Date (via calendar days) April 1, 2008				
80199	16	<input type="checkbox"/> Completion Date (via calendar days) Plus Working Days	April 1, 2008	
80293	17	<input type="checkbox"/> Concrete Box Culverts with Skews > 30 Degrees and Design Fills ≤ 5 Feet	April 1, 2012	
80294	18	<input type="checkbox"/> Concrete Box Culverts with Skews ≤ 30 Degrees Regardless of Design Fill and Skews > 30 Degrees with Design Fills > 5 Feet	April 1, 2012	
80277 20 <input type="checkbox"/> Concrete Mix Design – Department Provided Jan. 1, 2012				
80261	21	<input type="checkbox"/> Construction Air Quality – Diesel Retrofit	June 1, 2010	
80029	22	<input type="checkbox"/> Disadvantaged Business Enterprise Participation	Sept. 1, 2000	Aug. 2, 2011
80265 25 <input type="checkbox"/> Friction Aggregate Jan. 1, 2011				
80229	26	<input type="checkbox"/> Fuel Cost Adjustment	April 1, 2009	July 1, 2009
80303	27	<input type="checkbox"/> Granular Materials	Nov. 1, 2012	
80246 30 <input type="checkbox"/> Hot-Mix Asphalt – Density Testing of Longitudinal Joints Jan. 1, 2010 April 1, 2012				
80045 32 <input type="checkbox"/> Material Transfer Device June 15, 1999 Jan. 1, 2009				
80297	33	<input type="checkbox"/> Modified Urethane Pavement Marking	April 1, 2012	
80165	34	<input type="checkbox"/> Moisture Cured Urethane Paint System	Nov. 1, 2006	Jan. 1, 2010
80231 36 <input type="checkbox"/> Pavement Marking Removal April 1, 2009				
80298	37	<input type="checkbox"/> Pavement Marking Tape Type IV	April 1, 2012	
80254	38	<input type="checkbox"/> Pavement Patching	Jan. 1, 2010	
80022	39	<input checked="" type="checkbox"/> Payments to Subcontractors	June 1, 2000	Jan. 1, 2006
80278 41 <input type="checkbox"/> Planting Woody Plants Jan. 1, 2012 Aug. 1, 2012				

Note: Specials that go in every contract have already been marked with an "X" for you.

Designer: _____

FAP: _____

Contract No.: _____

Section: _____

Letting: _____

County: _____

<u>File Name</u>	<u>#</u>	<u>Special Provision Title</u>	<u>Effective</u>	<u>Revised</u>
80300	44	<input type="checkbox"/> Preformed Plastic Pavement Marking Type D - Inlaid	April 1, 2012	
80218	45	<input type="checkbox"/> Preventive Maintenance – Bituminous Surface Treatment	Jan. 1, 2009	April 1, 2012
80219	46	<input type="checkbox"/> Preventive Maintenance – Cape Seal	Jan. 1, 2009	April 1, 2012
80220	47	<input type="checkbox"/> Preventive Maintenance – Micro-Surfacing	Jan. 1, 2009	April 1, 2012
80221	48	<input type="checkbox"/> Preventive Maintenance – Slurry Seal	Jan. 1, 2009	April 1, 2012
34261	50	<input type="checkbox"/> Railroad Protective Liability Insurance	Dec. 1, 1986	Jan. 1, 2006
80157	51	<input type="checkbox"/> Railroad Protective Liability Insurance (5 and 10)	Jan. 1, 2006	
80283	53	<input type="checkbox"/> Removal and Disposal of Regulated Substances	Jan. 1, 2012	
80224	54	<input type="checkbox"/> Restoring Bridge Approach Pavements Using High-Density Foam	Jan. 1, 2009	Jan. 1, 2012
80271	55	<input type="checkbox"/> Safety Edge	April 1, 2011	
80307	56	<input type="checkbox"/> Seeding	Nov. 1, 2012	
80127	57	<input type="checkbox"/> Steel Cost Adjustment	April 2, 2004	April 1, 2009
80255	58	<input type="checkbox"/> Stone Matrix Asphalt	Jan. 1, 2010	Jan. 1, 2012
80143	59	<input checked="" type="checkbox"/> Subcontractor Mobilization Payments	April 2, 2005	April 1, 2011
80308	61	<input type="checkbox"/> Synthetic Fibers in Concrete Gutter, Curb, Median and Paved Ditch	Nov. 1, 2012	
80286	62	<input type="checkbox"/> Temporary Erosion and Sediment Control	Jan. 1, 2012	
80225	63	<input type="checkbox"/> Temporary Raised Pavement Marker	Jan. 1, 2009	
80301	65	<input type="checkbox"/> Tracking the Use of Pesticides	Aug. 1, 2012	
80273	66	<input type="checkbox"/> Traffic Control Deficiency Deduction	Aug. 1, 2011	
20338	67	<input type="checkbox"/> Training Special Provisions	Oct. 15, 1975	
80270	69	<input checked="" type="checkbox"/> Utility Coordination and Conflicts	April 1, 2011	Jan. 1, 2012
80288	70	<input type="checkbox"/> Warm Mix Asphalt	Jan. 1, 2012	Nov. 1, 2012
80302	71	<input type="checkbox"/> Weekly DBE Trucking Reports	June 2, 2012	
80289	72	<input type="checkbox"/> Wet Reflective Thermoplastic Pavement Marking	Jan. 1, 2012	
80071	73	<input type="checkbox"/> Working Days	Jan. 1, 2002	

The following special provisions are either in the 2013 Standard Specifications, the 2013 Recurring Special Provisions, or the special provisions Portland Cement Concrete, QC/QA of Concrete Mixtures, or Placing and Consolidating Concrete:

<u>File Name</u>	<u>Special Provision Title</u>	<u>New Location</u>	<u>Effective</u>	<u>Revised</u>
80275	Agreement to Plan Quantity	Article 202.07	Jan. 1, 2012	
80291	Calcium Chloride Accelerator for Class PP-2 Concrete	Recurring CS #28	April 1, 2012	
80237	Construction Air Quality – Diesel Vehicle Emissions Control	Articles 105.03 and 107.41	April 1, 2009	Jan. 2, 2012
80239	Construction Air Quality – Idling Restrictions	Articles 105.03 and 107.41	April 1, 2009	
80177	Digital Terrain Modeling for Earthwork Calculations	Recurring CS #32	April 1, 2007	
80272	Drainage and Inlet Protection Under Traffic	Articles 603.02 and 603.07	April 1, 2011	Jan. 1, 2012
80228	Flagger at Side Roads and Entrances	Articles 701.13 and 701.20	April 1, 2009	
80109	Impact Attenuators	Section 643	Nov. 1, 2003	Jan. 1, 2012
80110	Impact Attenuators, Temporary	Section 706	Nov. 1, 2003	Jan. 1, 2012
80203	Metal Hardware Cast into Concrete	Articles 503.02, 504.02, and 1006.13	April 1, 2008	Jan. 1, 2012
80290	Payrolls and Payroll Records	Recurring CS #5	Jan. 2, 2012	

Note: Specials that go in every contract have already been marked with an "X" for you.

Designer: _____

FAP: _____

Contract No.: _____

Section: _____

Letting: _____

County: _____

<u>File Name</u>	<u>Special Provision Title</u>	<u>New Location</u>	<u>Effective</u>	<u>Revised</u>
80299	Portland Cement Concrete Inlay or Overlay	Recurring CS #29	April 1, 2012	
80280	Portland Cement Concrete Sidewalk	Article 424.07	Jan. 1, 2012	
80152	Self-Consolidating Concrete for Cast-In-Place Construction	The following special provisions: Portland Cement Concrete, QC/QA of Concrete Mixtures and Placing and Consolidating Concrete	Nov. 1, 2005	April 1, 2012
80132	Self-Consolidating Concrete for Precast and Precast Prestressed Products	The following special provisions: Portland Cement Concrete, QC/QA of Concrete Mixtures and Placing and Consolidating Concrete	July 1, 2004	April 1, 2012
80284	Shoulder Rumble Strips	Article 642.05	Jan. 1, 2012	
80285	Sidewalk, Corner or Crosswalk Closure	Articles 701.03, 701.15, and 1106.02	Jan. 1, 2012	
80075	Surface Testing of Pavements (Section 406 overlay portion will remain a special provision and will now be called "Surface Testing of HMA Overlays".)	Articles 407.09, 407.12, 420.10, 420.20, and 1101.10	April 1, 2002	Jan. 1, 2007
80287	Type G Inlet Box	Article 610.09	Jan. 1, 2012	

The following special provisions require additional information from the designer. The additional information needs to be included in a separate document attached to this check sheet. The Project Development and Implementation section will then include the information in the applicable special provision. The Special Provisions are:

- Bridge Demolition Debris
- Building Removal-Case I
- Building Removal-Case II
- Building Removal-Case III
- Building Removal-Case IV
- Completion Date
- Completion Date Plus Working Days
- DBE Participation
- Material Transfer Device
- Railroad Protective Liability Insurance
- Training Special Provisions
- Working Days

Designer Notes
Recurring Special Provisions

Designer Notes for January 1, 2013 Recurring Special Provisions

(Updated for January 18, 2013 and March 8, 2013 lettings.)

1. Designer Note: This check sheet is required in all contracts that involve Federal funds.
2. Designer Note: This check sheet is required in all Federal contracts.
3. Designer Note: This check sheet is required in all contracts.
4. Designer Note: This check sheet is required in all contracts involving State funds only.
5. Designer Note: This check sheet is required in all contracts involving State funds only.
6. Designer Note: Include in all contracts where Asbestos Bearing Pad Removal is part of the structure work.
7. Designer Note: Include in all contracts where the existing bridge deck HMA surface is to be removed and the waterproofing membrane contains asbestos and will be removed. The designer must have in the project files a completed "Asbestos Determination Certificate" for every bridge within the project limits. The District Bridge Maintenance Engineer and/or the District Hydraulics Engineer can provide copies of these certificates. If your project has any bridge deck containing asbestos, insert this special provision as well as the General Notes entitled "Asbestos Bridge Wearing Surface Removal".
8. Designer Note: This check sheet will be required for those contracts that will involve Contractor work on haul road stream crossings, other temporary stream crossings, and in stream work pads. Contracts that would generally involve this type of work would be bridges/structures, new or rebuilt, and contracts involving earth excavation, embankment or borrow excavation. Discuss these types of work operations and any other stream related work with your Project Engineer. Any in-stream crossing or other work will require an individual 404 permit from the Corps of Engineers. Be sure to let the Hydraulics Engineer (Jim Miller) know as soon as possible that a Corps permit will be needed. The permit has a lead-time and is required for the project to proceed to letting.
9. Designer Note: (See #10 below.) Depending on IDOT manpower, this check sheet will be included as a pay item when the Contractor will be required to do all contract staking, except bridges. A large span culvert measuring more than 6 meters (20 feet) along the survey line will require a structure number be assigned to the structure. This will require that the Designer, if he is calling for Contractor staking, use the check sheet entitled Construction Layout Stakes and not the check sheet entitled Construction Layout Stakes Except for Structures. Discuss with the Bureau of Project Implementation (Construction) as to what manpower sources are available.
10. Designer Note: Depending on IDOT manpower needs, this check sheet will be included as a pay item when the Contractor will be required to do all contract staking, including bridges. This check sheet should be used for a large box culvert or a multi pipe that will require a structure number. This would be a structure that will have a span length along survey line of more than 6 meters (20 feet).

Discuss this check sheet with the Bureau of Project Implementation (Construction) as to what manpower sources are available.

11. Designer Note: This special provision specifies the requirements for geotextile fabric for use on railroad crossings.

Include only on projects where the railroad crossing is a contract pay item. Also may be required for temporary crossings.

Railroad crossings are generally (99%) handled by the Railroad through an agreement and not part of our contract. If in doubt as to how to handle, discuss with Project Support.

12. Designer Note: Use this check sheet where existing pavement is being reconstructed and voids are evident under the existing pavement that can be filled by grouting. Discuss with Maintenance Field Engineer responsible for the area.

NOTE: A detail of the slab movement detection device is included in CADD and this drawing must be included in your contract plans.

13. Designer Note: This check sheet will be required on a contract where cold milling is required but where the cold milled area will not be overlaid. Include CADD Standard 440001 in your plans. If your contract is to be cold milled and the area overlaid, you should use one of the two District special provisions on this subject, not this check sheet.

14. Designer Note: This check sheet requires that once a lift of bituminous resurfacing is placed on a lane of pavement, any adjoining bituminous shoulder shall be resurfaced with an equal thickness before any other lane is resurfaced for each lift of resurfacing. Insert this special on resurfacing projects which meet the following criteria: All four lane interstates and freeways, all four lane expressways, four lane highways with ADT > 25,000 or peak one-way VPH > 1700, two lane highways with ADT > 10,000 or peak one-way VPH > 800.

15. Designer Note: This check sheet should be used on resurfacing projects to address areas which need repair, but do not warrant full depths repair. Joints and cracks, which exhibit environmental distresses such as spalling and "D" cracking or contain maintenance patching, are eligible for using this method of repair. Joints and cracks which exhibit load related distresses such as pumping, alligator cracking, corner breaks, compression failures, subgrade failures or punch outs should not use this method of repair. Discuss use with your Project Engineer.

16. Designer Note: Intended to remove thick bituminous overlay so that the original pavement can be examined and then patched, if necessary. It also further defines specific pay items for work involved.

17. Designer Note: This check sheet was developed by Materials and Physical Research as an alternate to replacing Preformed Joint Sealer and Neoprene Expansion Joints up to 65 mm (2 ½ inches). Include with any projects that have POLYMER CONCRETE as a pay item.

18. **Designer Note:** This rehabilitation process can be used in a variety of gravity applications such as trenchless rehabilitation of sanitary sewers, storm sewers, and process piping. Insert this special provision if trenchless repair of the items listed above is selected. Prior to selection consult your Project Engineer. Additional information such as size of pipe to be lined, number of laterals, and manhole treatment may be necessary.
19. **Designer Note:** This check sheet calls for CA 16 for backfill and wrapping the trench. Discuss usage with Implementation.
20. **Designer Note:** This check sheet was developed by the Central Bureau of Traffic and should be incorporated into all plans containing guardrail, barrier wall or bridge rail. The designer is required to specify the color of all reflectors to be placed and to provide appropriate traffic control standards for the installation of reflectors/markers. It is the District's option to select the type of reflector marker for use on guardrail and barrier walls, and the type of terminal marker for guardrail. This option should be specified by the pay item used. The District prefers use of the top mounted reflector Type C on barrier walls. Include Highway Standards 635006 and 635011 in the plans if this Check Sheet is used.
21. **Designer Note:** This check sheet was developed to obtain the desired pipe coating on bike racks. Use on all projects with bike racks.
22. **Designer Note:** This special provision covers the installation of temporary glare screens on temporary concrete barrier. Glare screens may be needed on temporary concrete barriers separating opposing lanes of traffic, especially on horizontal and vertical curves where oncoming headlight glare could be a problem. Discuss usage with your project engineer.
23. **Designer Note:** This special provision is for use on bridge contracts where staging is required and the District wants the contractor to have an option to post-mounting the temporary bridge and traffic signals. Discuss use with the District Traffic Control Technician.
24. **Designer Note:** Intended for use on all freeway/expressway contracts with lane closures as shown on Highway Standard 701400. It may also be used at the District's discretion on high visibility projects and/or projects that will require several months to complete.
25. **Designer Note:** This check sheet should be included for all projects containing roadway lighting. The designer should also include CADD Standard 701301-D4 in the plans.
26. **Designer Note:** This check sheet was developed to address difficulties with obtaining metric sized bolts. Include in all metric projects, which contain or could contain any type of bolted connection.
27. **Designer Note:** This check sheet was developed to address difficulties with obtaining metric sized reinforcement bars. Include in all metric projects containing reinforcement bars.

28. Designer Note: This special provision not to be used in District Four. Not recommended for use on recently constructed pavements or bridge decks. This is not recommended when there is steel in the patches due to the corrosion the calcium chloride causes.
29. Designer Note: Insert into contracts where a PCC inlay or overlay is selected. This method is for locations where excessive rutting has become a problem. Discuss with the Project Engineer, Operations, and Implementation before using. Also, refer to BDE Manual, Chapter 53 before using.
30. Designer Note: Do not use Check Sheet #30 unless requested by Materials.
31. Designer Note: Do not use Check #31. Use BDE special instead. This check sheet has been modified by BDE Special "Quality Control/Quality Assurance of Concrete Mixtures."
32. Designer Note: This special allows the use of digital terrain modeling for field measurements of earthwork. This is to be used at the district's discretion. Discuss it with your Project Engineer and Construction.

**Index for
Supplemental Specifications
and
Recurring Special Provisions**

INDEX
FOR
SUPPLEMENTAL SPECIFICATIONS
AND RECURRING SPECIAL PROVISIONS

Adopted January 1, 2013

This index contains a listing of SUPPLEMENTAL SPECIFICATIONS, frequently used RECURRING SPECIAL PROVISIONS, and LOCAL ROADS AND STREETS RECURRING SPECIAL PROVISIONS.

ERRATA Standard Specifications for Road and Bridge Construction (Adopted 1-1-12) (Revised 1-1-13)

SUPPLEMENTAL SPECIFICATIONS

<u>Std. Spec. Sec.</u>		<u>Page No.</u>
105	Control of Work	1
107	Legal Regulations and Responsibility to Public	2
202	Earth and Rock Excavation	4
211	Topsoil and Compost	5
407	Hot-Mix Asphalt Pavement (Full-Depth)	6
420	Portland Cement Concrete Pavement	10
424	Portland Cement Concrete Sidewalk	12
503	Concrete Structures	13
504	Precast Concrete Structures	14
540	Box Culverts	15
603	Adjusting Frames and Grates of Drainage and Utility Structures	16
610	Shoulder Inlets with Curb	18
642	Shoulder Rumble Strips	19
643	Impact Attenuators	20
701	Work Zone Traffic Control and Protection	22
706	Impact Attenuators, Temporary	24
780	Pavement Striping	26
860	Master Controller	27
1006	Metals	28
1042	Precast Concrete Products	29
1073	Controller	30
1083	Elastomeric Bearings	31
1101	General Equipment	32
1106	Work Zone Traffic Control Devices	34

RECURRING SPECIAL PROVISIONS

The following RECURRING SPECIAL PROVISIONS indicated by an "X" are applicable to this contract and are included by reference:

<u>CHECK SHEET #</u>		<u>PAGE NO.</u>
1	Additional State Requirements for Federal-Aid Construction Contracts (Eff. 2-1-89) (Rev. 1-1-10)	35
2	Subletting of Contracts (Federal-Aid Contracts) (Eff. 1-1-88) (Rev. 5-1-93)	38
3	EEO (Eff. 7-21-78) (Rev. 11-18-80)	39
4	Specific Equal Employment Opportunity Responsibilities Non Federal-Aid Contracts (Eff. 3-20-89) (Rev. 1-1-94)	49
5	Required Provisions - State Contracts (Eff. 4-1-85) (Rev. 1-1-13)	54
6	Asbestos Bearing Pad Removal (Eff. 11-1-03)	59
7	Asbestos Waterproofing Membrane and Asbestos Hot-Mix Asphalt Surface Removal (Eff. 6-1-89) (Rev. 1-1-09)	60
8	Haul Road Stream Crossings, Other Temporary Stream Crossings, and In-Stream Work Pads (Eff. 1-2-92) (Rev. 1-1-98)	61
9	Construction Layout Stakes Except for Bridges (Eff. 1-1-99) (Rev. 1-1-07)	62
10	Construction Layout Stakes (Eff. 5-1-93) (Rev. 1-1-07)	65
11	Use of Geotextile Fabric for Railroad Crossing (Eff. 1-1-95) (Rev. 1-1-07)	68
12	Subsealing of Concrete Pavements (Eff. 11-1-84) (Rev. 1-1-07)	70
13	Hot-Mix Asphalt Surface Correction (Eff. 11-1-87) (Rev. 1-1-09)	74
14	Pavement and Shoulder Resurfacing (Eff. 2-1-00) (Rev. 1-1-09)	76
15	PCC Partial Depth Hot-Mix Asphalt Patching (Eff. 1-1-98) (Rev. 1-1-07)	77
16	Patching with Hot-Mix Asphalt Overlay Removal (Eff. 10-1-95) (Rev. 1-1-07)	79
17	Polymer Concrete (Eff. 8-1-95) (Rev. 1-1-08)	80
18	PVC Pipeliner (Eff. 4-1-04) (Rev. 1-1-07)	82
19	Pipe Underdrains (Eff. 9-9-87) (Rev. 1-1-07)	83
20	Guardrail and Barrier Wall Delineation (Eff. 12-15-93) (Rev. 1-1-12)	84
21	Bicycle Racks (Eff. 4-1-94) (Rev. 1-1-12)	88
22	Temporary Modular Glare Screen System (Eff. 1-1-00) (Rev. 1-1-07)	90
23	Temporary Portable Bridge Traffic Signals (Eff. 8-1-03) (Rev. 1-1-07)	92
24	Work Zone Public Information Signs (Eff. 9-1-02) (Rev. 1-1-07)	94
25	Night Time Inspection of Roadway Lighting (Eff. 5-1-96)	95
26	English Substitution of Metric Bolts (Eff. 7-1-96)	96
27	English Substitution of Metric Reinforcement Bars (Eff. 4-1-96) (Rev. 1-1-03)	97
28	Calcium Chloride Accelerator for Portland Cement Concrete (Eff. 1-1-01) (Rev. 1-1-13)	98
29	Portland Cement Concrete Inlay or Overlay for Pavements (Eff. 11-1-08) (Rev. 1-1-13)	99
30	Quality Control of Concrete Mixtures at the Plant (Eff. 8-1-00) (Rev. 1-1-11)	102
31	Quality Control/Quality Assurance of Concrete Mixtures (Eff. 4-1-92) (Rev. 1-1-11)	110
32	Digital Terrain Modeling for Earthwork Calculations (Eff. 4-1-07)	122

BDE Special Provisions

Numeric Index

REVISED INDEX

NUMERIC DESIGN INTERIM SPECIAL PROVISIONS (ISP's)

Get a copy of the current check list from the Program Development Secretary, indicate which ISP's are to be included in your set of special provisions, fill in any blanks as indicated on the check list, and include with your set of special provisions to be sent to Springfield where they will be inserted.

<u>Standard Spec. No.</u>	<u>PC No.</u>	<u>Item</u>
100.00	10000	Errata for the 2012 Standard Specifications
105.04	10504	Traffic Control Deficiency Deduction
105.07	10507	Utility Coordination and Conflicts
107.01	10701	Construction Air Quality – Diesel Retrofit
107.11a	10711a	Railroad Protective Liability Insurance
107.11b	10711b	Railroad Protective Liability Insurance (5 and 10)
107.19a	10719a	Building Removal Case I
107.19b	10719b	Building Removal Case II
107.19c	10719c	Building Removal Case III
107.19d	10719d	Building Removal Case IV
107.23	10723	Tracking the Use of Pesticides
107.38	10738	Bridge Demolition Debris
108.05	10805	Working Days
108.05a	10805a	Completion Date (Via Calendar Days)
108.05b	10805b	Completion Date (Via Calendar Days) Plus Working Days
108.06	10806	Training Special Provision
108.06a	10806a	Disadvantaged Business Enterprise Participation
108.06b	10806b	Weekly DBE Trucking Reports

NUMERIC DESIGN INTERIM SPECIAL PROVISIONS (ISP's)

<u>Standard Spec. No.</u>	<u>PC No.</u>	<u>Item</u>
109.00a	10900a	Steel Cost Adjustment
109.01	10901	Bituminous Materials Cost Adjustments
109.03	10903	Fuel Cost Adjustment
109.07	10907	Payments to Subcontractors
250.07	25007	Seeding
253.00	25300	Planting Woody Plants
280.02	28002	Above Grade Inlet Protection
280.04	28004	Temporary Erosion and Sediment Control
303.00	30300	Aggregate Subgrade Improvement
312.26	31226	Portland Cement Concrete
400.01	40001	Preventive Maintenance – Cape Seal
400.02	40002	Preventive Maintenance – Micro-Surfacing
400.03	40003	Preventive Maintenance – Slurry Seal
400.04	40004	Preventive Maintenance – Bituminous Surface Treatment
406.00	40600	Warm Mix Asphalt
406.00f	40600f	Material Transfer Device
406.03	40603	Surface Testing of Hot-Mix Asphalt Overlays
406.05	40605	Safety Edge
406.06	40606	Stone Matrix Asphalt
406.07	40607	Hot-Mix Asphalt – Density Testing of Longitudinal Joints
420.16	42016	Restoring Bridge Approach Pavements Using High-Density Foam
503.06	50306	Placing and Consolidating Concrete
503.19	50319	Bridge Relief Joint Sealer

NUMERIC DESIGN INTERIM SPECIAL PROVISIONS (ISP's)

<u>Standard Spec. No.</u>	<u>PC No.</u>	<u>Item</u>
504.00	50400	Concrete Box Culverts with Skews > 30 Degrees and Design Fills ≤ 5 Feet
504.04	50404	Concrete Box Culverts with Skews ≤ 30 Degrees Regardless of Design Fill and Skews >30 Degrees with Design Fills > 5 Feet
542.00	54200	Concrete End Sections for Pipe Culverts
542.01	54201	Traversable Pipe Grate
543.00	54300	Insertion Lining of Culverts
606.02	60602	Synthetic Fibers in Concrete Gutter, Curb, Median, and Paved Ditch
643.00	64300	High Tension Cable Median Barrier
669.01	69901	Removal and Disposal of Regulated Substances
671.00	67100	Subcontractor Mobilization Payments
701.00	70100	Automated Flagger Assistance Devices
701.17	70117	Pavement Patching
703.00	70300	Temporary Raised Pavement Marker
703.02	70302	Pavement Marking Tape Type IV
780.00	780.00	Wet Reflective Thermoplastic Pavement Marking
780.01	78001	Modified Urethane pavement Marking
780.02	78002	Preformed Plastic Pavement Marking Type D - Inlaid
780.03	780.03	Grooving for Recessed Pavement Markings
780.13	78013	Polyurea Pavement Markings
783.03	78303	Pavement Marking Removal
888.00	88800	Accessible Pedestrian Signals (APS)
1003.04	100304	Granular Materials
1004.01	100401	Friction Aggregate
1004.02	100402	Coarse Aggregate in Bridge Approach Slabs/Footings

NUMERIC DESIGN INTERIM SPECIAL PROVISIONS (ISP's)

<u>Standard Spec. No.</u>	<u>PC No.</u>	<u>Item</u>
1006.09	100609	Anchor Bolts
1008.27	100827	Moisture Cured Urethane Paint System
1020.05a	102005a	Concrete Mix Design – Department Provided
1020.16	102016	Quality Control/Quality Assurance of Concrete Mixtures
1031.00	103100	Reclaimed Asphalt Pavement and Reclaimed Asphalt Shingles
1040.03	104003	Drain Pipe, Tile, Drainage Mat, and Wall Drain
1082.01	108201	Fabric Bearing Pads
1088.01	108801	Coated Galvanized Steel Conduit
1106.02i	110602i	Movable Traffic Barrier
1106.02k	110602k	Temporary Water Filled Barrier

BDE Special Provisions

Alphabetic Index

REVISED INDEX
10/09/12

ALPHABETIC LIST OF DESIGN INTERIM SPECIAL PROVISIONS (ISP's)

Get a copy of the current check list from the Program Development Secretary, indicate which ISP's are to be included in your set of special provisions, fill in any blanks as indicated on the check list, and include with your set of special provisions to be sent to Springfield where they will be inserted.

<u>Standard Spec. No.</u>	<u>PC No.</u>	<u>Item</u>
280.02	28002	Above Grade Inlet Protection
888.00	88800	Accessible Pedestrian Signals (APS)
303.00	30300	Aggregate Subgrade Improvement
1006.09	100609	Anchor Bolts
701.00	70100	Automated Flagger Assistance Devices
109.01	10901	Bituminous Materials Cost Adjustment
107.38	10738	Bridge Demolition Debris
503.19	50319	Bridge Relief Joint Sealer
107.19a	10719a	Building Removal Case I
107.19b	10719b	Building Removal Case II
107.19c	10719c	Building Removal Case III
107.19d	10719d	Building Removal Case IV
1004.02	100402	Coarse Aggregate in Bridge Approach Slabs/Footings
1088.01	108801	Coated Galvanized Steel Conduit
108.05a	10805a	Completion Date (Via Calendar Days)
108.05b	10805b	Completion Date (Via Calendar Days) Plus working Days
504.00	50400	Concrete Box Culverts with Skews > 30 Degrees and Design Fills \leq 5 Feet
504.04	50404	Concrete Box Culverts with Skews \leq 30 Degrees Regardless of Design Fill and Skews >30 Degrees with Design Fills > 5 Feet
542.00	54200	Concrete End Sections for Pipe Culverts
503.19	50319	Concrete Joint Sealer

REVISED INDEX
10/09/12

ALPHABETIC LIST OF DESIGN INTERIM SPECIAL PROVISIONS (ISP's)

<u>Standard Spec. No.</u>	<u>PC No.</u>	<u>Item</u>
1020.05a	102005a	Concrete Mix Design – Department Provided
107.01	10701	Construction Air Quality – Diesel Retrofit
108.06a	10806a	Disadvantaged Business Enterprise Participation
1040.03	104003	Drain Pipe, Tile, Drainage Mat, and Wall Drain
100.00	10000	Errata for the 2012 Standard Specifications
1082.01	108201	Fabric Bearing Pads
1004.01	100401	Friction Aggregate
109.03	10903	Fuel Cost Adjustment
1003.04	100304	Granular Materials
780.03	780.03	Grooving for Recessed Pavement Markings
643.00	64300	High Tension Cable Median Barrier
406.07	40607	Hot-Mix Asphalt-Density Testing of Longitudinal Joints
543.00	54300	Insertion Lining of Culverts
406.00f	40600f	Material Transfer Device
780.01	78001	Modified Urethane Pavement Marking
1008.27	100827	Moisture Cured Urethane Paint System
1106.02i	110602i	Movable Traffic Barrier
783.03	78303	Pavement Marking Removal
703.02	70302	Pavement Marking Tape Type IV
701.17	70117	Pavement Patching
109.07	10907	Payments to Subcontractors
503.06	50306	Placing and Consolidating Concrete
253.00	25300	Planting Woody Plants
780.13	78013	Polyurea Pavement Markings

REVISED INDEX

10/09/12

ALPHABETIC LIST OF DESIGN INTERIM SPECIAL PROVISIONS (ISP's)

<u>Standard Spec. No.</u>	<u>PC No.</u>	<u>Item</u>
312.26	31226	Portland Cement Concrete
780.00	78000	Preformed Plastic Pavement Marking Type D - Inlaid
400.04	40004	Preventive Maintenance - Bituminous Surface Treatment
400.01	40001	Preventive Maintenance – Cape Seal
400.02	40002	Preventive Maintenance – Micro-Surfacing
400.03	40003	Preventive Maintenance – Slurry Seal
1020.16	102016	Quality Control/Quality Assurance of Concrete Mixtures
107.11	10711a	Railroad Protective Liability Insurance
107.11	10711b	Railroad Protective Liability Insurance (5 and 10)
1031.00	103100	Reclaimed Asphalt Pavement and Reclaimed Asphalt Singles
669.01	66901	Removal and Disposal of Regulated Substances
420.16	42016	Restoring Bridge Approach Pavements Using High-Density Foam
406.05	40605	Safety Edge
250.07	25007	Seeding
109.00	10900a	Steel Cost Adjustment
406.06	40606	Stone Matrix Asphalt
671.00	67100	Subcontractor Mobilization Payments
406.03	40603	Surface Testing of Hot-Mix Asphalt Overlays
606.02	60602	Synthetic Fibers in Concrete Gutters, Curb, Median, and Paved Ditch
280.04	28004	Temporary Erosion and Sediment Control
703.00	70300	Temporary Raised Pavement Marker
1106.02k	110602k	Temporary Water Filled Barrier
107.23	10723	Tracking the Use of Pesticides

REVISED INDEX
10/09/12

ALPHABETIC LIST OF DESIGN INTERIM SPECIAL PROVISIONS (ISP's)

<u>Standard Spec. No.</u>	<u>PC No.</u>	<u>Item</u>
105.04	10504	Traffic Control Deficiency Deduction
108.06	10806	Training Special Provision
542.01	54201	Traversable Pipe Grate
105.07	10507	Utility Coordination and Conflicts
406.00	40600	Warm Mix Asphalt
108.06b	10806b	Weekly DBE Trucking Reports (BDE)
780.00	78000	Wet Reflective Thermoplastic Pavement Marking
108.05	10805	Working Days

Designer Note: Insert into all projects utilizing aggregate subgrade improvements. When using also include BDE special "Reclaimed Asphalt Pavement (RAP) and Reclaimed Asphalt Shingles (RAS)." Check with district Soils Engineer to determine thickness.

AGGREGATE SUBGRADE IMPROVEMENT (BDE)

Effective: April 1, 2012
Revised: January 1, 2013

Add the following Section to the Standard Specifications:

"SECTION 303. AGGREGATE SUBGRADE IMPROVEMENT

303.01 Description. This work shall consist of constructing an aggregate subgrade improvement.

303.02 Materials. Materials shall be according to the following.

Item	Article/Section
(a) Coarse Aggregate	1004.06
(b) Reclaimed Asphalt Pavement (RAP) (Notes 1, 2, and 3)	1031

Note 1. Crushed RAP, from either full depth or single lift removal, may be mechanically blended with aggregate gradations CS 01, CS 02, and RR 01 but shall not exceed 40 percent of the total product. The top size of the RAP shall be less than 4 in. (100 mm) and well graded.

Note 2. RAP having 100 percent passing the 1½ in. (37.5 mm) sieve and being well graded, may be used as capping aggregate in the top 3 in. (75 mm) when aggregate gradations CS 01, CS 02, or RR 01 are used in lower lifts.

Note 3. The RAP used for aggregate subgrade improvement shall be according to the current Bureau of Materials and Physical Research Policy Memorandum, "Reclaimed Asphalt Pavement (RAP) for Aggregate Applications".

303.03 Equipment. The vibratory machine shall be according to Article 1101.01, or as approved by the Engineer.

303.04 Soil Preparation. The stability of the soil shall be according to the Department's Subgrade Stability Manual for the aggregate thickness specified.

303.05 Placing Aggregate. The maximum nominal lift thickness of aggregate gradations CA 02, CA 06, or CA 10 shall be 12 in. (300 mm). The maximum nominal lift thickness of aggregate gradations CS 01, CS 02, and RR 01 shall be 24 in. (600 mm).

303.06 Capping Aggregate. The top surface of the aggregate subgrade shall consist of a minimum 3 in. (75 mm) of aggregate gradations CA 06 or CA 10. When the contract specifies that a granular subbase is to be placed on the aggregate subgrade improvement, the 3 in. (75 mm) of capping aggregate shall be the same gradation and may be placed with the underlying aggregate subgrade improvement material.

303.07 Compaction. All aggregate lifts shall be compacted to the satisfaction of the Engineer. If the moisture content of the material is such that compaction cannot be obtained, sufficient water shall be added so that satisfactory compaction can be obtained.

303.08 Finishing and Maintenance of Aggregate Subgrade Improvement. The aggregate subgrade improvement shall be finished to the lines, grades, and cross sections shown on the plans, or as directed by the Engineer. The aggregate subgrade improvement shall be maintained in a smooth and compacted condition.

303.09 Method of Measurement. This work will be measured for payment according to Article 311.08.

303.10 Basis of Payment. This work will be paid for at the contract unit price per cubic yard (cubic meter) or ton (metric ton) for AGGREGATE SUBGRADE IMPROVEMENT or at the contract unit price per Square Yard (Square Meter) for AGGREGATE SUBGRADE IMPROVEMENT, of the thickness specified."

Add the following to Section 1004 of the Standard Specifications:

"1004.06 Coarse Aggregate for Aggregate Subgrade Improvement. The aggregate shall be according to Article 1004.01 and the following.

- (a) Description. The coarse aggregate shall be crushed gravel, crushed stone, or crushed concrete.
- (b) Quality. The coarse aggregate shall consist of sound durable particles reasonably free of deleterious materials.
- (c) Gradation.
 - (1) The coarse aggregate gradation for total subgrade thickness less than or equal to 12 in. (300 mm) shall be CA 2, CA 6, CA 10, or CS 01.

The coarse aggregate gradation for total subgrade thickness more than 12 in. (300 mm) shall be CS 01, CS 02 or RR 01(see Article 1005.01(c)).

COARSE AGGREGATE SUBGRADE GRADATIONS					
Grad No.	Sieve Size and Percent Passing				
	8"	6"	4"	2"	#4
CS 01	100	97 ± 3	90 ± 10	45 ± 25	20 ± 20
CS 02		100	80 ± 10	25 ± 15	

COARSE AGGREGATE SUBGRADE GRADATIONS (Metric)					
Grad No.	Sieve Size and Percent Passing				
	200 mm	150 mm	100 mm	50 mm	4.75 mm
CS 01	100	97 ± 3	90 ± 10	45 ± 25	20 ± 20
CS 02		100	80 ± 10	25 ± 15	

- (2) The 3 in. (75 mm) capping aggregate shall be gradation CA 6 or CA 10."

31226

312.26

Designer Note: Insert in all contracts using cast-in-place, precast, or precast prestressed concrete.

PORTLAND CEMENT CONCRETE (BDE)

Effective: January 1, 2012

Revised: January 1, 2013

Revise Notes 1 and 2 of Article 312.24 of the Standard Specifications to read:

"Note 1. Coarse aggregate shall be gradation CA 6, CA 7, CA 9, CA 10, or CA 11, Class D quality or better. Article 1020.05(d) shall apply.

Note 2. Fine aggregate shall be FA 1 or FA 2. Article 1020.05(d) shall apply."

Revise the first paragraph of Article 312.26 of the Standard Specifications to read:

"312.26 Proportioning and Mix Design. At least 60 days prior to start of placing CAM II, the Contractor shall submit samples of materials for proportioning and testing. The mixture shall contain a minimum of 200 lb (90 kg) of cement per cubic yard (cubic meter). Portland cement may be replaced with fly ash according to Article 1020.05(c)(1), however the minimum portland cement content in the mixture shall be 170 lbs/cu yd (101 kg/cu m). Blends of coarse and fine aggregates will be permitted, provided the volume of fine aggregate does not exceed the volume of coarse aggregate. The Engineer will determine the proportions of materials for the mixture. However, the Contractor may substitute their own mix design. Article 1020.05(a) shall apply and a Level III PCC Technician shall develop the mix design."

Revise the second paragraph of Article 503.22 of the Standard Specifications to read:

Other cast-in-place concrete for structures will be paid for at the contract unit price per cubic yard (cubic meter) for CONCRETE HANDRAIL, CONCRETE ENCASEMENT, and SEAL COAT CONCRETE."

Add the following to Article 1003.02 of the Standard Specifications:

(e) Alkali Reaction.

(1) ASTM C 1260. Each fine aggregate will be tested by the Department for alkali reaction according to ASTM C 1260. The test will be performed with Type I or II

portland cement having a total equivalent alkali content ($\text{Na}_2\text{O} + 0.658\text{K}_2\text{O}$) of 0.90 percent or greater. The Engineer will determine the assigned expansion value for each aggregate, and these values will be made available on the Department's Alkali-Silica Potential Reactivity Rating List. The Engineer may differentiate aggregate based on ledge, production method, gradation number, or other factors. An expansion value of 0.03 percent will be assigned to limestone or dolomite fine aggregates (manufactured stone sand). However, the Department reserves the right to perform the ASTM C 1260 test.

- (2) ASTM C 1293 by Department. In some instances, such as chert natural sand or other fine aggregates, testing according to ASTM C 1260 may not provide accurate test results. In this case, the Department may only test according to ASTM C 1293.
- (3) ASTM C 1293 by Contractor. If an individual aggregate has an ASTM C 1260 expansion value that is unacceptable to the Contractor, an ASTM C 1293 test may be performed by the Contractor to evaluate the Department's ASTM C 1260 test result. The laboratory performing the ASTM C 1293 test shall be approved by the Department according to the current Bureau of Materials and Physical Research Policy Memorandum "Minimum Laboratory Requirements for Alkali-Silica Reactivity (ASR) Testing".

The ASTM C 1293 test shall be performed with Type I or II portland cement having a total equivalent alkali content ($\text{Na}_2\text{O} + 0.658\text{K}_2\text{O}$) of 0.80 percent or greater. The interior vertical wall of the ASTM C 1293 recommended container (pail) shall be half covered with a wick of absorbent material consisting of blotting paper. If the testing laboratory desires to use an alternate container, wick of absorbent material, or amount of coverage inside the container with blotting paper, ASTM C 1293 test results with an alkali-reactive aggregate of known expansion characteristics shall be provided to the Engineer for review and approval. If the expansion is less than 0.040 percent after one year, the aggregate will be assigned an ASTM C 1260 expansion value of 0.08 percent that will be valid for two years, unless the Engineer determines the aggregate has changed significantly. If the aggregate is manufactured into multiple gradation numbers, and the other gradation numbers have the same or lower ASTM C 1260 value, the ASTM C 1293 test result may apply to multiple gradation numbers.

The Engineer reserves the right to verify a Contractor's ASTM C 1293 test result. When the Contractor performs the test, a split sample shall be provided to the Engineer. The Engineer may also independently obtain a sample at any time. The aggregate will be considered reactive if the Contractor or Engineer obtains an expansion value of 0.040 percent or greater.

Revise the first paragraph of Article 1004.01(e)(5) of the Standard Specifications to read:

“Crushed concrete, crushed slag, or lightweight aggregate for portland cement concrete shall be stockpiled in a moist condition (saturated surface dry or greater) and the moisture content shall be maintained uniformly throughout the stockpile by periodic sprinkling.”

Revise Article 1004.02(d) of the Standard Specifications to read:

“(d)Combining Sizes. Each size shall be stored separately and care shall be taken to prevent them from being mixed until they are ready to be proportioned. Separate compartments shall be provided to proportion each size.

(1) When Class BS concrete is to be pumped, the coarse aggregate gradation shall have a minimum of 45 percent passing the 1/2 in. (12.5 mm) sieve. The Contractor may combine two or more coarse aggregate sizes, consisting of CA 7, CA 11, CA 13, CA 14, and CA 16, provided a CA 7 or CA 11 is included in the blend.

(2) If the coarse aggregate is furnished in separate sizes, they shall be combined in proportions to provide a uniformly graded coarse aggregate grading within the following limits.

Class of Concrete ^{1/}	Combined Sizes	Sieve Size and Percent Passing						
		2 1/2 in.	2 in.	1 3/4 in.	1 1/2 in.	1 in.	1/2 in.	No. 4
PV ^{2/}	CA 5 & CA 7	---	---	100	98±2	72±22	22±12	3±3
	CA 5 & CA 11	---	---	100	98±2	72±22	22±12	3±3
SI and SC ^{2/}	CA 3 & CA 7	100	95±5	---	---	55±25	20±10	3±3
	CA 3 & CA 11	100	95±5	---	---	55±25	20±10	3±3
	CA 5 & CA 7	---	---	100	98±2	72±22	22±12	3±3
	CA 5 & CA 11	---	---	100	98±2	72±22	22±12	3±3

Class of Concrete ^{1/}	Combined Sizes	Sieve Size (metric) and Percent Passing						
		63 mm	50 mm	45 mm	37.5 mm	25 mm	12.5 mm	4.75 mm
PV ^{2/}	CA 5 & CA 7	---	---	100	98±2	72±22	22±12	3±3
	CA 5 & CA 11	---	---	100	98±2	72±22	22±12	3±3
SI and SC ^{2/}	CA 3 & CA 7	100	95±5	---	---	55±25	20±10	3±3
	CA 3 & CA 11	100	95±5	---	---	55±25	20±10	3±3
	CA 5 & CA 7	---	---	100	98±2	72±22	22±12	3±3
	CA 5 & CA 11	---	---	100	98±2	72±22	22±12	3±3

1/ See Table 1 of Article 1020.04.

2/ Any of the listed combination of sizes may be used.”

Add the following to Article 1004.02 of the Standard Specifications:

(g) Alkali Reaction.

- (1) ASTM C 1260. Each coarse aggregate will be tested by the Department for alkali reaction according to ASTM C 1260. The test will be performed with Type I or II portland cement having a total equivalent alkali content ($\text{Na}_2\text{O} + 0.658\text{K}_2\text{O}$) of 0.90 percent or greater. The Engineer will determine the assigned expansion value for each aggregate, and these values will be made available on the Department's Alkali-Silica Potential Reactivity Rating List. The Engineer may differentiate aggregate based on ledge, production method, gradation number, or other factors. An expansion value of 0.05 percent will be assigned to limestone or dolomite coarse aggregates. However, the Department reserves the right to perform the ASTM C 1260 test.
- (2) ASTM C 1293 by Department. In some instances testing a coarse aggregate according to ASTM C 1260 may not provide accurate test results. In this case, the Department may only test according to ASTM C 1293.
- (3) ASTM C 1293 by Contractor. If an individual aggregate has an ASTM C 1260 expansion value that is unacceptable to the Contractor, an ASTM C 1293 test may be performed by the Contractor according to Article 1003.02(e)(3).

Revise the first paragraph of Article 1019.06 of the Standard Specifications to read:

“1019.06 Contractor Mix Design. A Contractor may submit their own mix design and may propose alternate fine aggregate materials, fine aggregate gradations, or material proportions. Article 1020.05(a) shall apply and a Level III PCC Technician shall develop the mix design.”

Revise Section 1020 of the Standard Specifications to read:

“SECTION 1020. PORTLAND CEMENT CONCRETE

1020.01 Description. This item shall consist of the materials, mix design, production, testing, curing, low air temperature protection, and temperature control of concrete.

1020.02 Materials. Materials shall be according to the following.

Item	Article/Section
(a) Cement	1001
(b) Water	1002
(c) Fine Aggregate	1003
(d) Coarse Aggregate	1004
(e) Concrete Admixtures	1021
(f) Finely Divided Minerals	1010
(g) Concrete Curing Materials	1022
(h) Straw	1081.06(a)(1)
(l) Calcium Chloride	1013.01

1020.03 Equipment. Equipment shall be according to the following.

Item	Article/Section
(a) Concrete Mixers and Trucks	1103.01
(b) Batching and Weighing Equipment	1103.02
(c) Automatic and Semi-Automatic Batching Equipment	1103.03
(d) Water Supply Equipment	1103.11
(e) Membrane Curing Equipment	1101.09
(f) Mobile Portland Cement Concrete Plants	1103.04

1020.04 Concrete Classes and General Mix Design Criteria. The classes of concrete shown in Table 1 identify the various mixtures by the general uses and mix design criteria. If the class of concrete for a specific item of construction is not specified, Class SI concrete shall be used.

For the minimum cement factor in Table 1, it shall apply to portland cement, portland-pozzolan cement, and portland blast-furnace slag except when a particular cement is specified in the Table.

The Contractor shall not assume that the minimum cement factor indicated in Table 1 will produce a mixture that will meet the specified strength. In addition, the Contractor shall not assume that the maximum finely divided mineral allowed in a mix design according to Article 1020.05(c) will produce a mixture that will meet the specified strength. The Contractor shall select a cement factor within the allowable range that will obtain the specified strength. The Contractor shall take into consideration materials selected, seasonal temperatures, and other factors which may require the Contractor to submit multiple mix designs.

For a portland-pozzolan cement, portland blast-furnace slag cement, or when replacing portland cement with finely divided minerals per Articles 1020.05(c) and 1020.05(d), the portland cement content in the mixture shall be a minimum of 375 lbs/cu yd (222 kg/cu m).

When the total of organic processing additions, inorganic processing additions, and limestone exceed 5.0 percent in the cement, the minimum portland cement content in the mixture shall be 400 lbs/cu yd (237 kg/cu m). When calculating the portland cement portion in the portland-pozzolan or portland blast-furnace slag cement, the AASHTO M 240 tolerance may be ignored.

Special classifications may be made for the purpose of including the concrete for a particular use or location as a separate pay item in the contract. The concrete used in such cases shall conform to this section.

TABLE 1. CLASSES OF CONCRETE AND MIX DESIGN CRITERIA

Class of Conc.	Use	Specification Section Reference	Cement Factor cwt/cu yd (3)		Water / Cement Ratio lb/lb	Slump in. (4)	Mix Design Compressive Strength (Flexural Strength) psi, minimum			Air Content %	Coarse Aggregate Gradations (14)
			Min.	Max.			3 Days	14 Days	28 Days		
DS	Drilled Shaft (12) Metal Shell Piles (12) Sign Structures Drilled Shaft (12) Light Tower Foundation (12)	516	6.65	7.05	0.32 - 0.44	6 - 8 (6)	4000 (675)		5.0 - 8.0	CA 13, CA 14, CA 16, or a blend of these gradations.	
		512									
		734									
837											
SC	Seal Coat	503	5.65 (1) 6.05 (2)	7.05	0.32 - 0.44	3 - 5	3500 (650)		Optional 6.0 max.	CA 3 & CA 7, CA 3 & CA 11, CA 5 & CA 7, CA 5 & CA 11, CA 7, or CA 11	
SI	Structures (except Superstructure) Sidewalk Slope Wall Encasement Box Culverts End Section and Collar Curb, Gutter, Curb & Gutter, Median, and Paved Ditch Concrete Barrier Sign Structures Spread Footing Concrete Foundation Pole Foundation (12) Traffic Signal Foundation Drilled Shaft (12) Square or Rectangular	503									
		424									
		511									
		512									
		540									
		542									
		606									
		637									
		734									
		836									
878											
			5.65 (1) 6.05 (2)	7.05	0.32 - 0.44	2 - 4 (5)	3500 (650)		5.0 - 8.0 (5)	CA 3 & CA 7, CA 3 & CA 11, CA 5 & CA 7, CA 5 & CA 11, CA 7, CA 11, CA 13, CA 14, or CA 16 (13)	

Notes:

- (1) Central-mixed.
- (2) Truck-mixed or shrink-mixed.
- (3) For Class SC concrete and for any other class of concrete that is to be placed underwater, except Class DS concrete, the cement factor shall be increased by ten percent.
- (4) The maximum slump may be increased to 7 in. when a high range water-reducing admixture is used for all classes of concrete, except Class PV, SC, and PP. For Class SC, the maximum slump may be increased to 8 in. For Class PP-1, the maximum slump may be increased to 6 in. For Class PS, the 7 in. maximum slump may be increased to 8 1/2 in. if the high range water-reducing admixture is the polycarboxylate type.
- (5) The slump range for slipform construction shall be 1/2 to 2 1/2 in. and the air content range shall be 5.5 to 8.0 percent.
- (6) If concrete is placed to displace drilling fluid, or against temporary casing, the slump shall be 8 - 10 in. at the point of placement. If a water-reducing admixture is used in lieu of a high range water-reducing admixture according to Article 1020.05(b)(7), the slump shall be 2 - 4 in.
- (7) For Class BS concrete used in bridge deck patching, the coarse aggregate gradation shall be CA 13, CA 14, or CA 16, except CA 11 may be used for full-depth patching.
- (8) In addition to the Type III portland cement, 100 lb/cu yd of ground granulated blast-furnace slag and 50 lb/cu yd of microsilica (silica fume) shall be used. For an air temperature greater than 85 °F, the Type III portland cement may be replaced with Type I or II portland cement.
- (9) The cement shall be a rapid hardening cement from the Department's "Approved List of Packaged, Dry, Rapid Hardening Cementitious Materials for Concrete Repairs" for PP-4 and calcium aluminate cement for PP-5.
- (10) For Class PP concrete used in bridge deck patching, the coarse aggregate gradation shall be CA 13, CA 14, or CA 16, except CA 11 may be used for full-depth patching. In addition, the mix design shall have 72 hours to obtain a 4,000 psi compressive or 675 psi flexural strength for all PP mix designs.
- (11) The nominal maximum size permitted is 3/4 in. Nominal maximum size is defined as the largest sieve which retains any of the aggregate sample particles.
- (12) The concrete mix shall be designed to remain fluid throughout the anticipated duration of the pour plus one hour. At the Engineer's discretion, the Contractor may be required to conduct a minimum 2 cu yd trial batch to verify the mix design.
- (13) CA 3 or CA 5 may be used when the nominal maximum size does not exceed two-thirds the clear distance between parallel reinforcement bars, or between the reinforcement bar and the form. Nominal maximum size is defined in Note 11.
- (14) Alternate combinations of gradation sizes may be used with the approval of the Engineer. Refer also to Article 1004.02(d) for additional information on combining sizes.

TABLE 1. CLASSES OF CONCRETE AND MIX DESIGN CRITERIA (metric)

Class of Conc.	Use	Specification Section Reference	Cement Factor kg/cu m (3)		Water / Cement Ratio kg/kg	Sump mm (4)	Mix Design Compressive Strength (Flexural Strength) kPa, minimum			Air Content %	Coarse Aggregate Gradations (14)																			
			Min.	Max			3	Days																						
								14	28																					
DS	Drilled Shaft (12) Metal Shell Piles (12) Sign Structures Drilled Shaft (12) Light Tower Foundation (12)	516 512 734 837	395	418	0.32 - 0.44	150 - 200 (6)	27,500 (4650)		5.0 - 8.0	CA 13, CA 14, CA 16, or a blend of these gradations.																				
											SC	Seal Coat	503	335 (1) 360 (2)	418	0.32 - 0.44	75 - 125	24,000 (4500)	Optional 6.0 max.	CA 3 & CA 7, CA 3 & CA 11, CA 5 & CA 7, CA 5 & CA 11, CA 7, or CA 11										
																					SI	Structures (except Superstructure) Sidewalk Slope Wall Encasement Box Culverts Erod Section and Collar Curb, Gutter, Curb & Gutter, Median, and Paved Ditch, Concrete Barrier Sign Structures Spread Footing Concrete Foundation Pole Foundation (12) Traffic Signal Foundation Drilled Shaft (12) Square or Rectangular	503 424 511 512 540 542 606 637 734 836 878	335 (1) 360 (2)	418	0.32 - 0.44	50 - 100 (5)	24,000 (4500)	5.0 - 8.0 (5)	CA 3 & CA 7, CA 3 & CA 11, CA 5 & CA 7, CA 5 & CA 11, CA 7, CA 11, CA 13, CA 14, or CA 16 (13)

- Notes:
- (1) Central-mixed.
 - (2) Truck-mixed or shrink-mixed.
 - (3) For Class SC concrete and for any other class of concrete that is to be placed underwater, except Class DS concrete, the cement factor shall be increased by ten percent.
 - (4) The maximum slump may be increased to 175 mm when a high range water-reducing admixture is used for all classes of concrete except Class PV, SC, and PP. For Class SC, the maximum slump may be increased to 200 mm. For Class PP-1, the maximum slump may be increased to 150 mm. For Class PS, the 175 mm maximum slump may be increased to 215 mm if the high range water-reducing admixture is the polycarboxylate type.
 - (5) The slump range for slipform construction shall be 13 to 64 mm and the air content range shall be 5.5 to 8.0 percent.
 - (6) If concrete is placed to displace drilling fluid, or against temporary casing, the slump shall be 200 - 250 mm at the point of placement. If a water-reducing admixture is used in lieu of a high range water-reducing admixture according to Article 1020.05(b)(7), the slump shall be 50 - 100 mm.
 - (7) For Class BS concrete used in bridge deck patching, the coarse aggregate gradation shall be CA 13, CA 14, or CA 16, except CA 11 may be used for full-depth patching.
 - (8) In addition to the Type III portland cement, 60 kg/cu m of ground granulated blast-furnace slag and 30 kg/cu m of microsilica (silica fume) shall be used. For an air temperature greater than 30 °C, the Type III portland cement may be replaced with Type I or II portland cement.
 - (9) The cement shall be a rapid hardening cement from the Department's "Approved List of Packaged, Dry, Rapid Hardening Cementitious Materials for Concrete Repairs" for PP-4 and calcium aluminate cement for PP-5.
 - (10) For Class PP concrete used in bridge deck patching, the coarse aggregate gradation shall be CA 13, CA 14, or CA 16, except CA 11 may be used for full-depth patching. In addition, the mix design shall have 72 hours to obtain a 27,500 kPa compressive or 4,650 kPa flexural.
 - (11) The nominal maximum size permitted is 19 mm. Nominal maximum size is defined as the largest sieve which retains any of the aggregate sample particles.
 - (12) The concrete mix shall be designed to remain fluid throughout the anticipated duration of the pour plus one hour. At the Engineer's discretion, the Contractor may be required to conduct a minimum 1.5 cu m trial batch to verify the mix design.
 - (13) CA 3 or CA 5 may be used when the nominal maximum size does not exceed two-thirds the clear distance between parallel reinforcement bars, or between the reinforcement bar and the form. Nominal maximum size is defined in Note 11.
 - (14) Alternate combinations of gradation sizes may be used with the approval of the Engineer. Refer also to Article 1004.02(d) for additional information on combining sizes.

Self-consolidating concrete is a flowable mixture that does not require mechanical vibration for consolidation. Self-consolidating concrete mix designs may be developed for Class BS, PC, PS, DS, and SI concrete. Self-consolidating concrete mix designs may also be developed for precast concrete products that are not subjected to Class PC concrete requirements according to Section 1042. The mix design criteria for the concrete mixture shall be according to Article 1020.04 with the following exceptions.

- (a) The slump requirements shall not apply.
- (b) The concrete mixture should be uniformly graded, and information in the "Portland Cement Concrete Level III Technician Course – Manual of Instructions for Design of Concrete Mixtures" may be used to develop the uniformly graded mix design. The coarse aggregate gradations shall be CA 11, CA 13, CA 14, CA 16, or a blend of these gradations. However, the final gradation when using a single coarse aggregate or combination of coarse aggregates shall have 100 percent pass the 1 in. (25 mm) sieve, and minimum 95 percent pass the 3/4 in. (19 mm) sieve. The fine aggregate proportion shall be a maximum 50 percent by weight (mass) of the total aggregate used.
- (c) The slump flow range shall be 22 in. (560 mm) minimum to 28 in. (710 mm) maximum and tested according to Illinois Test Procedure SCC-2.
- (d) The visual stability index shall be a maximum of 1 and tested according to Illinois Test Procedure SCC-2.
- (e) The J-Ring value shall be a maximum of 2 in. (50 mm) and tested according to Illinois Test Procedure SCC-3. The L-Box blocking ratio shall be a minimum of 80 percent and tested according to Illinois Test Procedure SCC-3. The Contractor has the option to select either test.
- (f) The hardened visual stability index shall be a maximum of 1 and tested according to Illinois Test Procedure SCC-6.
- (g) If Class PC concrete requirements do not apply to the precast concrete product according to Section 1042, the maximum cement factor shall be 7.05 cwt/cu yd (418 kg/cu m) and the maximum allowable water/cement ratio shall be 0.44.
- (h) If the measured slump flow, visual stability index, J-Ring value, or L-Box blocking ratio fall outside the limits specified, a check test will be made. In the event of a second failure, the Engineer may refuse to permit the use of the batch of concrete represented.

The Contractor may use water or self-consolidating admixtures at the jobsite to obtain the specified slump flow, visual stability index, J-ring value, or L-box blocking ratio. The maximum design water/cement ratio shall not be exceeded.

1020.05 Other Concrete Criteria. The concrete shall be according to the following.

- (a) Proportioning and Mix Design. For all Classes of concrete, it shall be the Contractor's responsibility to determine mix design material proportions and to proportion each batch of concrete. A Level III PCC Technician shall develop the mix design for all Classes of concrete, except Classes PC and PS. The mix design, submittal information, trial batch, and Engineer verification shall be according to the "Portland Cement Concrete Level III Technician" course material.

The Contractor shall provide the mix designs a minimum of 45 calendar days prior to production. More than one mix design may be submitted for each class of concrete.

The Engineer will verify the mix design submitted by the Contractor. Verification of a mix design shall in no manner be construed as acceptance of any mixture produced. Once a mix design has been verified, the Engineer shall be notified of any proposed changes.

Tests performed at the jobsite will determine if a mix design can meet specifications. If the tests indicate it cannot, the Contractor shall make adjustments to a mix design, or submit a new mix design if necessary, to comply with the specifications.

- (b) Admixtures. The Contractor shall be responsible for using admixtures and determining dosages for all Classes of concrete, cement aggregate mixture II, and controlled low-strength material that will produce a mixture with suitable workability, consistency, and plasticity. In addition, admixture dosages shall result in the mixture meeting the specified plastic and hardened properties. The Contractor shall obtain approval from the Engineer to use an accelerator when the concrete temperature is greater than 60 °F (16 °C). However, this accelerator approval by the Engineer will not be required for Class PP, RR, PC, and PS concrete. The accelerator shall be the non-chloride type unless otherwise specified in the contract plans.

The Department will maintain an Approved List of Corrosion Inhibitors. Corrosion inhibitor dosage rates shall be according to Article 1020.05(b)(10). For information on approved controlled low-strength material air-entraining admixtures, refer to Article 1019.02. The Department will also maintain an Approved List of Concrete Admixtures, and an admixture technical representative shall be consulted by the Contractor prior to the pour when determining an admixture dosage from this list or when making minor admixture dosage adjustments at the jobsite. The dosage shall be within the range indicated on the approved list unless the influence by other admixtures, jobsite conditions (such as a very short haul time), or other circumstances warrant a dosage outside the range. The Engineer shall be notified when a dosage is proposed outside the range. To determine an admixture dosage, air temperature, concrete temperature, cement source and quantity, finely divided mineral sources and quantity, influence of other admixtures, haul time, placement conditions, and other factors as appropriate shall be considered. The Engineer may request the Contractor to have a batch of concrete mixed in the lab or field to verify the admixture dosage is correct. An admixture dosage or combination of admixture dosages shall not delay the initial set of concrete by more than one hour. When a retarding admixture is required or appropriate for a bridge deck or bridge deck overlay pour, the initial set time shall be delayed until the deflections due

to the concrete dead load are no longer a concern for inducing cracks in the completed work. However, a retarding admixture shall not be used to further extend the pour time and justify the alteration of a bridge deck pour sequence.

When determining water in admixtures for water/cement ratio, the Contractor shall calculate 70 percent of the admixture dosage as water, except a value of 50 percent shall be used for a latex admixture used in bridge deck latex concrete overlays.

The sequence, method, and equipment for adding the admixtures shall be approved by the Engineer. Admixtures shall be added to the concrete separately. An accelerator shall always be added prior to a high range water-reducing admixture, if both are used.

Admixture use shall be according to the following.

- (1) When the atmosphere or concrete temperature is 65 °F (18 °C) or higher, a retarding admixture shall be used in the Class BS concrete and concrete bridge deck overlays. The proportions of the ingredients of the concrete shall be the same as without the retarding admixture, except that the amount of mixing water shall be reduced, as may be necessary, in order to maintain the consistency of the concrete as required. In addition, a high range water-reducing admixture shall be used in bridge deck concrete. At the option of the Contractor, a water-reducing admixture may be used with the high range water-reducing admixture in Class BS concrete.
- (2) At the Contractor's option, admixtures in addition to an air-entraining admixture may be used for Class PP-1 or RR concrete. When the air temperature is less than 55 °F (13 °C) and an accelerator is used, the non-chloride accelerator shall be calcium nitrite.
- (3) When Class C fly ash or ground granulated blast-furnace slag is used in Class PP-1 or RR concrete, a water-reducing or high range water-reducing admixture shall be used.
- (4) For Class PP-2 or PP-3 concrete, a non-chloride accelerator followed by a high range water-reducing admixture shall be used, in addition to the air-entraining admixture. The Contractor has the option to use a water-reducing admixture with the high range water-reducing admixture. For Class PP-3 concrete, the non-chloride accelerator shall be calcium nitrite. For Class PP-2 concrete, the non-chloride accelerator shall be calcium nitrite when the air temperature is less than 55 °F (13 °C).
- (5) For Class PP-4 concrete, a high range water-reducing admixture shall be used in addition to the air-entraining admixture. The Contractor has the option to use a water-reducing admixture with the high range water-reducing admixture. An accelerator shall not be used. For stationary or truck-mixed concrete, a retarding admixture shall be used to allow for haul time. The Contractor has the option to use

a mobile portland cement concrete plant, but a retarding admixture shall not be used unless approved by the Engineer.

For PP-5 concrete, a non-chloride accelerator, high range water-reducing admixture, and air-entraining admixture shall be used. The accelerator, high range water-reducing admixture, and air-entraining admixture shall be per the Contractor's recommendation and dosage. The approved list of concrete admixtures shall not apply. A mobile portland cement concrete plant shall be used to produce the patching mixture.

- (6) When a calcium chloride accelerator is specified in the contract, the maximum chloride dosage shall be 1.0 quart (1.0 L) of solution per 100 lb (45 kg) of cement. The dosage may be increased to a maximum 2.0 quarts (2.0 L) per 100 lb (45 kg) of cement if approved by the Engineer. When a calcium chloride accelerator for Class PP-2 concrete is specified in the contract, the maximum chloride dosage shall be 1.3 quarts (1.3 L) of solution per 100 lb (45 kg) of cement. The dosage may be increased to a maximum 2.6 quarts (2.6 L) per 100 lb (45 kg) of cement if approved by the Engineer.
- (7) For Class DS concrete a retarding admixture and a high range water-reducing admixture shall be used. For dry excavations that are 10 ft (3 m) or less, the high range water-reducing admixture may be replaced with a water-reducing admixture if the concrete is vibrated. The use of admixtures shall take into consideration the slump loss limits specified in Article 516.12 and the fluidity requirement in Article 1020.04 (Note 12).
- (8) At the Contractor's option, when a water-reducing admixture or a high range water-reducing admixture is used for Class PV, PP-1, RR, SC, and SI concrete, the cement factor may be reduced a maximum 0.30 hundredweight/cu yd (18 kg/cu m). However, a cement factor reduction will not be allowed for concrete placed underwater.
- (9) When Type F or Type G high range water-reducing admixtures are used, the initial slump shall be a minimum of 1 1/2 in. (40 mm) prior to addition of the Type F or Type G admixture, except as approved by the Engineer.
- (10) When specified, a corrosion inhibitor shall be added to the concrete mixture utilized in the manufacture of precast, prestressed concrete members and/or other applications. It shall be added, at the same rate, to all grout around post-tensioning steel when specified.

When calcium nitrite is used, it shall be added at the rate of 4 gal/cu yd (20 L/cu m), and shall be added to the mix immediately after all compatible admixtures have been introduced to the batch.

When Rheocrete 222+ is used, it shall be added at the rate of 1.0 gal/cu yd (5.0 L/cu m), and the batching sequence shall be according to the manufacturer's instructions.

(c) Finely Divided Minerals. Use of finely divided minerals shall be according to the following.

(1) Fly Ash. At the Contractor's option, fly ash from approved sources may partially replace portland cement in cement aggregate mixture II, Class PV, PP-1, PP-2, RR, BS, PC, PS, DS, SC, and SI concrete.

The use of fly ash shall be according to the following.

- a. Measurements of fly ash and portland cement shall be rounded up to the nearest 5 lb (2.5 kg).
- b. When Class F fly ash is used in cement aggregate mixture II, Class PV, BS, PC, PS, DS, SC, and SI concrete, the amount of portland cement replaced shall not exceed 25 percent by weight (mass).
- c. When Class C fly ash is used in cement aggregate mixture II, Class PV, PP-1, PP-2, RR, BS, PC, PS, DS, SC, and SI concrete, the amount of portland cement replaced shall not exceed 30 percent by weight (mass).
- d. Fly ash may be used in concrete mixtures when the air temperature is below 40 °F (4 °C), but the Engineer may request a trial batch of the concrete mixture to show the mix design strength requirement will be met.

(2) Ground Granulated Blast-Furnace (GGBF) Slag. At the Contractor's option, GGBF slag may partially replace portland cement in Class PV, PP-1, PP-2, RR, BS, PC, PS, DS, SC, and SI concrete. For Class PP-3 concrete, GGBF slag shall be used according to Article 1020.04.

The use of GGBF slag shall be according to the following.

- a. Measurements of GGBF slag and portland cement shall be rounded up to the nearest 5 lb (2.5 kg).
- b. When GGBF slag is used in Class PV, PP-1, PP-2, RR, BS, PC, PS, DS, SC and SI concrete, the amount of portland cement replaced shall not exceed 35 percent by weight (mass).
- c. GGBF slag may be used in concrete mixtures when the air temperature is below 40 °F (4 °C), but the Engineer may request a trial batch of the concrete mixture to show the mix design strength requirement will be met.

- (3) **Microsilica.** At the Contractor's option, microsilica may be added at a maximum of 5.0 percent by weight (mass) of the cement and finely divided minerals summed together.

Microsilica shall be used in Class PP-3 concrete according to Article 1020.04.

- (4) **High Reactivity Metakaolin (HRM).** At the Contractor's option, HRM may be added at a maximum of 5.0 percent by weight (mass) of the cement and finely divided minerals summed together.
- (5) **Mixtures with Multiple Finely Divided Minerals.** Except as specified for Class PP-3 concrete, the Contractor has the option to use more than one finely divided mineral in Class PV, PP-1, PP-2, RR, BS, PC, PS, DS, SC, and SI concrete as follows.
- a. The mixture shall contain a maximum of two finely divided minerals. The finely divided mineral in portland-pozzolan cement or portland blast-furnace slag cement shall count toward the total number of finely divided minerals allowed. The finely divided minerals shall constitute a maximum of 35.0 percent of the total cement plus finely divided minerals. The fly ash portion shall not exceed 30.0 percent for Class C fly ash or 25.0 percent for Class F fly ash. The Class C and F fly ash combination shall not exceed 30.0 percent. The ground granulated blast-furnace slag portion shall not exceed 35.0 percent. The microsilica or high-reactivity metakaolin portion used together or separately shall not exceed ten percent. The finely divided mineral in the portland-pozzolan cement or portland blast-furnace slag blended cement shall apply to the maximum 35.0 percent.
 - b. **Central Mixed.** For Class PV, SC, and SI concrete, the mixture shall contain a minimum of 565 lbs/cu yd (335 kg/cu m) of cement and finely divided minerals summed together. If a water-reducing or high-range water-reducing admixture is used, the Contractor has the option to use a minimum of 535 lbs/cu yd (320 kg/cu m).
 - c. **Truck-Mixed or Shrink-Mixed.** For Class PV, SC, and SI concrete, the mixture shall contain a minimum of 605 lbs/cu yd (360 kg/cu m) of cement and finely divided minerals summed together. If a water-reducing or high-range water-reducing admixture is used, the Contractor has the option to use a minimum of 575 lbs/cu yd (345 kg/cu m).
 - d. **Central-Mixed, Truck-Mixed or Shrink-Mixed.** For Class PP-1 and RR concrete, the mixture shall contain a minimum of 650 lbs/cu yd (385 kg/cu m) of cement and finely divided minerals summed together. For Class PP-1 and RR concrete using Type III portland cement, the mixture shall contain a minimum of 620 lbs/cu yd (365 kg/cu m).

For Class PP-2 concrete, the mixture shall contain a minimum of 735 lbs/cu yd (435 kg/cu m) of cement and finely divided minerals summed together. For Class BS concrete, the mixture shall contain a minimum of 605 lbs/cu yd (360 kg/cu m). For Class DS concrete, the mixture shall contain a minimum of 665 lbs/cu yd (395 kg/cu m).

If a water-reducing or high range water-reducing admixture is used in Class PP-1 and RR concrete, the Contractor has the option to use a minimum of 620 lbs/cu yd (365 kg/cu m) of cement and finely divided minerals summed together. If a water-reducing or high-range water-reducing admixture is used with Type III portland cement in Class PP-1 and RR concrete, the Contractor has the option to use a minimum of 590 lbs/cu yd (350 kg/cu m).

- e. Central-Mixed or Truck-Mixed. For Class PC and PS concrete, the mixture shall contain a minimum of 565 lbs/cu yd (335 kg/cu m) of cement and finely divided minerals summed together.
 - f. The mixture shall contain a maximum of 705 lbs/cu yd (418 kg/cu m) of cement and finely divided mineral(s) summed together for Class PV, BS, PC, PS, DS, SC, and SI concrete. For Class PP-1 and RR concrete, the mixture shall contain a maximum of 750 lbs/cu yd (445 kg/cu m). For Class PP-1 and RR concrete using Type III portland cement, the mixture shall contain a maximum of 720 lbs/cu yd (425 kg/cu m). For Class PP-2 concrete, the mixture shall contain a maximum of 820 lbs/cu yd (485 kg/cu m).
 - g. For Class SC concrete and for any other class of concrete that is to be placed underwater, except Class DS concrete, the allowable cement and finely divided minerals summed together shall be increased by ten percent.
 - h. The combination of cement and finely divided minerals shall comply with Article 1020.05(d).
- (d) Alkali-Silica Reaction. For cast-in-place (includes cement aggregate mixture II and latex mixtures), precast, and precast prestressed concrete, one of the mixture options provided in Article 1020.05(d)(2) shall be used to reduce the risk of a deleterious alkali-silica reaction in concrete exposed to humid or wet conditions. The mixture options are not intended or adequate for concrete exposed to potassium acetate, potassium formate, sodium acetate, or sodium formate. The mixture options will not be required for the dry environment (humidity less than 60 percent) found inside buildings for residential or commercial occupancy.

The mixture options shall not apply to concrete revetment mats, insertion lining of pipe culverts, portland cement mortar fairing course, controlled low-strength material, miscellaneous grouts that are not prepackaged, Class PP-3 concrete, Class PP-4 concrete, and Class PP-5 concrete.

- (1) Aggregate Groups. Each combination of aggregates used in a mixture will be assigned to an aggregate group. The point at which the coarse aggregate and fine aggregate expansion values intersect in the following table will determine the group.

Aggregate Groups			
Coarse Aggregate or Coarse Aggregate Blend ASTM C 1260 Expansion	Fine Aggregate Or Fine Aggregate Blend ASTM C 1260 Expansion		
	≤0.16%	>0.16% - 0.27%	>0.27%
≤0.16%	Group I	Group II	Group III
>0.16% - 0.27%	Group II	Group II	Group III
>0.27%	Group III	Group III	Group IV

- (2) Mixture Options. Based upon the aggregate group, the following mixture options shall be used. However, the Department may prohibit a mixture option if field performance shows a deleterious alkali-silica reaction or Department testing indicates the mixture may experience a deleterious alkali-silica reaction.

Reduction of Risk for Deleterious Alkali-Silica Reaction					
Aggregate Groups	Mixture Options				
	Option 1	Option 2	Option 3	Option 4	Option 5
Group I	Mixture options are not applicable. Use any cement or finely divided mineral.				
Group II	X	X	X	X	X
Group III	X	Combine Option 2 with Option 3	Combine Option 2 with Option 3	X	X
Group IV	X	Combine Option 2 with Option 4	Invalid Option	Combine Option 2 with Option 4	X

"X" denotes valid mixture option for aggregate group.

- a. Mixture Option 1. The coarse or fine aggregates shall be blended to place the material in a group that will allow the selected cement or finely divided mineral to be used. Coarse aggregate may only be blended with another coarse aggregate. Fine aggregate may only be blended with another fine aggregate. Blending of

coarse with fine aggregate to place the material in another group will not be permitted.

When a coarse or fine aggregate is blended, the weighted expansion value shall be calculated separately for the coarse and fine aggregate as follows:

Weighted Expansion Value = $(a/100 \times A) + (b/100 \times B) + (c/100 \times C) + \dots$

Where: a, b, c... = percentage of aggregate in the blend;
A, B, C... = expansion value for that aggregate.

b. Mixture Option 2. A finely divided mineral shall be used as described in 1), 2), 3), or 4) that follow. In addition, a blended cement with a finely divided mineral may be added to a separate finely divided mineral to meet the following requirements, provided the finely divided minerals are the same material. However, adding together two different finely divided minerals to obtain the specified minimum percentage of one material will not be permitted for 1), 2), 3), and 4). Refer to Mixture Option 5 to address this situation.

1. Class F Fly Ash. For cement aggregate mixture II, Class PV, BS, PC, PS, MS, DS, SC and SI concrete, the Class F fly ash shall be a minimum 25.0 percent by weight (mass) of the cement and finely divided minerals summed together.

If the maximum total equivalent available alkali content ($\text{Na}_2\text{O} + 0.658\text{K}_2\text{O}$) exceeds 4.50 percent for the Class F fly ash, it may be used only if it complies with Mixture Option 5.

2. Class C Fly Ash. For cement aggregate mixture II, Class PV, PP-1, PP-2, RR, BS, PC, PS, DS, SC, and SI concrete, Class C fly ash shall be a minimum of 25.0 percent by weight (mass) of the cement and finely divided minerals summed together.

If the maximum total equivalent available alkali content ($\text{Na}_2\text{O} + 0.658\text{K}_2\text{O}$) exceeds 4.50 percent or the calcium oxide exceeds 26.50 percent for the Class C fly ash, it may be used only per Mixture Option 5.

3. Ground Granulated Blast-Furnace Slag. For Class PV, PP-1, PP-2, RR, BS, PC, PS, DS, SC, and SI concrete, ground granulated blast-furnace slag shall be a minimum of 25.0 percent by weight (mass) of the cement and finely divided minerals summed together.

If the maximum total equivalent available alkali content ($\text{Na}_2\text{O} + 0.658\text{K}_2\text{O}$) exceeds 1.00 percent for the ground granulated blast-furnace slag, it may be used only per Mixture Option 5.

4. Microsilica or High Reactivity Metakaolin, Microsilica solids or high reactivity metakaolin shall be a minimum 5.0 percent by weight (mass) of the cement and finely divided minerals summed together.

If the maximum total equivalent available alkali content ($\text{Na}_2\text{O} + 0.658\text{K}_2\text{O}$) exceeds 1.00 percent for the Microsilica or High Reactivity Metakaolin, it may be used only if it complies with Mixture Option 5.

- c. Mixture Option 3. The cement used shall have a maximum total equivalent alkali content ($\text{Na}_2\text{O} + 0.658\text{K}_2\text{O}$) of 0.60 percent. When aggregate in Group II is involved and the Contractor desires to use a finely divided mineral, any finely divided mineral may be used with the cement unless the maximum total equivalent available alkali content ($\text{Na}_2\text{O} + 0.658\text{K}_2\text{O}$) exceeds 4.50 percent for the fly ash; or 1.00 percent for the ground granulated blast-furnace slag, microsilica or high reactivity metakaolin. If the alkali content is exceeded, the finely divided mineral may be used only per Mixture Option 5.
- d. Mixture Option 4. The cement used shall have a maximum total equivalent alkali content ($\text{Na}_2\text{O} + 0.658\text{K}_2\text{O}$) of 0.45 percent. When aggregate in Group II or III is involved and the Contractor desires to use a finely divided mineral, any finely divided mineral may be used with the cement unless the maximum total equivalent available alkali content ($\text{Na}_2\text{O} + 0.658\text{K}_2\text{O}$) exceeds 4.50 percent for the fly ash; or 1.00 percent for the ground granulated blast-furnace slag, microsilica, or high reactivity metakaolin. If the alkali content is exceeded, the finely divided mineral may be used only per Mixture Option 5.
- e. Mixture Option 5. The proposed cement or finely divided mineral may be used if the ASTM C 1567 expansion value is ≤ 0.16 percent when performed on the aggregate in the concrete mixture with the highest ASTM C 1260 test result. The laboratory performing the ASTM C 1567 test shall be approved by the Department according to the current Bureau of Materials and Physical Research Policy Memorandum "Minimum Laboratory Requirements for Alkali-Silica Reactivity (ASR) Testing". The ASTM C 1567 test will be valid for two years, unless the Engineer determines the materials have changed significantly.

For latex concrete, the ASTM C 1567 test shall be performed without the latex.

The 0.20 percent autoclave expansion limit in ASTM C 1567 shall not apply.

If during the two year time period the Contractor needs to replace the cement, and the replacement cement has an equal or lower total equivalent alkali content ($\text{Na}_2\text{O} + 0.658\text{K}_2\text{O}$), a new ASTM C 1567 test will not be required.

The Engineer reserved the right to verify a Contractor's ASTM C 1567 test result. When the Contractor performs the test, a split sample may be requested by the Engineer. The Engineer may also independently obtain a sample at any time.

The proposed cement or finely divided mineral will not be allowed for use if the Contractor or Engineer obtains an expansion value greater than 0.16 percent.

1020.06 Water/Cement Ratio. The water/cement ratio shall be determined on a weight (mass) basis. When a maximum water/cement ratio is specified, the water shall include mixing water, water in admixtures, free moisture on the aggregates, and water added at the jobsite. The quantity of water may be adjusted within the limit specified to meet slump requirements.

When fly ash, ground granulated blast-furnace slag, high-reactivity metakaolin, or microsilica (silica fume) are used in a concrete mix, the water/cement ratio will be based on the total cement and finely divided minerals contained in the mixture.

1020.07 Slump. The slump shall be determined according to Illinois Modified AASHTO T 119.

If the measured slump falls outside the limits specified, a check test will be made. In the event of a second failure, the Engineer may refuse to permit the use of the batch of concrete represented.

If the Contractor is unable to add water to prepare concrete of the specified slump without exceeding the maximum design water/cement ratio, a water-reducing admixture shall be added.

1020.08 Air Content. The air content shall be determined according to Illinois Modified AASHTO T 152 or Illinois Modified AASHTO T 196. The air-entrainment shall be obtained by the use of cement with an approved air-entraining admixture added during the mixing of the concrete or the use of air-entraining cement.

If the air-entraining cement furnished is found to produce concrete having air content outside the limits specified, its use shall be discontinued immediately and the Contractor shall provide other air-entraining cement which will produce air contents within the specified limits.

If the air content obtained is above the specified maximum limit at the jobsite, the Contractor may have the concrete further mixed, within the limits of time and revolutions specified, to reduce the air content. If the air content obtained is below the specified minimum limit, the Contractor may add to the concrete a sufficient quantity of an approved air-entraining admixture at the jobsite to bring the air content within the specified limits.

1020.09 Strength Tests. The specimens shall be molded and cured according to Illinois Modified AASHTO T 23. Specimens shall be field cured with the construction item as specified in Illinois Modified AASHTO T 23. The compressive strength shall be determined according to Illinois Modified AASHTO T 22. The flexural strength shall be determined according to Illinois Modified AASHTO T 177.

Except for Class PC and PS concrete, the Contractor shall transport the strength specimens from the site of the work to the field laboratory or other location as instructed by the Engineer. During transportation in a suitable light truck, the specimens shall be embedded in straw,

burlap, or other acceptable material in a manner meeting with the approval of the Engineer to protect them from damage; care shall be taken to avoid impacts during hauling and handling. For strength specimens, the Contractor shall provide a field curing box for initial curing and a water storage tank for final curing. The field curing box will be required when an air temperature below 60 °F (16 °C) is expected during the initial curing period. The device shall maintain the initial curing temperature range specified in Illinois Modified AASHTO T 23, and may be insulated or power operated as appropriate.

1020.10 Handling, Measuring, and Batching Materials. Aggregates shall be handled in a manner to prevent mixing with soil and other foreign material.

Aggregates shall be handled in a manner which produces a uniform gradation, before placement in the plant bins. Aggregates delivered to the plant in a nonuniform gradation condition shall be stockpiled. The stockpiled aggregate shall be mixed uniformly before placement in the plant bins.

Aggregates shall have a uniform moisture content before placement in the plant bins. This may require aggregates to be stockpiled for 12 hours or more to allow drainage, or water added to the stockpile, or other methods approved by the Engineer. Moisture content requirements for crushed concrete, crushed slag or lightweight aggregate shall be according to Article 1004.01(e)(5).

Aggregates, cement, and finely divided minerals shall be measured by weight (mass). Water and admixtures shall be measured by volume or weight (mass).

The Engineer may permit aggregates, cement, and finely divided minerals to be measured by volume for small isolated structures and for miscellaneous items. Aggregates, cement, and finely divided minerals shall be measured individually. The volume shall be based upon dry, loose materials.

1020.11 Mixing Portland Cement Concrete. The mixing of concrete shall be according to the following.

(a) Ready-Mixed Concrete. Ready-mixed concrete is central-mixed, truck-mixed, or shrink-mixed concrete transported and delivered in a plastic state ready for placement in the work and shall be according to the following.

(1) Central-Mixed Concrete. Central-mixed concrete is concrete which has been completely mixed in a stationary mixer and delivered in a truck agitator, a truck mixer operating at agitating speed, or a nonagitator truck.

The stationary mixer shall operate at the drum speed for which it was designed. The batch shall be charged into the drum so that some of the water shall enter in advance of the cement, finely divided minerals, and aggregates. The flow of the water shall be uniform and all water shall be in the drum by the end of the first 15 seconds of the mixing period. Water shall begin to enter the drum from zero to

two seconds in advance of solid material and shall stop flowing within two seconds of the beginning of mixing time.

Some coarse aggregate shall enter in advance of other solid materials. For the balance of the charging time for solid materials, the aggregates, finely divided minerals, and cement (to assure thorough blending) shall each flow at acceptably uniform rates, as determined by visual observation. Coarse aggregate shall enter two seconds in advance of other solid materials and a uniform rate of flow shall continue to within two seconds of the completion of charging time.

The entire contents of the drum, or of each single compartment of a multiple-drum mixer, shall be discharged before the succeeding batch is introduced.

The volume of concrete mixed per batch shall not exceed the mixer's rated capacity as shown on the standard rating plate on the mixer by more than ten percent.

The minimum mixing time shall be 75 seconds for a stationary mixer having a capacity greater than 2 cu yd (1.5 cu m). For a mixer with a capacity equal to or less than 2 cu yd (1.5 cu m) the mixing time shall be 60 seconds. Transfer time in multiple drum mixers is included in the mixing time. Mixing time shall begin when all materials are in the mixing compartment and shall end when the discharge of any part of the batch is started. The required mixing times will be established by the Engineer for all types of stationary mixers.

When central-mixed concrete is to be transported in a truck agitator or a truck mixer, the stationary-mixed batch shall be transferred to the agitating unit without delay and without loss of any portion of the batch. Agitating shall start immediately thereafter and shall continue without interruption until the batch is discharged from the agitator. The ingredients of the batch shall be completely discharged from the agitator before the succeeding batch is introduced. Drums and auxiliary parts of the equipment shall be kept free from accumulations of materials.

The vehicles used for transporting the mixed concrete shall be of such capacity, or the batches shall be so proportioned, that the entire contents of the mixer drum can be discharged into each vehicle load.

- (2) **Truck-Mixed Concrete.** Truck-mixed concrete is completely mixed and delivered in a truck mixer. When the mixer is charged with fine and coarse aggregates simultaneously, not less than 60 nor more than 100 revolutions of the drum or blades at mixing speed shall be required, after all of the ingredients including water are in the drum. When fine and coarse aggregates are charged separately, not less than 70 revolutions will be required. For self-consolidating concrete, a minimum of 100 revolutions is required in all cases. Additional mixing beyond 100 revolutions shall be at agitating speed unless additions of water, admixtures, or other materials are made at the jobsite. The mixing operation shall begin immediately after the cement and water, or the cement and wet aggregates, come in contact. The

ingredients of the batch shall be completely discharged from the drum before the succeeding batch is introduced. The drum and auxiliary parts of the equipment shall be kept free from accumulations of materials. If additional water or an admixture is added at the jobsite, the concrete batch shall be mixed a minimum of 40 additional revolutions after each addition.

- (3) **Shrink-Mixed Concrete.** Shrink-mixed concrete is mixed partially in a stationary mixer and completed in a truck mixer for delivery. The mixing time of the stationary mixer may be reduced to a minimum of 30 seconds to intermingle the ingredients, before transferring to the truck mixer. All ingredients for the batch shall be in the stationary mixer and partially mixed before any of the mixture is discharged into the truck mixer. The partially mixed batch shall be transferred to the truck mixer without delay and without loss of any portion of the batch, and mixing in the truck mixer shall start immediately. The mixing time in the truck mixer shall be not less than 50 nor more than 100 revolutions of the drum or blades at mixing speed. For self-consolidating concrete, a minimum of 100 revolutions is required in the truck mixer. Additional mixing beyond 100 revolutions shall be at agitating speed, unless additions of water, admixtures, or other materials are made at the jobsite. Units designed as agitators shall not be used for shrink mixing. The ingredients of the batch shall be completely discharged from the drum before the succeeding batch is introduced. The drum and auxiliary parts of the equipment shall be kept free from accumulations of materials. If additional water or an admixture is added at the jobsite, the concrete batch shall be mixed a minimum of 40 additional revolutions after each addition.
- (4) **Mixing Water.** Wash water shall be completely discharged from the drum or container before a batch is introduced. All mixing water shall be added at the plant and any adjustment of water at the jobsite by the Contractor shall not exceed the specified maximum water/cement ratio or slump. If strength specimens have been made for a batch of concrete, and subsequently during discharge there is more water added, additional strength specimens shall be made for the batch of concrete. No additional water may be added at the jobsite to central-mixed concrete if the mix design has less than 565 lbs/cu yd (335 kg/cu m) of cement and finely divided minerals summed together.
- (5) **Mixing and Agitating Speeds.** The mixing or agitating speeds used for truck mixers or truck agitators shall be per the manufacturer's rating plate.
- (6) **Capacities.** The volume of plastic concrete in a given batch will be determined according to AASHTO T 121, based on the total weight (mass) of the batch, determined either from the weight (masses) of all materials, including water, entering the batch or directly from the net weight (mass) of the concrete in the batch as delivered.

The volume of mixed concrete in truck mixers or truck agitators shall in no case be greater than the rated capacity determined according to the Truck Mixer, Agitator,

and Front Discharge Concrete Carrier Standards of the Truck Mixer Manufacturer's Bureau, as shown by the rating plate attached to the truck. If the truck mixer does not have a rating plate, the volume of mixed concrete shall not exceed 63 percent of the gross volume of the drum or container, disregarding the blades. For truck agitators, the value is 80 percent.

- (7) Time of Haul. Haul time shall begin when the delivery ticket is stamped. The delivery ticket shall be stamped no later than five minutes after the addition of the mixing water to the cement, or after the addition of the cement to the aggregate when the combined aggregates contain free moisture in excess of two percent by weight (mass). If more than one batch is required for charging a truck using a stationary mixer, the time of haul shall start with mixing of the first batch. Haul time shall end when the truck is emptied for incorporation of the concrete into the work.

The time elapsing from when water is added to the mix until it is deposited in place at the site of the work shall not exceed 30 minutes when the concrete is transported in nonagitating trucks.

The maximum haul time for concrete transported in truck mixers or truck agitators shall be according to the following.

Concrete Temperature at Point of Discharge °F (°C)	Haul Time	
	Hours	Minutes
50-64 (10-17.5)	1	30
>64 (>17.5) - without retarder	1	0
>64 (>17.5) - with retarder	1	30

To encourage start-up testing for mix adjustments at the plant, the first two trucks will be allowed an additional 15 minutes haul time whenever such testing is performed.

For a mixture which is not mixed on the jobsite, a delivery ticket shall be required for each load. The following information shall be recorded on each delivery ticket: (1) ticket number; (2) name of producer and plant location; (3) contract number; (4) name of Contractor; (5) stamped date and time batched; (6) truck number; (7) quantity batched; (8) amount of admixture(s) in the batch; (9) amount of water in the batch; and (10) Department mix design number.

For concrete mixed in jobsite stationary mixers, the above delivery ticket may be waived, but a method of verifying the haul time shall be established to the satisfaction of the Engineer.

- (8) Production and Delivery. The production of ready-mixed concrete shall be such that the operations of placing and finishing will be continuous insofar as the job operations require. The Contractor shall be responsible for producing concrete that will have the required workability, consistency, and plasticity when delivered to the work. Concrete which is unsuitable for placement as delivered will be rejected. The

Contractor shall minimize the need to adjust the mixture at the jobsite, such as adding water and admixtures prior to discharging.

- (9) Use of Multiple Plants in the Same Construction Item. The Contractor may simultaneously use central-mixed, truck-mixed, and shrink-mixed concrete from more than one plant, for the same construction item, on the same day, and in the same pour. However, the following criteria shall be met.
- a. Each plant shall use the same cement, finely divided minerals, aggregates, admixtures, and fibers.
 - b. Each plant shall use the same mix design. However, material proportions may be altered slightly in the field to meet slump and air content criteria. Field water adjustments shall not result in a difference that exceeds 0.02 between plants for water/cement ratio. The required cement factor for central-mixed concrete shall be increased to match truck-mixed or shrink-mixed concrete, if the latter two types of mixed concrete are used in the same pour.
 - c. The maximum slump difference between deliveries of concrete shall be 3/4 in. (19 mm) when tested at the jobsite. If the difference is exceeded, but test results are within specification limits, the concrete may be used. The Contractor shall take immediate corrective action and shall test subsequent deliveries of concrete until the slump difference is corrected. For each day, the first three truck loads of delivered concrete from each plant shall be tested for slump by the Contractor. Thereafter, when a specified test frequency for slump is to be performed, it shall be conducted for each plant at the same time.
 - d. The maximum air content difference between deliveries of concrete shall be 1.5 percent when tested at the jobsite. If the difference is exceeded, but test results are within specification limits, the concrete may be used. The Contractor shall take immediate corrective action and shall test subsequent deliveries of concrete until the air content difference is corrected. For each day, the first three truck loads of delivered concrete from each plant shall be tested for air content by the Contractor. Thereafter, when a specified test frequency for air content is to be performed, it shall be conducted for each plant at the same time.
 - e. Strength tests shall be performed and taken at the jobsite for each plant. When a specified strength test is to be performed, it shall be conducted for each plant at the same time. The difference between plants for strength shall not exceed 900 psi (6200 kPa) compressive and 90 psi (620 kPa) flexural. If the strength difference requirements are exceeded, the Contractor shall take corrective action.
 - f. The maximum haul time difference between deliveries of concrete shall be 15 minutes. If the difference is exceeded, but haul time is within specification

limits, the concrete may be used. The Contractor shall take immediate corrective action and check subsequent deliveries of concrete.

(b) Class PC Concrete. The concrete shall be central-mixed or truck-mixed. Variations in plastic concrete properties shall be minimized between batches.

(c) Class PV Concrete. The concrete shall be central-mixed, truck-mixed, or shrink-mixed.

The required mixing time for stationary mixers with a capacity greater than 2 cu yd (1.5 cu m) may be less than 75 seconds upon satisfactory completion of a mixer performance test. Mixer performance tests may be requested by the Contractor when the quantity of concrete to be placed exceeds 50,000 sq yd (42,000 sq m). The testing shall be conducted according to the current Bureau of Materials and Physical Research's Policy Memorandum, "Field Test Procedures for Mixer Performance and Concrete Uniformity Tests".

The Contractor will be allowed to test two mixing times within a range of 50 to 75 seconds. If satisfactory results are not obtained from the required tests, the mixing time shall continue to be 75 seconds for the remainder of the contract. If satisfactory results are obtained, the mixing time may be reduced. In no event will mixing time be less than 50 seconds.

The Contractor shall furnish the labor, equipment, and material required to perform the testing according to the current Bureau of Materials and Physical Research's Policy Memorandum, "Field Test Procedures for Mixer Performance and Concrete Uniformity Tests".

A contract which has 12 ft (3.6 m) wide pavement or base course, and a continuous length of 1/2 mile (0.8 km) or more, shall have the following additional requirements.

(1) The plant and truck delivery operation shall be able to provide a minimum of 50 cu yd (38 cu m) of concrete per hour.

(2) The plant shall have automatic or semi-automatic batching equipment.

(d) All Other Classes of Concrete. The concrete shall be central-mixed, truck-mixed, or shrink-mixed concrete.

1020.12 Mobile Portland Cement Concrete Plants. The use of a mobile portland cement concrete plant may be approved under the provisions of Article 1020.10 for volumetric proportioning in small isolated structures, thin overlays, and for miscellaneous and incidental concrete items.

The first 1 cu ft (0.03 cu m) of concrete produced may not contain sufficient mortar and shall not be incorporated in the work. The side plate on the cement feeder shall be removed

periodically (normally the first time the mixer is used each day) to see if cement is building up on the feed drum.

Sufficient mixing capacity of mixers shall be provided to enable continuous placing and finishing insofar as the job operations and the specifications require.

Slump and air tests made immediately after discharge of the mix may be misleading, since the aggregates may absorb a significant amount of water for four or five minutes after mixing.

1020.13 Curing and Protection. The method of curing, curing period, and method of protection for each type of concrete construction is included in the following Index Table.

INDEX TABLE OF CURING AND PROTECTION OF CONCRETE CONSTRUCTION			
TYPE OF CONSTRUCTION	CURING METHODS	CURING PERIOD DAYS	LOW AIR TEMPERATURE PROTECTION METHODS
Cast-in-Place Concrete ^{11/}			
Pavement			
Shoulder	1020.13(a)(1)(2)(3)(4)(5) ^{3/ 5/}	3	1020.13(c)
Base Course			
Base Course Widening	1020.13(a)(1)(2)(3)(4)(5) ^{2/}	3	1020.13(c)
Driveway			
Median			
Barrier			
Curb			
Gutter	1020.13(a)(1)(2)(3)(4)(5) ^{4/ 5/}	3	1020.13(c) ^{16/}
Curb & Gutter			
Sidewalk			
Slope Wall			
Paved Ditch			
Catch Basin			
Manhole	1020.13(a)(1)(2)(3)(4)(5) ^{4/}	3	1020.13(c)
Inlet			
Valve Vault			
Pavement Patching	1020.13(a)(1)(2)(3)(4)(5) ^{2/}	3 ^{12/}	1020.13(c)
Bridge Deck Patching	1020.13(a)(3)(5)	3 or 7 ^{12/}	1020.13(c)
Railroad Crossing	1020.13(a)(3)(5)	1	1020.13(c)
Piles and Drilled Shafts	1020.13(a)(3)(5)	7	1020.13(d)(1)(2)(3)
Foundations & Footings			
Seal Coat	1020.13(a)(1)(2)(3)(4)(5) ^{4/ 5/}	7	1020.13(d)(1)(2)(3)
Substructure	1020.13(a)(1)(2)(3)(4)(5) ^{11/ 7/}	7	1020.13(d)(1)(2)(3)
Superstructure (except deck)	1020.13(a)(1)(2)(3)(5) ^{8/}	7	1020.13(d)(1)(2)
Deck			
Bridge Approach Slab	1020.13(a)(5)	7	1020.13(d)(1)(2) ^{17/}
Retaining Walls	1020.13(a)(1)(2)(3)(4)(5) ^{11/ 7/}	7	1020.13(d)(1)(2)
Pump Houses	1020.13(a)(1)(2)(3)(4)(5) ^{1/}	7	1020.13(d)(1)(2)
Culverts	1020.13(a)(1)(2)(3)(4)(5) ^{4/ 5/}	7	1020.13(d)(1)(2) ^{18/}
Other Incidental Concrete	1020.13(a)(1)(2)(3)(5)	3	1020.13(c)
Precast Concrete ^{11/}			
Bridge Slabs			
Piles and Pile Caps	1020.13(a)(3)(5) ^{9/ 10/}	As ^{13/}	9/
Other Structural Members		Required	
All Other Precast Items	1020.13(a)(3)(4)(5) ^{2/ 9/ 10/}	As ^{14/}	9/
		Required	
Precast, Prestressed Concrete ^{11/}			
All Items	1020(a)(3)(5) ^{9/ 10/}	Until Strand Tensioning is Released ^{15/}	9/

Notes-General:

- 1/ Type I, membrane curing only
- 2/ Type II, membrane curing only
- 3/ Type III, membrane curing only

- 4/ Type I, II and III membrane curing
- 5/ Membrane Curing will not be permitted between November 1 and April 15.
- 6/ The use of water to inundate foundations and footings, seal coats or the bottom slab of culverts is permissible when approved by the Engineer, provided the water temperature can be maintained at 45 °F (7 °C) or higher.
- 7/ Asphalt emulsion for waterproofing may be used in lieu of other curing methods when specified and permitted according to Article 503.18.
- 8/ On non-traffic surfaces which receive protective coat according to Article 503.19, a linseed oil emulsion curing compound may be used as a substitute for protective coat and other curing methods. The linseed oil emulsion curing compound will be permitted between April 16 and October 31 of the same year, provided it is applied with a mechanical sprayer according to Article 1101.09(b).
- 9/ Steam, supplemental heat, or insulated blankets (with or without steam/supplemental heat) are acceptable and shall be according to the Bureau of Materials and Physical Research's Policy Memorandum "Quality Control/Quality Assurance Program for Precast Concrete Products" and the "Manual for Fabrication of Precast, Prestressed Concrete Products".
- 10/ A moist room according to AASHTO M 201 is acceptable for curing.
- 11/ If curing is required and interrupted because of form removal for cast-in-place concrete items, precast concrete products, or precast prestressed concrete products, the curing shall be resumed within two hours from the start of the form removal.
- 12/ Curing maintained only until opening strength is attained for pavement patching, with a maximum curing period of three days. For bridge deck patching the curing period shall be three days if Class PP concrete is used and 7 days if Class BS concrete is used.
- 13/ The curing period shall end when the concrete has attained the mix design strength. The producer has the option to discontinue curing when the concrete has attained 80 percent of the mix design strength or after seven days. All strength test specimens shall remain with the units and shall be subjected to the same curing method and environmental condition as the units, until the time of testing.
- 14/ The producer shall determine the curing period or may elect to not cure the product. All strength test specimens shall remain with the units and shall be subjected to the same curing method and environmental condition as the units, until the time of testing.

15/ The producer has the option to continue curing after strand release.

16/ When structural steel or structural concrete is in place above slope wall, Article 1020.13(c) shall not apply. The protection method shall be according to Article 1020.13(d)(1).

17/ When Article 1020.13(d)(2) is used to protect the deck, the housing may enclose only the bottom and sides. The top surface shall be protected according to Article 1020.13(d)(1).

18/ For culverts having a waterway opening of 10 sq ft (1 sq m) or less, the culverts may be protected according to Article 1020.13(d)(3).

(a) **Methods of Curing.** Except as provided for in the Index Table of Curing and Protection of Concrete Construction, curing shall be accomplished by one of the following described methods. When water is required to wet the surface, it shall be applied as a fine spray so that it will not mar or pond on the surface. Except where otherwise specified, the curing period shall be at least 72 hours.

(1) **Waterproof Paper Method.** The surface of the concrete shall be covered with waterproof paper as soon as the concrete has hardened sufficiently to prevent marring the surface. The surface of the concrete shall be wetted immediately before the paper is placed. The blankets shall be lapped at least 12 in. (300 mm) end to end, and these laps shall be securely weighted with a windrow of earth, or other approved method, to form a closed joint. The same requirements shall apply to the longitudinal laps where separate strips are used for curing edges, except the lap shall be at least 9 in. (225 mm). The edges of the blanket shall be weighted securely with a continuous windrow of earth or any other means satisfactory to the Engineer to provide an air-tight cover. Any torn places or holes in the paper shall be repaired immediately by patches cemented over the openings, using a bituminous cement having a melting point of not less than 180 °F (82 °C). The blankets may be reused, provided they are air-tight and kept serviceable by proper repairs.

A longitudinal pleat shall be provided in the blanket to permit shrinkage where the width of the blanket is sufficient to cover the entire surface. The pleat will not be required where separate strips are used for the edges. Joints in the blanket shall be sewn or cemented together in such a manner that they will not separate during use.

(2) **Polyethylene Sheeting Method.** The surface of the concrete shall be covered with white polyethylene sheeting as soon as the concrete has hardened sufficiently to prevent marring the surface. The surface of the concrete shall be wetted immediately before the sheeting is placed. The edges of the sheeting shall be weighted securely with a continuous windrow of earth or any other means satisfactory to the Engineer to provide an air-tight cover. Adjoining sheets shall overlap not less than 12 in. (300 mm) and the laps shall be securely weighted with earth, or any other means satisfactory to the Engineer, to provide an air tight cover.

For surface and base course concrete, the polyethylene sheets shall be not less than 100 ft (30 m) in length nor longer than can be conveniently handled, and shall be of such width that, when in place, they will cover the full width of the surface, including the edges, except that separate strips may be used to cover the edges. Any tears or holes in the sheeting shall be repaired. When sheets are no longer serviceable as a single unit, the Contractor may select from such sheets and reuse those which will serve for further applications, provided two sheets are used as a single unit; however, the double sheet units will be rejected when the Engineer deems that they no longer provide an air tight cover.

- (3) **Wetted Burlap Method.** The surface of the concrete shall be covered with wetted burlap blankets as soon as the concrete has hardened sufficiently to prevent marring the surface. The blankets shall overlap 6 in. (150 mm). At least two layers of wetted burlap shall be placed on the finished surface. The burlap shall be kept saturated by means of a mechanically operated sprinkling system. In place of the sprinkling system, at the Contractor's option, two layers of burlap covered with impermeable covering shall be used. The burlap shall be kept saturated with water. Plastic coated burlap may be substituted for one layer of burlap and impermeable covering.

The blankets shall be placed so that they are in contact with the edges of the concrete, and that portion of the material in contact with the edges shall be kept saturated with water.

- (4) **Membrane Curing Method.** Membrane curing will not be permitted where a protective coat, concrete sealer, or waterproofing is to be applied, or at areas where rubbing or a normal finish is required, or at construction joints other than those necessary in pavement or base course. Concrete at these locations shall be cured by another method specified in Article 1020.13(a).

After all finishing work to the concrete surface has been completed, it shall be sealed with membrane curing compound of the type specified within ten minutes. The seal shall be maintained for the specified curing period. The edges of the concrete shall, likewise, be sealed within ten minutes after the forms are removed. Two separate applications, applied at least one minute apart, each at the rate of not less than 1 gal/250 sq ft (0.16 L/sq m) will be required upon the surfaces and edges of the concrete. These applications shall be made with the mechanical equipment specified. Type III compound shall be agitated immediately before and during the application.

At locations where the coating is discontinuous or where pin holes show or where the coating is damaged due to any cause and on areas adjacent to sawed joints, immediately after sawing is completed, an additional coating of membrane curing compound shall be applied at the above specified rate. The equipment used may be of the same type as that used for coating variable widths of pavement. Before the additional coating is applied adjacent to sawed joints, the cut faces of the joint shall be protected by inserting a suitable flexible material in the joint, or placing an

adhesive width of impermeable material over the joint, or by placing the permanent sealing compound in the joint. Material, other than the permanent sealing compound, used to protect cut faces of the joint, shall remain in place for the duration of the curing period. In lieu of applying the additional coating, the area of the sawed joint may be cured according to any other method permitted.

When rain occurs before an application of membrane curing compound has dried, and the coating is damaged, the Engineer may require another application be made in the same manner and at the same rate as the original coat. The Engineer may order curing by another method specified, if unsatisfactory results are obtained with membrane curing compound.

- (5) **Wetted Cotton Mat Method.** After the surface of concrete has been textured or finished, it shall be covered immediately with dry or damp cotton mats. The cotton mats shall be placed in a manner which will not mar the concrete surface. A texture resulting from the cotton mat material is acceptable. The cotton mats shall then be wetted immediately and thoroughly soaked with a gentle spray of water. For bridge decks, a foot bridge shall be used to place and wet the cotton mats.

The cotton mats shall be maintained in a wetted condition until the concrete has hardened sufficiently to place soaker hoses without marring the concrete surface. The soaker hoses shall be placed on top of the cotton mats at a maximum 4 ft (1.2 m) spacing. The cotton mats shall be kept wet with a continuous supply of water for the remainder of the curing period. Other continuous wetting systems may be used if approved by the Engineer.

After placement of the soaker hoses, the cotton mats shall be covered with white polyethylene sheeting or burlap-polyethylene blankets.

For construction items other than bridge decks, soaker hoses or a continuous wetting system will not be required if the alternative method keeps the cotton mats wet. Periodic wetting of the cotton mats is acceptable.

For areas inaccessible to the cotton mats on bridge decks, curing shall be according to Article 1020.13(a)(3).

- (b) **Removing and Replacing Curing Covering.** When curing methods specified above in Article 1020.13(a), (1), (2), or (3) are used for concrete pavement, the curing covering for each day's paving shall be removed to permit testing of the pavement surface with a profilograph or straightedge, as directed by the Engineer.

Immediately after testing, the surface of the pavement shall be wetted thoroughly and the curing coverings replaced. The top surface and the edges of the concrete shall not be left unprotected for a period of more than 1/2 hour.

- (c) Protection of Concrete, Other Than Structures, From Low Air Temperatures. When the official National Weather Service forecast for the construction area predicts a low of 32 °F (0 °C), or lower, or if the actual temperature drops to 32 °F (0 °C), or lower, concrete less than 72 hours old shall be provided at least the following protection.

Minimum Temperature	Protection
25 – 32 °F (-4 – 0 °C)	Two layers of polyethylene sheeting, one layer of polyethylene and one layer of burlap, or two layers of waterproof paper.
Below 25 °F (-4 °C)	6 in. (150 mm) of straw covered with one layer of polyethylene sheeting or waterproof paper.

These protective covers shall remain in place until the concrete is at least 96 hours old. When straw is required on pavement cured with membrane curing compound, the compound shall be covered with a layer of burlap, polyethylene sheeting or waterproof paper before the straw is applied.

After September 15, there shall be available to the work within four hours, sufficient clean, dry straw to cover at least two days production. Additional straw shall be provided as needed to afford the protection required. Regardless of the precautions taken, the Contractor shall be responsible for protection of the concrete placed and any concrete damaged by cold temperatures shall be removed and replaced.

- (d) Protection of Concrete Structures From Low Air Temperatures. When the official National Weather Service forecast for the construction area predicts a low below 45 °F (7 °C), or if the actual temperature drops below 45 °F (7 °C), concrete less than 72 hours old shall be provided protection. Concrete shall also be provided protection when placed during the winter period of December 1 through March 15. Concrete shall not be placed until the materials, facilities, and equipment for protection are approved by the Engineer.

When directed by the Engineer, the Contractor may be required to place concrete during the winter period. When winter construction is specified, the Contractor shall proceed with the construction, including excavation, pile driving, concrete, steel erection, and all appurtenant work required for the complete construction of the item, except at times when weather conditions make such operations impracticable.

Regardless of the precautions taken, the Contractor shall be responsible for protection of the concrete placed and any concrete damaged by cold temperatures shall be removed and replaced.

- (1) Protection Method I. The concrete shall be completely covered with insulating material such as fiberglass, rock wool, or other approved commercial insulating material having the minimum thermal resistance R, as defined in ASTM C 168, for

the corresponding minimum dimension of the concrete unit being protected as shown in the following table.

Minimum Pour Dimension		Thermal Resistance R
in.	(mm)	
6 or less	(150 or less)	R=16
> 6 to 12	(> 150 to 300)	R=10
> 12 to 18	(> 300 to 450)	R=6
> 18	(> 450)	R=4

The insulating material manufacturer shall clearly mark the insulating material with the thermal resistance R value.

The insulating material shall be completely enclosed on sides and edges with an approved waterproof liner and shall be maintained in a serviceable condition. Any tears in the liner shall be repaired in a manner approved by the Engineer. The Contractor shall provide means for checking the temperature of the surface of the concrete during the protection period.

On formed surfaces, the insulating material shall be attached to the outside of the forms with wood cleats or other suitable means to prevent any circulation of air under the insulation and shall be in place before the concrete is placed. The blanket insulation shall be applied tightly against the forms. The edges and ends shall be attached so as to exclude air and moisture. If the blankets are provided with nailing flanges, the flanges shall be attached to the studs with cleats. Where tie rods or reinforcement bars protrude, the areas adjacent to the rods or bars shall be adequately protected in a manner satisfactory to the Engineer. Where practicable, the insulation shall overlap any previously placed concrete by at least 1 ft (300 mm). Insulation on the underside of floors on steel members shall cover the top flanges of supporting members. On horizontal surfaces, the insulating material shall be placed as soon as the concrete has set, so that the surface will not be marred and shall be covered with canvas or other waterproof covering. The insulating material shall remain in place for a period of seven days after the concrete is placed.

The Contractor may remove the forms, providing the temperature is 35 °F (2 °C) and rising and the Contractor is able to wrap the particular section within two hours from the time of the start of the form removal. The insulation shall remain in place for the remainder of the seven days curing period.

- (2) Protection Method II. The concrete shall be enclosed in adequate housing and the air surrounding the concrete kept at a temperature of not less than 50 °F (10 °C) nor more than 80 °F (27 °C) for a period of seven days after the concrete is placed. The Contractor shall provide means for checking the temperature of the surface of the concrete or air temperature within the housing during the protection period. All exposed surfaces within the housing shall be cured according to the Index Table.

The Contractor shall provide adequate fire protection where heating is in progress and such protection shall be accessible at all times. The Contractor shall maintain labor to keep the heating equipment in continuous operation.

At the close of the heating period, the temperature shall be decreased to the approximate temperature of the outside air at a rate not to exceed 15 °F (8 °C) per 12 hour period, after which the housing maybe removed. The surface of the concrete shall be permitted to dry during the cooling period.

- (3) Protection Method III. As soon as the surface is sufficiently set to prevent marring, the concrete shall be covered with 12 in. (300 mm) of loose, dry straw followed by a layer of impermeable covering. The edges of the covering shall be sealed to prevent circulation of air and prevent the cover from flapping or blowing. The protection shall remain in place until the concrete is seven days old. If construction operations require removal, the protection removed shall be replaced immediately after completion or suspension of such operations.

1020.14 Temperature Control for Placement. Temperature control for concrete placement shall be according to the following.

- (a) Concrete other than Structures. Concrete may be placed when the air temperature is above 35 °F (2 °C) and rising, and concrete placement shall stop when the falling temperature reaches 40 °F (4 °C) or below, unless otherwise approved by the Engineer.

The temperature of concrete immediately before placement shall be a minimum of 50 °F (10 °C) and a maximum of 90 °F (32 °C). If concrete is pumped, the temperature of the concrete at point of placement shall be a minimum of 50 °F (10 °C) and a maximum of 90 °F (32 °C). A maximum concrete temperature shall not apply to Class PP concrete.

- (b) Concrete in Structures. Concrete may be placed when the air temperature is above 40 °F (4 °C) and rising, and concrete placement shall stop when the falling temperature reaches 45 °F (7 °C) or below, unless otherwise approved by the Engineer.

The temperature of the concrete immediately before placement shall be a minimum of 50 °F (10 °C) and a maximum of 90 °F (32 °C). If concrete is pumped, the temperature of the concrete at point of placement shall be a minimum of 50 °F (10 °C) and a maximum of 90 °F (32 °C).

When insulated forms are used according to Article 1020.13(d)(1), the maximum temperature of the concrete mixture immediately before placement shall be 80 °F (25 °C).

When concrete is placed in contact with previously placed concrete, the temperature of the freshly mixed concrete may be increased to 80 °F (25 °C) by the Contractor to offset anticipated heat loss.

- (c) All Classes of Concrete. Aggregates and water shall be heated or cooled uniformly and as necessary to produce concrete within the specified temperature limits. No frozen aggregates shall be used in the concrete.
- (d) Temperature. The concrete temperature shall be determined according to Illinois Modified AASHTO T 309.

1020.15 Heat of Hydration Control for Concrete Structures. The Contractor shall control the heat of hydration for concrete structures when the least dimension for a drilled shaft, foundation, footing, substructure, or superstructure concrete pour exceeds 5.0 ft (1.5 m). The work shall be according to the following.

- (a) Temperature Restrictions. The maximum temperature of the concrete after placement shall not exceed 150 °F (66 °C). The maximum temperature differential between the internal concrete core and concrete 2 to 3 in. (50 to 75 mm) from the exposed surface shall not exceed 35 °F (19 °C). The Contractor shall perform temperature monitoring to ensure compliance with the temperature restrictions.
- (b) Thermal Control Plan. The Contractor shall provide a thermal control plan a minimum of 28 calendar days prior to concrete placement for review by the Engineer. Acceptance of the thermal control plan by the Engineer shall not preclude the Contractor from specification compliance, and from preventing cracks in the concrete. At a minimum, the thermal control plan shall provide detailed information on the following requested items and shall comply with the specific specifications indicated for each item.
 - (1) Concrete mix design(s) to be used. Grout mix design if post-cooling with embedded pipe.

The mix design requirements in Articles 1020.04 and 1020.05 shall be revised to include the following additional requirements to control the heat of hydration.

- a. The concrete mixture should be uniformly graded and preference for larger size aggregate should be used in the mix design. Article 1004.02(d)(2) shall apply and information in the "Portland Cement Concrete Level III Technician Course – Manual of Instructions for Design of Concrete Mixtures" may be used to develop the uniformly graded mixture.
- b. The following shall apply to all concrete except Class DS concrete or when self-consolidating concrete is desired. For central-mixed concrete, the Contractor shall have the option to develop a mixture with a minimum of 520 lbs/cu yd (309 kg/cu m) of cement and finely divided minerals summed together. For truck-mixed or shrink-mixed concrete, the Contractor shall have the option to develop a mixture with a minimum of 550 lbs/cu yd (326 kg/cu m) of cement and finely divided minerals summed together. A water-reducing or high range water-reducing admixture shall be used in the central mixed, truck-mixed or shrink-

mixed concrete mixture. For any mixture to be placed underwater, the minimum cement and finely divided minerals shall be 550 lbs/cu yd (326 kg/cu m) for central-mixed concrete, and 580 lbs/cu yd (344 kg/cu m) for truck-mixed or shrink-mixed concrete.

For Class DS concrete, CA 11 may be used. If CA 11 is used, the Contractor shall have the option to develop a mixture with a minimum cement and finely divided minerals of 605 lbs/cu yd (360 kg/cu m) summed together. If CA 11 is used and either Class DS concrete is placed underwater or a self-consolidating concrete mixture is desired, the Contractor shall have the option to develop a mixture with a minimum cement and finely divided minerals of 635 lbs/cu yd (378 kg/cu m) summed together.

- c. The minimum portland cement content in the mixture shall be 375 lbs/cu yd (222 kg/cu m). When the total of organic processing additions, inorganic processing additions, and limestone addition exceed 5.0 percent in the cement, the minimum portland cement content in the mixture shall be 400 lbs/cu yd (237 kg/cu m). For a drilled shaft, foundation, footing, or substructure, the minimum portland cement may be reduced to as low as 330 lbs/cu yd (196 kg/cu m) if the concrete has adequate freeze/thaw durability. The Contractor shall provide freeze/thaw test results according to AASHTO T 161 Procedure A or B, and the relative dynamic modulus of elasticity of the mix design shall be a minimum of 80 percent. Freeze/thaw testing will not be required for concrete that will not be exposed to freezing and thawing conditions as determined by the Engineer.
- d. The maximum cement replacement with fly ash shall be 40.0 percent. The maximum cement replacement with ground granulated blast-furnace slag shall be 65.0 percent. When cement replacement with ground granulated blast-furnace slag exceeds 35.0 percent, only Grade 100 shall be used.
- e. The mixture may contain a maximum of two finely divided minerals. The finely divided mineral in portland-pozzolan cement or portland blast-furnace slag cement shall count toward the total number of finely divided minerals allowed. The finely divided minerals shall constitute a maximum of 65.0 percent of the total cement plus finely divided minerals. The fly ash portion shall not exceed 40.0 percent. The ground granulated blast-furnace slag portion shall not exceed 65.0 percent. The microsilica or high-reactivity metakaolin portion used together or separately shall not exceed 5.0 percent.
- f. The time to obtain the specified strength may be increased to a maximum 56 days, provided the curing period specified in Article 1020.13 is increased to a minimum of 14 days.

The minimum grout strength for filling embedded pipe shall be as specified for the concrete, and testing shall be according to AASHTO T 106.

- (2) The selected mathematical method for evaluating heat of hydration thermal effects, which shall include the calculated adiabatic temperature rise, calculated maximum concrete temperature, and calculated maximum temperature differential between the internal concrete core and concrete 2 to 3 in. (50 to 75 mm) from the exposed surface. The time when the maximum concrete temperature and maximum temperature differential will occur is required.

Acceptable mathematical methods include ACI 207.2R "Report on Thermal and Volume Change Effects on Cracking of Mass Concrete" as well as other proprietary methods. The Contractor shall perform heat of hydration testing on the cement and finely divided minerals to be used in the concrete mixture. The test shall be according to ASTM C 186 or other applicable test methods, and the result for heat shall be used in the equation to calculate adiabatic temperature rise. Other required test parameters for the mathematical model may be assumed if appropriate.

The Contractor has the option to propose a higher maximum temperature differential between the internal concrete core and concrete 2 to 3 in. (50 to 75 mm) from the exposed surface, but the proposed value shall not exceed 50 °F (28 °C). In addition, based on strength gain of the concrete, multiple maximum temperature differentials at different times may be proposed. The proposed value shall be justified through a mathematical method.

- (3) Proposed maximum concrete temperature or temperature range prior to placement.

Article 1020.14 shall apply except a minimum 40 °F (4 °C) concrete temperature will be permitted.

- (4) Pre-cooling, post-cooling, and surface insulation methods that will be used to ensure the concrete will comply with the specified maximum temperature and specified or proposed temperature differential. For reinforcement that extends beyond the limits of the pour, the Contractor shall indicate if the reinforcement is required to be covered with insulation.

Refer to ACI 207.4R "Cooling and Insulating Systems for Mass Concrete" for acceptable methods that will be permitted. If embedded pipe is used for post-cooling, the material shall be polyvinyl chloride or polyethylene. The embedded pipe system shall be properly supported, and the Contractor shall subsequently inspect glued joints to ensure they are able to withstand free falling concrete. The embedded pipe system shall be leak tested after inspection of the glued joints, and prior to the concrete placement. The leak test shall be performed at maximum service pressure or higher for a minimum of 15 minutes. All leaks shall be repaired. The embedded pipe cooling water may be from natural sources such as streams and rivers, but shall be filtered to prevent system stoppages. When the embedded pipe is no longer needed, the surface connections to the pipe shall be removed to a depth of 4 in. (100 mm) below the surface of the concrete. The remaining pipe shall be

completely filled with grout. The 4 in. (100 mm) deep concrete hole shall be filled with nonshrink grout. Form and insulation removal shall be done in a manner to prevent cracking and ensure the maximum temperature differential is maintained. Insulation shall be in good condition as determined by the Engineer and properly attached.

- (5) Dimensions of each concrete pour, location of construction joints, placement operations, pour pattern, lift heights, and time delays between lifts.

Refer to ACI 207.1R "Guide to Mass Concrete" for acceptable placement operations that will be permitted.

- (6) Type of temperature monitoring system, the number of temperature sensors, and location of sensors.

A minimum of two independent temperature monitoring systems and corresponding sensors shall be used.

The temperature monitoring system shall have a minimum temperature range of 32 °F (0 °C) to 212 °F (100 °C), an accuracy of ± 2 °F (± 1 °C), and be able to automatically record temperatures without external power. Temperature monitoring shall begin once the sensor is encased in concrete, and with a maximum interval of one hour. Temperature monitoring may be discontinued after the maximum concrete temperature has been reached, post-cooling is no longer required, and the maximum temperature differential between the internal concrete core and the ambient air temperature does not exceed 35 °F (19 °C). The Contractor has the option to select a higher maximum temperature differential, but the proposed value shall not exceed 50 °F (28 °C). The proposed value shall be justified through a mathematical method.

At a minimum, a temperature sensor shall be located at the theoretical hottest portion of the concrete, normally the geometric center, and at the exterior face that will provide the maximum temperature differential. At the exterior face, the sensor shall be located 2 to 3 in. (50 to 75 mm) from the surface of the concrete. Sensors shall also be located a minimum of 1 in. (25 mm) away from reinforcement, and equidistant between cooling pipes if either applies. A sensor will also be required to measure ambient air temperature. The entrant/exit cooling water temperature for embedded pipe shall also be monitored.

Temperature monitoring results shall be provided to the Engineer a minimum of once each day and whenever requested by the Engineer. The report may be electronic or hard copy. The report shall indicate the location of each sensor, the temperature recorded, and the time recorded. The report shall be for all sensors and shall include ambient air temperature and entrant/exit cooling water temperatures. The temperature data in the report may be provided in tabular or graphical format, and the report shall indicate any corrective actions during the monitoring period. At the

completion of the monitoring period, the Contractor shall provide the Engineer a final report that includes all temperature data and corrective actions.

(7) Indicate contingency operations to be used if the maximum temperature or temperature differential of the concrete is reached after placement.

- (c) **Temperature Restriction Violations.** If the maximum temperature of the concrete after placement exceeds 150 °F (66 °C), but is equal to or less than 158 °F (70 °C), the concrete will be accepted if no cracking or other unacceptable defects are identified. If cracking or unacceptable defects are identified, Article 105.03 shall apply. If the concrete temperature exceeds 158 °F (70 °C), Article 105.03 shall apply.

If a temperature differential between the internal concrete core and concrete 2 to 3 in. (50 to 75 mm) from the exposed surface exceeds the specified or proposed maximum value allowed, the concrete will be accepted if no cracking or other unacceptable defects are identified. If unacceptable defects are identified, Article 105.03 shall apply.

When the maximum 150 °F (66 °C) concrete temperature or the maximum allowed temperature differential is violated, the Contractor shall implement corrective action prior to the next pour. In addition, the Engineer reserves the right to request a new thermal control plan for acceptance before the Contractor is allowed to pour again.

- (d) **Inspection and Repair of Cracks.** The Engineer will inspect the concrete for cracks after the temperature monitoring is discontinued, and the Contractor shall provide access for the Engineer to do the inspection. A crack may require repair by the Contractor as determined by the Engineer. The Contractor shall be responsible for the repair of all cracks. Protective coat or a concrete sealer shall be applied to a crack less than 0.007 in. (0.18 mm) in width. A crack that is 0.007 in. (0.18 mm) or greater shall be pressure injected with epoxy according to Section 590.

Designer Note: Insert into all interstate resurfacing contracts and at the district's discretion into multi-lane resurfacing contracts with overlay thicknesses greater than or equal to 3.75 inches.

SURFACE TESTING OF HOT-MIX ASPHALT OVERLAYS (BDE)

Effective: January 1, 2013

Revise Article 406.03(h) of the Standard Specifications to read:

"(h) Pavement Surface Test Equipment 1101.10"

Revise Article 406.11 of the Standard Specifications to read:

"406.11 Surface Tests. The finished surface of the pavement shall be tested for smoothness according to Article 407.09 of the Supplemental Specifications, except as follows:

One wheel track shall be tested per lane. Testing shall be performed 3 ft (1 m) from and parallel to the edge of the lane away from traffic.

SMOOTHNESS ASSESSMENT SCHEDULE (HMA Overlays)		
High-Speed Mainline Pavement Average Profile Index in./mile (mm/km)	Low-Speed Mainline Pavement Average Profile Index in./mile (mm/km)	Assessment per subplot
6.0 (95) or less	15.0 (240) or less	+\$150.00
>6.0 (95) to 10.0 (160)	>15.0 (240) to 25.0 (400)	+\$80.00
>10.0 (160) to 30.0 (475)	>25.0 (400) to 45.0 (710)	+\$0.00
>30.0 (475) to 40.0 (635)	>45.0 (710) to 65.0 (1025)	+\$0.00
Greater than 40.0 (635)	Greater than 65.0 (1025)	-\$300.00"

Designer Note: Insert into contracts involving cast-in-place concrete precast concrete, or precast prestressed concrete.

PLACING AND CONSOLIDATING CONCRETE (BDE)

Effective: January 1, 2013

Revise the first paragraph of Article 503.06 of the Standard Specifications to read:

"503.06 Forms. Forms shall be set and maintained to the lines and grades shown on the plans, and shall be tight to prevent concrete leakage."

Revise Article 503.07 of the Standard Specifications to read:

"503.07 Placing and Consolidating. No concrete shall be placed on ice, snow, or frozen foundation material.

The method and manner of placing concrete shall be such as to avoid segregation or separation of the aggregates or the displacement of the reinforcement. The external surface of all concrete shall be thoroughly worked during the operations of placing in such a manner as to work the mortar against the forms to produce a smooth finish free of honeycomb and with a minimum of water and air pockets.

Open troughs and chutes shall extend as nearly as practicable to the point of deposit. Dropping the concrete a distance of more than 5 ft (1.5 m) or depositing a large quantity at any point and running or working it along the forms will not be permitted. The concrete for walls with an average thickness of 12 in. (300 mm) or less shall be placed with tubes so that the drop is not greater than 5 ft (1.5 m).

For self-consolidating concrete, the maximum distance of horizontal flow from the point of deposit shall be 15 ft (4.6 m). The distance may be increased if the dynamic segregation index (DSI) at the maximum flow distance is 10.0 percent or less according to Illinois Test Procedure SCC-8 (Option C). The maximum distance using the DSI shall be 25 ft (7.6 m). In addition, this specified horizontal flow distance shall apply to precast products. In the case of precast prestressed concrete products, refer to the Department's "Manual of Fabrication for Precast Prestressed Concrete Products" for the specified horizontal flow distance requirements.

When the form height for placing the self-consolidating concrete is greater than 10 ft (3.0 m), direct monitoring of form pressure shall be performed by the Contractor according to Illinois Test Procedure SCC-10. The monitoring requirement is a minimum, and the Contractor shall remain responsible for adequate design of the falsework and forms. The Contractor shall record the formwork pressure during concrete placement. This information shall be used by the Contractor to prevent the placement rate from exceeding the maximum formwork pressure allowed, to monitor the thixotropic change in the concrete during the pour, and to make appropriate adjustments to the mix design. This information shall be provided to the Engineer during the pour.

When concrete is pumped, the equipment shall be suitable in kind and adequate in capacity for the work and arranged so that vibrations will not damage freshly placed concrete. Aluminum pipe or conduit will not be permitted in pumping or placing concrete. Mixed concrete shall be supplied to maintain continuous operation of the pumping equipment.

When air entrained concrete is pumped, an accessory or accessories shall be incorporated in the discharge components to minimize air loss. The maximum allowable air loss caused by the pumping operation shall be 3.0 percent with the minimum air content at the point of discharge meeting the requirements of Article 1020.04.

Placing of concrete shall be regulated so that the pressures caused by the wet concrete will not exceed those used in the design of the forms. Special care shall be taken to fill each part of the forms by depositing the concrete as near its final position as possible, to work the coarser aggregates back from the face, and to force the concrete under and around the reinforcement bars without displacing them. Leakage through forms onto beams or girders shall not be allowed to harden and shall be removed while in a plastic state.

The concrete shall be consolidated by internal vibration unless self-consolidating concrete is used. Self-consolidating concrete may be used for inaccessible locations where consolidation by internal vibration is not practicable. The self-consolidating concrete shall be rodded with a piece of lumber, conduit, or vibrator if the material has lost its fluidity prior to placement of additional concrete. The vibrator may only be permitted if it can be used in a manner that does not cause segregation as determined by the Engineer. Any other method for restoring the fluidity of the concrete shall be approved by the Engineer.

The Contractor shall provide and use a sufficient number of vibrators to ensure that consolidation can be started immediately after the concrete has been deposited in the forms.

The vibrators shall be inserted into the concrete immediately after it is deposited and shall be moved throughout the mass so as to thoroughly work the concrete around the reinforcement, embedded fixtures, and into the corners and angles of the forms. Vibrators shall not be attached to the forms, reinforcement bars, or the surface of the concrete.

Application of vibrators shall be at points uniformly spaced and not farther apart than twice the radius over which the vibration is visibly effective. The duration of the vibration at the points of insertion shall be sufficient to thoroughly consolidate the concrete into place but shall not be continued so as to cause segregation. When consolidating concrete in bridge decks, the vibrator shall be vertically inserted into the concrete for 3 - 5 seconds or for a period of time determined by the Engineer. Vibration shall be supplemented by spading when required by the Engineer. In addition to the internal vibration required herein, formed surfaces which will be exposed to view after completion of the work shall be spaded with a spading tool approved by the Engineer.

Concrete shall be placed in continuous horizontal layers. When it is necessary by reason of an emergency to place less than a complete horizontal layer in one operation, such layer shall terminate in a vertical bulkhead. Separate batches shall follow each other closely and in no case shall the interval of time between the placing of successive batches be greater than 20 minutes.

If mix foaming or detrimental material is observed during placement or at the completion of a pour, the material shall be removed while the concrete is still plastic.

After the concrete has taken its initial set, care shall be exercised to avoid jarring the forms or placing any strain on the ends of projecting reinforcement."

Revise Article 516.12(a) of the Standard Specifications to read:

"(a) Free Fall Placement. The free fall placement shall only be permitted in shafts that can be dewatered to ensure less than 3 in. (75 mm) of standing water exist at the time of placement without causing side wall instability. The height of free fall placement shall be

a maximum of 60 ft (18.3 m) as measured from the discharge end, but it shall be reduced to a maximum of 30 ft (9.1 m) when self-consolidating concrete is used. The Contractor shall obtain approval from the Engineer to place self-consolidating concrete by free fall.

Concrete placed by free fall shall fall directly to the base without contacting either the rebar cage or shaft sidewall. Drop chutes may be used to direct concrete to the base during free fall placement.

Drop chutes used to direct placement of free fall concrete shall consist of a smooth tube of either one continuous section or multiple pieces that can be added and removed. Concrete may be placed through either a hopper at the top of the tube or side openings as the drop chute is retrieved during concrete placement. The drop chute shall be supported so that free fall does not exceed the specified maximum 60 ft (18.3 m) or 30 ft (9.1 m) at all times from the discharge end, and to ensure the concrete does not strike the rebar cage. If placement cannot be satisfactorily accomplished by free fall in the opinion of the Engineer, either a tremie or pump shall be used to accomplish the pour."

Designer Note: Insert into contracts utilizing Highway Standards 542001, 542006, 542011 or 542016.

CONCRETE END SECTIONS FOR PIPE CULVERTS (BDE)

Effective: January 1, 2013

Description. This work shall consist of constructing cast-in-place concrete and precast concrete end sections for pipe culverts. These end sections are shown on the plans as Highway Standard 542001, 542006, 542011, or 542016. This work shall be according to Section 542 of the Standard Specifications except as modified herein.

Materials. Materials shall be according to the following Articles of Division 1000 – Materials of the Standard Specifications.

Item	Article/Section
(a) Portland Cement Concrete (Note 1)	1020
(b) Precast Concrete End Sections (Note 2)	
(c) Coarse Aggregate (Note 3)	1004.05
(d) Structural Steel (Note 4)	1006.04
(e) Anchor Bolts and Rods (Note 5)	1006.09
(f) Reinforcement Bars	1006.10(a)
(g) Nonshrink Grout	1024.02
(h) Chemical Adhesive Resin System	1027
(i) Mastic Joint Sealer for Pipe	1055
(j) Hand Hole Plugs	1042.16

Note 1. Cast-in-place concrete end sections shall be Class SI, except the 14 day mix design shall have a compressive strength of 5000 psi (34,500 kPa) or a flexural strength of (800 psi) 5500 kPa and a minimum cement factor of 6.65 cwt/cu yd (395 kg/cu m).

Note 2. Precast concrete end sections shall be according to Articles 1042.02 and 1042.03(b)(c)(d)(e) of the Standard Specifications. The concrete shall be Class PC according to Section 1020, and shall have a minimum compressive strength of 5000 psi (34,000 kPa) at 28 days.

Joints between precast sections shall be produced with reinforced tongue and groove ends according to the requirements of ASTM C 1577.

Note 3. The granular bedding placed below a precast concrete end section shall be gradation CA 6, CA 9, CA 10, CA 12, CA 17, CA 18, or CA 19.

Note 4. All components of the culvert tie detail shall be galvanized according to the requirements of AASHTO M 111 or M 232 as applicable.

Note 5. The anchor rods for the culvert ties shall be according to the requirements of ASTM F 1554, Grade 105 (Grade 725).

CONSTRUCTION REQUIREMENTS

The concrete end sections may be precast or cast-in-place construction. Toe walls shall be either precast or cast-in-place, and shall be in proper position and backfilled according to the applicable paragraphs of Article 502.10 of the Standard Specifications prior to the installation of the concrete end sections. If soil conditions permit, cast-in-place toe walls may be poured directly against the soil. When poured directly against the soil, the clear cover of the sides and bottom of the toe wall shall be increased to 3 in. (75 mm) by increasing the thickness of the toe wall.

- (a) **Cast-In-Place Concrete End Sections.** Cast-in-place concrete end sections shall be constructed according to the requirements of Section 503 of the Standard Specifications and as shown on the plans.
- (b) **Precast Concrete End Sections.** When the concrete end sections will be precast, shop drawings detailing the slab thickness and reinforcement layout shall be submitted to the Engineer for review and approval.

The excavation and backfilling for precast concrete end sections shall be according to the requirements of Section 502 of the Standard Specifications, except a layer of granular bedding at least 6 in. (150 mm) in thickness shall be placed below the elevation of the bottom of the end section. The granular bedding shall extend a minimum of 2 ft (600 mm) beyond each side of the end section.

Anchor rods connecting precast sections shall be brought to a snug tight condition followed by an additional 2/3 turn on one of the nuts. Match marks shall be provided on the bolt and nut to verify relative rotation between the bolt and the nut.

Method of Measurement. This work will be measured for payment as each, with each end of each culvert being one each.

Basis of Payment. This work will be paid for at the contract unit price per each for CONCRETE END SECTION, STANDARD 542001; CONCRETE END SECTION, STANDARD 542006; CONCRETE END SECTION, 542011; or CONCRETE END SECTION, 542016, of the pipe diameter and slope specified.

Designer Note: Insert into contracts using Highway Standard 542311.

TRAVERSABLE PIPE GRATE (BDE)

Effective: January 1, 2013

Description. This work shall consist of constructing a traversable pipe grate on a concrete end section. The traversable pipe grate is shown on the plans as Highway Standard 542311.

Materials. Materials shall be according to the following Articles of Division 1000 – Materials of the Standard Specifications.

Item	Article/Section
(a) Traversable Pipe Grate Components (Note 1)	
(b) Chemical Adhesive Resin System	1027
(c) High Strength Steel Bolts, Nuts, and Washers (Note 2)	1006.08

Note 1. All steel pipe shall be according to ASTM A 53 (Type E or S), Grade B, standard weight (SCH. 40). Structural steel shapes and plates shall be according to AASHTO M270 Grade 50 (M 270M Grade 345) and the requirements of Article 1006.04 of the Standard Specifications. All steel components of the grating system shall be galvanized according to AASHTO M 111 or M 232 as applicable.

Anchor rods shall be according to ASTM F 1554, Grade 36 (Grade 250).

Note 2. Threaded rods conforming to the requirements of ASTM F 1554, Grade 105 (Grade 725) may be used for the thru bolts.

CONSTRUCTION REQUIREMENTS

Fabrication of the traversable pipe grate shall be according to the requirements of Section 505 of the Standard Specifications and as shown on the plans.

Anchor rods shall be set according to Article 509.06. Bolts and anchor rods shall be snug tightened by a few impacts of an impact wrench or the full force of a worker using an ordinary spud wrench. Thru bolts shall be snug tightened and shall be brought to a snug tight condition followed by an additional 2/3 turn on one of the nuts. Match marks shall be provided on the bolt and nut to verify relative rotation between the bolt and the nut.

Method of Measurement. This work will be measured for payment in place in feet (meters). The length measured shall be along the pipe grate elements from end to end for both longitudinal and intermediate support pipes.

Basis of Payment. This work will be paid for at the contract unit price per foot (meter) for TRAVERSABLE PIPE GRATE.

Designer Note: Insert on contracts using insertion lining of culverts.

INSERTION LINING OF CULVERTS (BDE)

Effective: January 1, 2013

"SECTION 543. INSERTION LINING OF CULVERTS

543.01 Description. This work shall consist of insertion lining of existing pipe culverts and grouting of the annular space between the existing culvert and the liner.

543.02 Materials. Materials shall be according to the following.

Item	Article/Section
(a) Polyethylene (PE) Solid Wall Pipe with a Smooth Interior (Note 1)	1040.04
(b) Polyethylene (PE) Profile Wall Pipe (Note 1)	1040.04
(c) Reinforced Plastic Mortar (RPM) Pipe (Note 1)	1040.05
(d) Corrugated PVC with a Smooth Interior (Note 1)	1040.03
(e) Corrugated Steel Pipe (Note 1)(Note 3).....	1006.01
(f) Steel Casing (Note 1)(Note 4)	1006.05(d)
(g) Grout Mixture (Note 2).....	1024.01
(h) Portland Cement Concrete	1020
(i) Controlled Low-Strength Material	1019
(j) Cellular Concrete	1029

Note 1. Insertion linings are specified according to the existing pipe's inside diameter to be lined. Unless the Contractor can demonstrate by calculation that a small cross sectional area is hydraulically equivalent or better, the insertion lining shall provide a minimum of 72 percent of the cross sectional opening of the existing culvert for diameters under 5 ft (1.5 m), 82 percent for culverts between 5 and 10 ft (1.5 and 3 m) in diameter, and 90 percent for culverts greater than 10 ft (3 m) in diameter.

Any of the listed liner materials are permitted if the cross sectional area requirement is met and the liner is structurally adequate to handle the dead and live loads per current AASHTO LRFD Design Standards without the existing culvert taken into consideration.

Note 2. The grout mixture shall be 6.50 hundredweight/cu yd (385 kg/cu m) of portland cement plus fine aggregate and water. Fly ash may replace a maximum of 5.25 hundredweight/cu yd (310 kg/cu m) of the portland cement. The water/cement ratio, according to Article 1020.06, shall not exceed 0.60. An air-entraining admixture shall be used to produce an air content, according to Article 1020.08, of not less than 6.0 percent nor more than 9.0 percent of the volume of the grout. The Contractor shall have the option to use a water-reducing or high range water-reducing admixture.

Note 3. Corrugated metal pipe shall be spiral ribbed or double walled with a smooth interior and shall be polymer coated or Aluminized Steel Type 2.

Note 4. For pipe diameter 24 in. (600 mm) and less, use 3/8 in. (9.5 mm) minimum wall thickness, and for pipe 36 in. (900 mm) and above use 1/2 in. (13 mm) minimum wall thickness.

CONSTRUCTION REQUIREMENTS

543.03 General. The Contractor shall submit a work plan at least 15 days prior to the start of work, detailing the methods for cleaning and preparing the existing culvert, the method(s) for joining the liner segments, the method for advancing the liner into the existing culvert, the process to fill the annular space and the proposed grout or cellular concrete mix design, and a list of potential corrective actions to address common installation issues that may arise. When applicable the method(s) for reconnecting or perpetuating existing lateral connections shall also be submitted. The Contractor shall verify that the specified liner can be installed and enough room remains to adequately fill the annular space remaining prior to ordering any materials. If a problem is discovered it shall be brought to the attention of the Engineer for resolution before ordering any materials.

Individual liner section lengths shall be planned to have no more than three joints per 50 ft (15 m) of pipe length unless approved by the Engineer.

Existing deformed culvert structures that require ovalled liners shall be lined with initial round solid wall PE pipe modified to an oval shape or elongated corrugated metal pipe.

All obvious cavities outside the existing culvert shall be filled with controlled low-strength material prior to the liner installation or with material placed in conjunction with filling the annular space between the liner and existing culvert.

Prior to commencing the liner installation, all jagged existing culvert edges or other deformities shall be repaired. All foreign material shall be removed from the existing culvert.

Joints shall be watertight and meet a 10.8 psi (74 kPa) laboratory test per ASTM D 3212. A mechanical coupler or male and female joint design shall use a gasket meeting ASTM F 477.

Joints shall have sufficient longitudinal or axial compression strength to withstand a maximum compressive force of 100 lbs/in. (17.5 N/mm) of outside diameter circumference in compression while maintaining joint integrity when tested.

Joints shall have sufficient pull-apart strength to withstand maximum tensile force of 100 lbs/in. (17.5 N/mm) of outside diameter circumference in tension without joint disassembly when tested.

Joints shall provide sufficient longitudinal or axial strength to preserve liner alignment, prevent separation at the joints, and maintain integrity while pushing or pulling pipe lengths into existing culverts. Joints shall be mechanical, fusion welded, or male and female joint connections. Mechanical or male and female joint connections shall be an integral part of the liner. Alternatively, the mechanical joint, male and female joints, or pipe ends may be heat fused provided that the fusion process meets the requirements of ASTM F 2620 and that the fused connection is water tight, and shall not reduce the inside diameter or enlarge the outside diameter of the liner being joined by 1/4 in. (6 mm).

If a liner is fusion welded, it shall be welded with a continuous weld for the circumference of the liner both inside and outside. The ends of liners that are to be welded or fused shall be at the same ambient temperature ± 5 °F (2.8 °C) and alignment bands shall be utilized. Welding, fusing, or joining shall be performed at all times by an installer trained and certified by either the liner's manufacturer or the welding, fusing, or joining equipment manufacturer. A copy of the welder's, fuser's, or joiner's certificate shall be provided to the Engineer prior to the start of work.

RPM liners or corrugated PVC liners with a smooth interior shall be joined according to the manufacturer's recommendations using joint lubricant. The joining may be accomplished in a jacking pit or other convenient location where the assembled liner can be brought into alignment with the existing culvert bore without damage. The Engineer will approve each joint before each section of liner is inserted.

The insertion may be made by pushing or pulling the assembled liner from either end of the culvert or if the size permits assembling inside the existing culvert. The Engineer may require the liner to have a temporary nose cone or plug to guide the liner past minor obstructions. The insertion operation shall not cause joints to separate nor damage the liner.

After the liner has been completely inserted and has been inspected in place by the Engineer, it shall be cut off 8 in. (200 mm) past the ends of the existing culvert or as otherwise directed by the Engineer. The liner shall be allowed to cool to the temperature of the existing culvert before it is cut off. The entire length of the annular space between the existing culvert and the liner shall be filled with a grout or cellular concrete.

Prior to filling the annular space, the upstream and downstream ends of the annular space shall have concrete bulkheads constructed to contain the grout mixture. The bulkheads shall be constructed with Class SI concrete. Alternative materials for the bulkhead as recommend by the pipe lining manufacturer may be used if approved by the Engineer. The bulkheads shall extend inward a minimum depth of 18 in. (450 mm) from the ends of the culvert. A method of venting through the bulkheads or grouting ports at the crown shall be utilized to allow air to escape when pumping material and to allow verification that the annular space has been filled.

When the grout or cellular concrete is pumped into the annular space, the Contractor shall prevent the floating of the liner. This shall be accomplished by any of the following methods.

- (a) Intermittent Pumping Method. Small amounts of material shall be pumped into the annular space and allowed to harden. This shall continue until the bond between the liner and material is sufficient to resist floating. The remainder of the annular space shall then be filled.
- (b) Bracing Method. Braces shall be installed in the annular space to prevent floating of the liner. Only braces which do not damage the liner shall be used. Bracing shall run parallel to the culvert.
- (c) Water Fill Method. The liner shall be temporarily filled with water before filling the annular space with grout.

The pumping operation shall completely fill the annular space along the entire length, but shall be performed in a manner that does not distort the liner. The pressure developed in the annular space shall not exceed the liner manufacturer's recommended value. The air temperature at time of placement and for 24 hours thereafter shall be a minimum of 35 °F (2 °C). The temperature of the cellular concrete at point of discharge shall be a minimum of 45 °F (7 °C) and a maximum of 95 °F (35 °C).

The grout or cellular concrete mixture shall have a minimum 28 day compressive strength of 150 psi (1035 kPa). The Engineer will sample the grout or cellular concrete a minimum of once each day for compression strength during production. Mold the grout specimens according to ASTM C 1107, and the cellular concrete according to ASTM C 495. For each test, three 2 in. x 2 in. (50 mm x 50 mm) specimens will be molded for the grout and four 3 in. x 6 in. (75 mm x 150 mm) specimens will be molded for the cellular concrete. The specimens shall be stored in a temperature range of 60 to 80 °F (16 to 27 °C) for the first 24-72 hours, and the Contractor shall provide a field curing box. After this time, the Engineer will transport the specimens to the

laboratory for curing and testing. The grout will be tested for compressive strength according to ASTM C 109, and the cellular concrete will be tested for compressive strength according to ASTM C 495.

Upon completion of the pumping operation, all remaining unfilled vent holes including those at both the upstream and downstream ends shall be filled with a nonshrink grout. Only enough water to make a stiff but workable nonshrink grout shall be used. The air temperature at time of placement and for 24 hours thereafter shall be a minimum of 35 °F (2 °C).

543.04 Method of Measurement. This work will be measured for payment in place in feet (meters).

Excavation in rock will be measured for payment according to Article 502.12.

543.05 Basis of Payment. This work will be paid for at the contract unit price per foot (meter) for INSERTION CULVERT LINER for the existing size specified.

Excavation in rock will be paid for according to Article 502.13.”

Revise Section 1040.04(d) of the Standard Specifications to read as follows.

“(d) PE Solid Wall Pipe with a Smooth Interior. The pipe shall be according to ASTM F 714 (DR 32.5) or ASTM F 2720 (SIDR 35), with a minimum cell classification of PE 335434 as defined in ASTM D 3350.

- (1) Pipe Culverts. The section properties shall be according to AASHTO's Section 17. The manufacturer shall submit written certification that the material meets AASHTO's Section 17 properties and the resin used to manufacture the pipe meets or exceeds the minimum cell classification requirements.
- (2) Insertion Lining. When used for insertion lining of culverts, the pipe liner for pipe diameters up to 63 in. (1600 mm) shall be according to AASHTO M 326.
- (3) Oval shaped pipe liners. Standard round size pipe may be ovalled by compression so as to allow liner installation in deformed existing structures to maximize hydraulic capacity. Compression ovaling shall be performed by the pipe supplier at their facility. Compression ovaling will not be permitted in the field or on the construction site. An ovalled liner may not be compressed to a rise/span ratio less than 0.7 unless approved by the Engineer. Ovalled liners shall be strutted in both the horizontal and vertical axis so as to maintain the oval shape when the compressive source is removed. Struts and bracing shall result in a uniform shaped culvert. Struts shall not be removed until the liner has been completely installed and the grout or cellular concrete has fully cured to its minimum compressive strength.”

Add the following Section to the Standard Specifications.

“SECTION 1029. CELLULAR CONCRETE

1029.01 Description. This item shall consist of the materials and equipment to manufacture cellular concrete.

1029.02 Materials. Materials shall be according to the following.

Item	Article/Section
(a) Portland Cement	1001
(b) Fly Ash	1010
(c) Water	1002
(d) Fine Aggregate.....	1003
(e) Concrete Admixtures.....	1021
(f) Foaming Agent (Note 1)	

Note 1. The foaming agent shall be according to ASTM C 869. For the foaming agent submittal, a report prepared by the manufacturer showing the product meets ASTM C 869 test requirements shall be provided. The submittal shall also include an infrared spectrophotometer trace no more than five years old. When the infrared spectrophotometer trace is more than seven years old, a new one shall be provided. The Department will maintain an "Approved List of Foaming Agents for Cellular Concrete".

1029.03 Equipment. Equipment shall be according to the following.

Item	Article/Section
(a) Concrete Mixers and Trucks.....	1103.01
(b) Batching and Weighing Equipment.....	1103.02
(c) Automatic and Semi-Automatic Batching Equipment.....	1103.03
(d) Water Supply Equipment.....	1103.11
(e) Mobile Portland Cement Concrete Plants.....	1103.04
(f) Foam Generator (Note 1)	
(g) Mobile Site Batch Plants (Note 2)	

Note 1. Foam generating equipment shall be calibrated daily to produce an accurate volume of foam.

Note 2. Mobile site batch plants shall be capable of mixing and pumping cellular concrete, and shall have a minimum 1 cu yd (0.76 cu m) capacity. Mobile site plants shall be calibrated before the start of a project and during the project as necessary."

Designer Note: Insert into all contracts involving high tension median barrier.

HIGH TENSION CABLE MEDIAN BARRIER (BDE)

Effective: January 1, 2007

Revised: January 1, 2013

Description. This work shall consist of furnishing and installing a high tension cable (HTC) median barrier with terminals/end anchorages.

Materials. Materials shall be according to the following.

Item	Article/Section
(a) Reinforcement Bars	1006.10(a)
(b) Portland Cement Concrete (Note 1)	1020
(c) Wire Rope (Cable) and Fittings (Note 2)	

Note 1. The portland cement concrete shall be Class SI.

Note 2. The wire rope (cable) shall be according to AASHTO M 30, Type 1 with Class A coating, of the diameter shown in the manufacturer's specifications. Additionally, the wire rope shall be prestretched and shall have a breaking strength of 39,285 lbs (175 kN) for 3/4 in. (19 mm) wire rope (individual wire strength equivalent to 174,000 psi (1200 N/mm)) and the prestretched wire rope shall have a minimum modulus of elasticity of 11,805,000 psi (8300 kg/mm).

The barrier shall be tested and accepted under the National Cooperative Highway Research Program (NCHRP) Report 350 for the required test level and be on the Department's approved list. Barriers installed on front slope grades of 1:6 or flatter shall be Test Level 4. Barriers installed on front slope grades steeper than 1:6 but 1:4 or flatter shall be Test Level 3.

The barrier shall include four longitudinal cables, each separated vertically from adjacent cable(s) by a minimum of 4 in. (100 mm), and according to the specific acceptance document issued by FHWA. Each cable shall run to a point of anchorage at the terminal without connection to any other cable. The maximum spacing for line posts in the cable barrier system shall be no more than shown in the specific document issued by FHWA, or 15 ft (4.6 m), whichever is less.

The terminals/end anchorages shall be tested and accepted under NCHRP Report 350 Test Level 3 and be on the Department's approved list.

Equipment. Equipment shall be according to the barrier manufacturer's specifications.

Construction Requirements

General. The HTC median barrier shall be constructed to the lines and grades shown on the plans and according to the manufacturer's specifications except as modified by the contracts documents.

Line Post Foundations. Line posts for the HTC median barrier shall be placed in concrete socket foundations. The minimum depth of the foundations shall be as shown on the plans. The minimum diameter for the foundations shall be 12 in. (300 mm) and the tops of the foundations shall be crowned 1/2 in. (13 mm).

When the barrier is to be placed within paved shoulders or mow strips, the paved area(s) shall be constructed first and the concrete foundations placed in cored or formed holes.

End Anchorages. The Contractor shall submit to the Engineer shop drawings detailing the required end anchorage foundation system at each location. The system shall utilize drilled shaft foundations and the number, diameter, depth, reinforcement, and cable connection of each shall be determined by the supplier. As a minimum, single shaft anchorage systems, with all cables terminating at one shaft, shall be at least 24 in. (600 mm) in diameter and 12 1/2 ft (3.8 m) deep while multiple shaft systems, with one cable per shaft, shall be at least 18 in. (450 mm) in diameter and 6 1/2 ft (2 m) deep. The foundation soils shall be inspected during installation to verify that either medium dense granular material or medium stiff clay soils are present. The minimum longitudinal reinforcement shall be 8 – No. 8 (No. 25) bars for the single shaft system, and 6 – No. 6 (No. 19) bars for the multiple shaft system. The minimum confinement reinforcement shall be No. 4 (No. 13) hoops at 6 in. (150 mm) centers or a No. 4 (No. 13) spiral with a 6 in. (150 mm) pitch. The minimum concrete cover over the reinforcement shall be 3 in. (75 mm).

Tensioning. Prior to acceptance of the work, the tension of the HTC median barrier shall be checked, and adjusted as necessary, according to the manufacturer's temperature/tension chart or relationship.

Hands-On Demonstration. When included in the contract, a hands-on demonstration(s) of maintenance/repair procedures, recommendations and discussion of vehicle recovery, and provisions for emergency openings in the barrier shall be conducted. These demonstrations shall be for emergency responders, maintenance personnel, and others invited by the Engineer and shall either be conducted either at the job-site or at another agreed to meeting facility. Up to 30 attendees shall be accommodated at each demonstration.

Method of Measurement. HTC median barrier will be measured for payment in feet (meters) along the top cable between terminals. Terminals shall be defined as the end anchorages and other components from the extreme ends of a run to a point 50 ft (15.2 m) into the run. This definition of the terminal applies regardless of the length of need point, transitions from anchorage to full height cable, or other features that may vary between systems.

Basis of Payment. This work will be paid for at the contract unit price per foot (meter) for HIGH TENSION CABLE MEDIAN BARRIER.

The terminals/end anchorages and demonstrations will be paid for at the contract per each for HIGH TENSION CABLE MEDIAN BARRIER TERMINALS and HIGH TENSION CABLE MEDIAN BARRIER DEMONSTRATION respectively.

Designer Note: Insert into projects where the grooving in of pavement marking is specified. Discuss the need for grooving with Operations and your Project Engineer.

GROOVING FOR RECESSED PAVEMENT MARKINGS (BDE)

Effective: November 1, 2012

Revised: January 1, 2013

Description. This work shall consist of grooving the pavement surface in preparation for the application of recessed pavement markings.

Equipment. Equipment shall be according to the following.

- (a) **Pavement Marking Tape Installations:** The grooving equipment shall have a free-floating saw blade cutting head equipped with gang-stacked diamond saw blades. The diamond saw blades shall be of uniform wear and shall produce a smooth textured surface. Any ridges in the groove shall have a maximum height of 15 mils (0.38 mm).
- (b) **Liquid Pavement Marking Installations:** The grooving equipment shall be equipped with either a free-floating saw blade cutting head or a free-floating grinder cutting head configuration with diamond or carbide tipped cutters and shall produce an irregular textured surface.

CONSTRUCTION REQUIREMENTS

General. The Contractor shall supply the Engineer with a copy of the pavement marking material manufacturer's recommendations for constructing a groove.

Pavement Grooving Methods. The grooves for recessed pavement markings shall be constructed using the following methods.

- (a) **Wet Cutting Head Operation.** When water is required or used to cool the cutting head, the groove shall be flushed with high pressure water immediately following the cut to avoid build up and hardening of slurry in the groove. The pavement surface shall be allowed to dry for a minimum of 24 hours prior to the final cleaning of the groove and application of the pavement marking material.
- (b) **Dry Cutting Head Operation.** When used on HMA pavements, the groove shall be vacuumed or cleaned by blasting with high-pressure air to remove loose aggregate, debris, and dust generated during the cutting operation. When used on PCC pavements, the groove shall be flushed with high pressure water or shot blasted to remove any PCC particles that may have become destabilized during the grooving process. If high pressure water is used, the pavement surface shall be allowed to dry for a minimum of 24 hours prior to the final cleaning of the groove and application of the pavement marking material.

Pavement Grooving. Grooving shall not cause ravels, aggregate fractures, spalling or disturbance of the joints to the underlying surface of the pavement. Grooves shall be cut into the pavement prior to the application of the pavement marking material. Grooves shall be cut such that the width is 1 in. (25 mm) greater than the width of the pavement marking line as specified on the plans. Grooves for letters and symbols shall be cut in a square or rectangular shape so that the entire marking will fit within the limits of the grooved area. The position of the edge of the grooves shall be a minimum of 4 in. (100 mm) from the edge of all longitudinal joints. The depth of the groove shall not be less than the manufacturer's recommendations for the pavement marking material specified, but shall be installed to a minimum depth of 110 mils (2.79 mm) and a maximum depth of 200 mils (5.08 mm) for pavement marking tapes and a minimum depth of 40 mils (1.02 mm) and a maximum depth of 80 mils (2.03 mm) for liquid markings. The cutting head shall be operated at the appropriate speed in order to prevent undulation of the cutting head and grooving at an inconsistent depth.

At the start of grooving operations, a 50 ft (16.7 m) test section shall be installed and depth measurements shall be made at 10 ft (3.3 m) intervals within the test section. The individual depth measurements shall be within the allowable ranges according to this Article. If it is determined the test section has not been grooved at the appropriate depth or texture, adjustments shall be made to the cutting head and another 50 ft (16.7 m) test section shall be installed and checked. This process shall continue until the test section meets the requirements of this Article.

For new HMA pavements, grooves shall not be installed within 14 days of the placement of the final course of pavement.

Final Cleaning. Immediately prior to the application of the pavement marking material or primer sealer, the groove shall be cleaned with high-pressure air blast.

Method of Measurement. This work will be measured for payment in place, in feet (meter) for the groove width specified.

Grooving for letter, numbers and symbols will be measured in square feet (square meters).

Basis of Payment. This work will be paid for at the contract unit price per foot (meter) for GROOVING FOR RECESSED PAVEMENT MARKING of the groove width specified, and per square foot (square meter) for GROOVING FOR RECESSED PAVEMENT MARKING, LETTERS AND SYMBOLS.

The following shall only apply when preformed plastic pavement markings are to be recessed:

Add the following paragraph after the first paragraph of Article 780.07 of the Standard Specifications.

"The markings shall be capable of being applied in a grooved slot on new and existing Portland cement concrete and HMA surfaces, by means of a pressure-sensitive, precoated adhesive, or liquid contact cement which shall be applied at the time of installation. A primer sealer shall be applied with a roller and shall cover and seal the entire bottom of the groove. The primer sealer shall be recommended by the manufacturer of the pavement marking material and shall be compatible with the material being used. The Contractor shall install the markings in the groove as soon as possible after the primer sealer cures according to the manufacturer's

recommendations. The markings placed in the groove shall be rolled and tamped into the groove with a roller or tamper cart cut to fit the groove and loaded with or weighing at least 200 lb (90kg). Vehicle tires shall not be used for tamping. The Contractor shall roll and tamp the material with a minimum of 6 passes to prevent easy removal or peeling."

Designer Notes: Insert into contracts with polyurea letters and symbols.

POLYUREA PAVEMENT MARKINGS (BDE)

Effective: November 1, 2012

Revise: January 1, 2013

Revise the first paragraph of Article 780.13 of the Standard Specifications to read:

“780.13 Basis of Payment. This work will be paid for at the contract unit prices per foot (meter) of applied line width, as specified, for THERMOPLASTIC PAVEMENT MARKING - LINE; PAINT PAVEMENT MARKING - LINE; EPOXY PAVEMENT MARKING - LINE; PREFORMED PLASTIC PAVEMENT MARKING - LINE - TYPE B, C, or B - INLAID; PREFORMED THERMOPLASTIC PAVEMENT MARKING - LINE, POLYUREA PAVEMENT MARKING TYPE I - LINE, POLYUREA PAVEMENT MARKING TYPE II - LINE; and/or per square foot (square meter) for THERMOPLASTIC PAVEMENT MARKING - LETTERS AND SYMBOLS; PAINT PAVEMENT MARKING - LETTERS AND SYMBOLS; EPOXY PAVEMENT MARKING - LETTERS AND SYMBOLS; PREFORMED PLASTIC PAVEMENT MARKING - TYPE B, C, or B - INLAID - LETTERS AND SYMBOLS; PREFORMED THERMOPLASTIC PAVEMENT MARKING - LETTERS AND SYMBOLS; POLYUREA PAVEMENT MARKING TYPE I - LETTERS AND SYMBOLS; POLYUREA PAVEMENT MARKING TYPE II - LETTERS AND SYMBOLS.”

Designer Note: Insert into all contracts requiring anchor bolts.

ANCHOR BOLTS (BDE)

Effective: January 1, 2013

Revise the fourth sentence of the first paragraph of Article 1006.09 of the Standard Specifications to read:

“Stud bolts or fully threaded rods shall be according to either ASTM A 354 Grade BC, ASTM A 193 Grade B7, or ASTM F 1554 Grade 105.”

Revise the second paragraph of Article 1006.09 of the Standard Specifications to read:

“Washers and nuts shall match with the hardness of the anchor bolt, stud, or rod. For ASTM F 1554 Grade 36 (Grade 250) or Grade 55 (Grade 380) anchor rods or bolts, washers shall be according to ASTM F 844 or ASTM F 436, and nuts shall be according to AASHTO M 291 Grade A. For ASTM F 1554 Grade 105 (Grade 725) bolts, ASTM A 354, or ASTM A 193 stud bolts, washers shall be according to AASHTO M 293 Type 1 or Type 3, and nuts shall be according to AASHTO M 291 Grade DH or DH3.”

Revise the seventh paragraph of Article 1006.09 of the Standard Specifications to read:

“Anchor bolts, rods, studs, nuts, and washers requiring galvanizing shall be hot dipped, with zinc coatings conforming to the requirements of ASTM F 2329.”

Revise the fourth paragraph of Article 1070.01 of the Standard Specifications to read:

“Fully threaded and galvanized anchor rods or stud bolts with washers and nuts shall be furnished with the foundations and shall be according to Article 1006.09. Anchors furnished according to ASTM F 1554 shall be Grade 105 (Grade 725).”

Revise the second paragraph of Article 1070.03 of the Standard Specifications to read:

“Top anchor rod nuts for all towers shall be the self-locking type with nylon or steel inserts.”

Designer Note: Insert into all contracts with cast-in-place concrete. This special replaces Recurring Check Sheet #31 of the same name, so don't use Check Sheet #31.

QUALITY CONTROL/QUALITY ASSURANCE OF CONCRETE MIXTURES (BDE)

Effective: January 1, 2012

Revised: January 1, 2013

Add the following to Section 1020 of the Standard Specifications:

"1020.16 Quality Control/Quality Assurance of Concrete Mixtures. This Article specifies the quality control responsibilities of the Contractor for concrete mixtures (except Class PC and PS concrete), cement aggregate mixture II, and controlled low-strength material incorporated in the project, and defines the quality assurance and acceptance responsibilities of the Engineer.

A list of quality control/quality assurance (QC/QA) documents is provided in Article 1020.16(g), Schedule D.

A Level I Portland Cement Concrete (PCC) Technician shall be defined as an individual who has successfully completed the Department's training for concrete testing.

A Level II Portland Cement Concrete (PCC) Technician shall be defined as an individual who has successfully completed the Department's training for concrete proportioning.

A Level III Portland Cement Concrete (PCC) Technician shall be defined as an individual who has successfully completed the Department's training for concrete mix design.

A Concrete Tester shall be defined as an individual who has successfully completed the Department's training to assist with concrete testing and is monitored on a daily basis.

Aggregate Technician shall be defined as an individual who has successfully completed the Department's training for gradation testing involving aggregate production and mixtures.

Mixture Aggregate Technician shall be defined as an individual who has successfully completed the Department's training for gradation testing involving mixtures.

Gradation Technician shall be defined as an individual who has successfully completed the Department's training to assist with gradation testing and is monitored on a daily basis.

- (a) **Equipment/Laboratory.** The Contractor shall provide a laboratory and test equipment to perform their quality control testing.

The laboratory shall be of sufficient size and be furnished with the necessary equipment, supplies, and current published test methods for adequately and safely performing all required tests. The laboratory will be approved by the Engineer according to the current Bureau of Materials and Physical Research Policy Memorandum "Minimum Private Laboratory Requirements for Construction Materials Testing or Mix Design". Production

of a mixture shall not begin until the Engineer provides written approval of the laboratory. The Contractor shall refer to the Department's "Required Sampling and Testing Equipment for Concrete" for equipment requirements.

Test equipment shall be maintained and calibrated as required by the appropriate test method, and when required by the Engineer. This information shall be documented on the Department's "Calibration of Concrete Testing Equipment" form.

Test equipment used to determine compressive or flexural strength shall be calibrated each 12 month period by an independent agency, using calibration equipment traceable to the National Institute of Standards and Technology (NIST). The Contractor shall have the calibration documentation available at the test equipment location.

The Engineer will have unrestricted access to the plant and laboratory at any time to inspect measuring and testing equipment, and will notify the Contractor of any deficiencies. Defective equipment shall be immediately repaired or replaced by the Contractor.

- (b) **Quality Control Plan.** The Contractor shall submit, in writing, a proposed Quality Control (QC) Plan to the Engineer. The QC Plan shall be submitted a minimum of 45 calendar days prior to the production of a mixture. The QC Plan shall address the quality control of the concrete, cement aggregate mixture II, and controlled low-strength material incorporated in the project. The Contractor shall refer to the Department's "Model Quality Control Plan for Concrete Production" to prepare a QC Plan. The Engineer will respond in writing to the Contractor's proposed QC Plan within 15 calendar days of receipt.

Production of a mixture shall not begin until the Engineer provides written approval of the QC Plan. The approved QC Plan shall become a part of the contract between the Department and the Contractor, but shall not be construed as acceptance of any mixture produced.

The QC Plan may be amended during the progress of the work, by either party, subject to mutual agreement. The Engineer will respond in writing to a Contractor's proposed QC Plan amendment within 15 calendar days of receipt. The response will indicate the approval or denial of the Contractor's proposed QC Plan amendment.

- (c) **Quality Control by Contractor.** The Contractor shall perform quality control inspection, sampling, testing, and documentation to meet contract requirements. Quality control includes the recognition of obvious defects and their immediate correction. Quality control also includes appropriate action when passing test results are near specification limits, or to resolve test result differences with the Engineer. Quality control may require increased testing, communication of test results to the plant or the jobsite, modification of operations, suspension of mixture production, rejection of material, or other actions as appropriate. The Engineer shall be immediately notified of any failing tests and subsequent remedial action. Passing tests shall be reported no later than the start of the next work day.

When a mixture does not comply with specifications, the Contractor shall reject the material; unless the Engineer accepts the material for incorporation in the work, according to Article 105.03.

- (1) **Personnel Requirements.** The Contractor shall provide a Quality Control (QC) Manager who will have overall responsibility and authority for quality control. The jobsite and plant personnel shall be able to contact the QC Manager by cellular phone, two-way radio or other methods approved by the Engineer.

The QC Manager shall visit the jobsite a minimum of once a week. A visit shall be performed the day of a bridge deck pour, the day a non-routine mixture is placed as determined by the Engineer, or the day a plant is anticipated to produce more than 1000 cu yd (765 cu m). Any of the three required visits may be used to meet the once per week minimum requirement.

The Contractor shall provide personnel to perform the required inspections, sampling, testing and documentation in a timely manner. The Contractor shall refer to the Department's "Qualifications and Duties of Concrete Quality Control Personnel" document.

A Level I PCC Technician shall be provided at the jobsite during mixture production and placement, and may supervise concurrent pours on the project. For concurrent pours, a minimum of one Concrete Tester shall be required at each pour location. If the Level I PCC Technician is at one of the pour locations, a Concrete Tester is still required at the same location. Each Concrete Tester shall be able to contact the Level I PCC Technician by cellular phone, two-way radio or other methods approved by the Engineer. A single Level I PCC Technician shall not supervise concurrent pours for multiple contracts.

A Level II PCC Technician shall be provided at the plant, or shall be available, during mixture production and placement. A Level II PCC Technician may supervise a maximum of three plants. Whenever the Level II PCC Technician is not at the plant during mixture production and placement, a Concrete Tester or Level I PCC Technician shall be present at the plant to perform any necessary concrete tests. The Concrete Tester, Level I PCC Technician, or other individual shall also be trained to perform any necessary aggregate moisture tests, if the Level II PCC Technician is not at the plant during mixture production and placement. The Concrete Tester, Level I PCC Technician, plant personnel, and jobsite personnel shall have the ability to contact the Level II PCC Technician by cellular phone, two-way radio, or other methods approved by the Engineer.

For a mixture which is produced and placed with a mobile portland cement concrete plant as defined in Article 1103.04, a Level II PCC Technician shall be provided. The Level II PCC Technician shall be present at all times during mixture production and placement. However, the Level II PCC Technician may request to be available if operations are satisfactory. Approval shall be obtained from the Engineer, and jobsite personnel shall have the ability to contact the Level II PCC Technician by cellular phone, two-way radio, or other methods approved by the Engineer.

A Concrete Tester, Mixture Aggregate Technician, and Aggregate Technician may provide assistance with sampling and testing. A Gradation Technician may provide assistance with testing. A Concrete Tester shall be supervised by a Level I or Level II PCC Technician. A Gradation Technician shall be supervised by a Level II PCC Technician, Mixture Aggregate Technician, or Aggregate Technician.

- (2) **Required Plant Tests.** Sampling and testing shall be performed at the plant, or at a location approved by the Engineer, to control the production of a mixture. The required minimum Contractor plant sampling and testing is indicated in Article 1020.16(g) Schedule A.
- (3) **Required Field Tests.** Sampling and testing shall be performed at the jobsite to control the production of a mixture, and to comply with specifications for placement. For standard curing, after initial curing, and for strength testing; the location shall be approved by the Engineer. The required minimum Contractor jobsite sampling and testing is indicated in Article 1020.16(g), Schedule B.
- (d) **Quality Assurance by Engineer.** The Engineer will perform quality assurance tests on independent samples and split samples. An independent sample is a field sample obtained and tested by only one party. A split sample is one of two equal portions of a field sample, where two parties each receive one portion for testing. The Engineer may request the Contractor to obtain a split sample. Aggregate split samples and any failing strength specimen shall be retained until permission is given by the Engineer for disposal. The results of all quality assurance tests by the Engineer will be made available to the Contractor. However, Contractor split sample test results shall be provided to the Engineer before Department test results are revealed. The Engineer's quality assurance independent sample and split sample testing is indicated in Article 1020.16(g), Schedule C.
- (1) **Strength Testing.** For strength testing, Article 1020.09 shall apply, except the Contractor and Engineer strength specimens may be placed in the same field curing box for initial curing and may be cured in the same water storage tank for final curing.
- (2) **Comparing Test Results.** Differences between the Engineer's and the Contractor's split sample test results will be considered reasonable if within the following limits:

Test Parameter	Acceptable Limits of Precision
Slump	0.75 in. (20 mm)
Air Content	0.9%
Compressive Strength	900 psi (6200 kPa)
Flexural Strength	90 psi (620 kPa)
Slump Flow (Self-Consolidating Concrete (SCC))	1.5 in. (40 mm)
Visual Stability Index (SCC)	Not Applicable
J-Ring (SCC)	1.5 in. (40 mm)
L-Box (SCC)	10 %
Hardened Visual Stability Index (SCC)	Not Applicable
Dynamic Segregation Index (SCC)	1.0 %
Flow (Controlled Low-Strength Material (CLSM))	1.5 in. (40 mm)
Strength (Controlled Low-Strength Material (CLSM))	40 psi (275 kPa)
Aggregate Gradation	See "Guideline for Sample Comparison" in Appendix "A" of the Manual of Test Procedures for Materials.

When acceptable limits of precision have been met, but only one party is within specification limits, the failing test shall be resolved before the material may be considered for acceptance.

(3) Test Results and Specification Limits.

- a. Split Sample Testing. If either the Engineer's or the Contractor's split sample test result is not within specification limits, and the other party is within specification limits; immediate retests on a split sample shall be performed for slump, air content, slump flow, visual stability index, J-Ring, L-Box, dynamic segregation index, flow (CLSM), or aggregate gradation. A passing retest result by each party will require no further action. If either the Engineer's or Contractor's slump, air content, slump flow, visual stability index, J-Ring, L-Box, dynamic segregation index, flow (CLSM), or aggregate gradation split sample retest result is a failure; or if either the Engineer's or Contractor's strength or hardened visual stability index test result is a failure, and the other party is within specification limits; the following actions shall be initiated to investigate the test failure:
1. The Engineer and the Contractor shall investigate the sampling method, test procedure, equipment condition, equipment calibration, and other factors.
 2. The Engineer or the Contractor shall replace test equipment, as determined by the Engineer.
 3. The Engineer and the Contractor shall perform additional testing on split samples, as determined by the Engineer.

For aggregate gradation, jobsite slump, jobsite air content, jobsite slump flow, jobsite visual stability index, jobsite J-Ring, jobsite L-Box, jobsite dynamic segregation index, and jobsite flow (CLSM); if the failing split sample test result is not resolved according to 1., 2., or 3., and the mixture has not been placed, the Contractor shall reject the material; unless the Engineer accepts the material for incorporation in the work according to Article 105.03. If the mixture has already been placed, or if a failing strength or hardened visual stability index test result is not resolved according to 1., 2., or 3., the material will be considered unacceptable.

If a continued trend of difference exists between the Engineer's and the Contractor's split sample test results, or if split sample test results exceed the acceptable limits of precision, the Engineer and the Contractor shall investigate according to items 1., 2., and 3.

- b. Independent Sample Testing. For aggregate gradation, jobsite slump, jobsite air content jobsite slump flow, jobsite visual stability index, jobsite J-Ring, jobsite L-Box, jobsite dynamic segregation index, jobsite flow (CLSM); if the result of a quality assurance test on a sample independently obtained by the Engineer is not within specification limits, and the mixture has not been placed, the Contractor shall reject the material, unless the Engineer accepts the material for incorporation in the work according to Article 105.03. If the mixture has already

been placed or the Engineer obtains a failing strength or hardened visual stability index test result, the material will be considered unacceptable.

(e) Acceptance by the Engineer. Final acceptance will be based on the Standard Specifications and the following:

- (1) The Contractor's compliance with all contract documents for quality control.
- (2) Validation of Contractor quality control test results by comparison with the Engineer's quality assurance test results using split samples. Any quality control or quality assurance test determined to be flawed may be declared invalid only when reviewed and approved by the Engineer. The Engineer will declare a test result invalid only if it is proven that improper sampling or testing occurred. The test result is to be recorded and the reason for declaring the test invalid will be provided by the Engineer.
- (3) Comparison of the Engineer's quality assurance test results with specification limits using samples independently obtained by the Engineer.

The Engineer may suspend mixture production, reject materials, or take other appropriate action if the Contractor does not control the quality of concrete, cement aggregate mixture II, or controlled low-strength material for acceptance. The decision will be determined according to (1), (2), or (3).

(f) Documentation.

- (1) Records. The Contractor shall be responsible for documenting all observations, inspections, adjustments to the mix design, test results, retest results, and corrective actions in a bound hardback field book, bound hardback diary, or appropriate Department form, which shall become the property of the Department. The documentation shall include a method to compare the Engineer's test results with the Contractor's results. The Contractor shall be responsible for the maintenance of all permanent records whether obtained by the Contractor, the consultants, the subcontractors, or the producer of the mixture. The Contractor shall provide the Engineer full access to all documentation throughout the progress of the work.

The Department's form MI 504M, form BMPR MI654, and form BMPR MI655 shall be completed by the Contractor, and shall be submitted to the Engineer weekly or as required by the Engineer. A correctly completed form MI 504M, form BMPR MI654, and form BMPR MI655 are required to authorize payment by the Engineer, for applicable pay items.

- (2) Delivery Truck Ticket. The following information shall be recorded on each delivery ticket or in a bound hardback field book: initial revolution counter reading (final reading optional) at the jobsite, if the mixture is truck-mixed; time discharged at the jobsite; total amount of each admixture added at the jobsite; and total amount of water added at the jobsite.

(g) Basis of Payment and Schedules. Quality Control/Quality Assurance of portland cement concrete mixtures will not be paid for separately, but shall be considered as included in the cost of the various concrete contract items.

SCHEDULE A

CONTRACTOR PLANT SAMPLING AND TESTING			
Item	Test	Frequency	IL Modified AASHTO or Department Test Method ^{1/}
Aggregates (Arriving at Plant)	Gradation ^{2/}	As needed to check source for each gradation number	2, 11, 27, and 248
Aggregates (Stored at Plant in Stockpiles or Bins)	Gradation ^{2/}	2,500 cu yd (1,900 cu m) for each gradation number ^{3/}	2, 11, 27, and 248
Aggregates (Stored at Plant in Stockpiles or Bins)	Moisture ^{4/} : Fine Aggregate	Once per week for moisture sensor, otherwise daily for each gradation number	Flask, Dunagan, Pycnometer Jar, or 255
	Moisture ^{4/} : Coarse Aggregate	As needed to control production for each gradation number	Dunagan, Pycnometer Jar, or 255
Mixture ^{5/}	Slump Air Content Unit Weight / Yield Slump Flow (SCC) Visual Stability Index (SCC) J-Ring (SCC) ^{6/} L-Box (SCC) ^{6/} Temperature	As needed to control production	T 141 and T 119 T 141 and T 152 or T 196 T 141 and T 121 SCC-1 and SCC-2 SCC-1 and SCC-2 SCC-1 and SCC-3 SCC-1 and SCC-4 T 141 and T 309
Mixture (CLSM) ^{7/}	Flow Air Content Temperature	As needed to control production	Illinois Test Procedure 307

1/ Refer to the Department's "Manual of Test Procedures for Materials".

2/ All gradation tests shall be washed. Testing shall be completed no later than 24 hours after the aggregate has been sampled.

3/ One per week (Sunday through Saturday) minimum unless the stockpile has not received additional aggregate material since the previous test.

One per day minimum for a bridge deck pour unless the stockpile has not received additional aggregate material since the previous test. The sample shall be taken and testing completed prior to the pour. The bridge deck aggregate sample may be taken the day before the pour or as approved by the Engineer.

4/ If the moisture test and moisture sensor disagree by more than 0.5 percent, retest. If the difference remains, adjust the moisture sensor to an average of two or more moisture tests. The Department's "Water/Cement Ratio Worksheet" form shall be completed when applicable.

5/ The Contractor may also perform strength testing according to Illinois Modified AASHTO T 141, T 23, and T 22 or T 177; or water content testing according to Illinois Modified AASHTO T 318.

The Contractor may also perform other available self-consolidating concrete (SCC) tests at the plant to control mixture production.

- 6/ The Contractor shall select the J-Ring or L-Box test for plant sampling and testing.
- 7/ The Contractor may also perform strength testing according to Illinois Test Procedure 307.

SCHEDULE B

CONTRACTOR JOBSITE SAMPLING & TESTING ^{1/}			
Item	Measured Property	Random Sample Testing Frequency per Mix Design and per Plant ^{2/}	IL Modified AASHTO Test Method
Pavement, Shoulder, Base Course, Widening, Driveway Pavement, Railroad Crossing, Cement Aggregate Mixture II	Slump ^{3/ 4/}	1 per 500 cu yd (400 cu m) or minimum 1/day	T 141 and T 119
	Air Content ^{3/ 5/ 6/}	1 per 100 cu yd (80 cu m) or minimum 1/day	T 141 and T 152 or T 196
	Compressive Strength ^{7/ 8/} or Flexural Strength ^{7/ 8/}	1 per 1250 cu yd (1000 cu m) or minimum 1/day	T 141, T 22 and T 23 or T 141, T 177 and T 23
Bridge Slab ^{9/} , Bridge Deck ^{9/} , Bridge Deck Overlay ^{9/} , Superstructure ^{9/} , Substructure, Culvert, Miscellaneous Drainage Structures, Retaining Wall, Building Wall, Drilled Shaft Pile & Encasement Footing, Foundation, Pavement Patching, Structural Repairs	Slump ^{3/ 4/}	1 per 50 cu yd (40 cu m) or minimum 1/day	T 141 and T 119
	Air Content ^{3/ 5/ 6/}	1 per 50 cu yd (40 cu m) or minimum 1/day	T 141 and T 152 or T 196
	Compressive Strength ^{7/ 8/} or Flexural Strength ^{7/ 8/}	1 per 250 cu yd (200 cu m) or minimum 1/day	T 141, T 22 and T 23 or T 141, T 177 and T 23
Seal Coat	Slump ^{3/}	1 per 250 cu yd (200 cu m) or minimum 1/day	T 141 and T 119
	Air Content ^{3/ 5/ 6/}	1 per 250 cu yd (200 cu m) or minimum 1/day when air is entrained	T 141 and T 152 or T 196
	Compressive Strength ^{7/ 8/} or Flexural Strength ^{7/ 8/}	1 per 250 cu yd (200 cu m) or minimum 1/day	T 141, T 22 and T 23 or T 141, T 177 and T 23

CONTRACTOR JOBSITE SAMPLING & TESTING ^{1/}			
Curb, Gutter, Median, Barrier, Sidewalk, Slope Wall, Paved Ditch, Fabric Formed Concrete Revetment Mat ^{10/} , Miscellaneous Items, Incidental Items	Slump ^{3/ 4/}	1 per 100 cu yd (80 cu m) or minimum 1/day	T 141 and T 119
	Air Content ^{3/ 5/ 6/}	1 per 50 cu yd (40 cu m) or minimum 1/day	T 141 and T 152 or T 196
	Compressive Strength ^{7/ 8/} or Flexural Strength ^{7/ 8/}	1 per 400 cu yd (300 cu m) or minimum 1/day	T 141, T 22 and T 23 or T 141, T 177 and T 23
The Item will use a Self-Consolidating Concrete Mixture	Slump Flow ^{3/} VSI ^{3/} J-Ring ^{3/ 11/} L-Box ^{3/ 11/}	Perform at same frequency that is specified for the Item's slump	SCC-1 & SCC-2 SCC-1 & SCC-2 SCC-1 & SCC-3 SCC-1 & SCC-4
The Item will use a Self-Consolidating Concrete Mixture	HVSI ^{12/}	Minimum 1/day at start of production for that day	SCC-1 and SCC-6
The Item will use a Self-Consolidating Concrete Mixture	Dynamic Segregation Index (DSI)	Minimum 1/week at start of production for that week	SCC-1 and SCC-8 (Option C)
The Item will use a Self-Consolidating Concrete Mixture	Air Content ^{3/ 5/ 6/}	Perform at same frequency that is specified for the Item's air content	SCC-1 and T 152 or T 196
The Item will use a Self-Consolidating Concrete Mixture	Compressive Strength ^{7/ 8/} or Flexural Strength ^{7/ 8/}	Perform at same frequency that is specified for the Item's strength	SCC-1, T 22 and T 23 or SCC-1, T 177 and T 23
All	Temperature ^{3/}	As needed to control production	T 141 and T 309
Controlled Low-Strength Material (CLSM)	Flow, Air Content, Compressive Strength (28-day) ^{13/} , and Temperature	First truck load delivered and as needed to control production thereafter	Illinois Test Procedure 307

1/ Sampling and testing of small quantities of curb, gutter, median, barrier, sidewalk, slope wall, paved ditch, miscellaneous items, and incidental items may be waived by the Engineer if requested by the Contractor. However, quality control personnel are still required according to Article 1020.16(c)(1) The Contractor shall also provide recent evidence that similar material has been found to be satisfactory under normal sampling and testing procedures. The total quantity that may be waived for testing shall not exceed 100 cu yd (76 cu m) per contract.

If the Contractor's or Engineer's test result for any jobsite mixture test is not within the specification limits, all subsequent truck loads delivered shall be tested by the Contractor until the problem is corrected.

2/ If one mix design is being used for several construction items during a day's production, one testing frequency may be selected to include all items. The construction items shall have the same slump, air content, and water/cement ratio specifications. For self-consolidating concrete, the construction items shall have the same slump flow, visual

stability index, J-Ring, L-Box, air content, and water/cement ratio specifications. The frequency selected shall equal or exceed the testing required for the construction item.

One sufficiently sized sample shall be taken to perform the required test(s). Random numbers shall be determined according to the Department's "Method for Obtaining Random Samples for Concrete". The Engineer will provide random sample locations.

- 3/ The temperature, slump, and air content tests shall be performed on the first truck load delivered, for each pour. For self consolidating concrete, the temperature, slump flow, visual stability index, J-Ring or L-Box, and air content tests shall be performed on the first truck load delivered, for each pour. Unless a random sample is required for the first truck load, testing the first truck load does not satisfy random sampling requirements.
- 4/ The slump random sample testing frequency shall be a minimum 1/day for a construction item which is slipformed.
- 5/ If a pump or conveyor is used for placement, a correction factor shall be established to allow for a loss of air content during transport. The first three truck loads delivered shall be tested, before and after transport by the pump or conveyor, to establish the correction factor. Once the correction is determined, it shall be re-checked after an additional 50 cu yd (40 cu m) is pumped, or an additional 100 cu yd (80 cu m) is conveyed. This shall continue throughout the pour. If the re-check indicates the correction factor has changed, a minimum of two truckloads is required to re-establish the correction factor. The correction factor shall also be re-established when significant changes in temperature, distance, pump or conveyor arrangement, and other factors have occurred. If the correction factor is >3.0 percent, the Contractor shall take corrective action to reduce the loss of air content during transport by the pump or conveyor. The Contractor shall record all air content test results, correction factors and corrected air contents. The corrected air content shall be reported on form BMPR MI654.
- 6/ If the Contractor's or Engineer's air content test result is within the specification limits, and 0.2 percent or closer to either limit, the next truck load delivered shall be tested by the Contractor. For example, if the specified air content range is 5.0 to 8.0 percent and the test result is 5.0, 5.1, 5.2, 7.8, 7.9 or 8.0 percent, the next truck shall be tested by the Contractor.
- 7/ The test of record for strength shall be the day indicated in Article 1020.04. For cement aggregate mixture II, a strength requirement is not specified and testing is not required. Additional strength testing to determine early falsework and form removal, early pavement or bridge opening to traffic, or to monitor strengths is at the discretion of the Contractor. Strength shall be defined as the average of at least two cylinder or two beam breaks for field tests.
- 8/ In addition to the strength test, a slump test, air content test, and temperature test shall be performed on the same sample. For self-consolidating concrete, a slump flow test, visual stability index test, J-Ring or L-Box test, air content test, and temperature test shall be performed on the same sample as the strength test. For mixtures pumped or conveyed, the Contractor shall sample according to Illinois Modified AASHTO T 141.
- 9/ The air content test will be required for each delivered truck load.

- 10/ For fabric formed concrete revetment mat, the slump test is not required and the flexural strength test is not applicable.
- 11/ The Contractor shall select the J-Ring or L-Box test for jobsite sampling and testing.
- 12/ In addition to the hardened visual stability index (HVSI) test, a slump flow test, visual stability index (VSI) test, J-Ring or L-Box test, air content test, and temperature test shall be performed on the same sample. The Contractor shall retain all hardened visual stability index cut cylinder specimens until the Engineer notifies the Contractor that the specimens may be discarded.
- 13/ The test of record for strength shall be the day indicated in Article 1019.04. In addition to the strength test, a flow test, air content test, and temperature test shall be performed on the same sample. The strength test may be waived by the Engineer if future removal of the material is not a concern.

SCHEDULE C

ENGINEER QUALITY ASSURANCE INDEPENDENT SAMPLE TESTING		
Location	Measured Property	Testing Frequency ^{1/}
Plant	Gradation of aggregates stored in stockpiles or bins, Slump and Air Content	As determined by the Engineer.
Jobsite	Slump, Air Content, Slump Flow, Visual Stability Index, J-Ring, L-Box, Hardened Visual Stability Index, Dynamic Segregation Index and Strength	As determined by the Engineer.
	Flow, Air Content, Strength (28-day), and Dynamic Cone Penetration for Controlled Low-Strength Material (CLSM)	As determined by the Engineer

ENGINEER QUALITY ASSURANCE SPLIT SAMPLE TESTING		
Location	Measured Property	Testing Frequency ^{1/}
Plant	Gradation of aggregates stored in stockpiles or bins ^{2/}	At the beginning of the project, the first test performed by the Contractor. Thereafter, a minimum of 10% of total tests required of the Contractor will be performed per aggregate gradation number and per plant.
	Slump and Air Content	As determined by the Engineer.
Jobsite	Slump ^{2/} , Air Content ^{2/ 3/} , Slump Flow ^{2/} , Visual Stability Index ^{2/} , J-Ring ^{2/} and L-box ^{2/}	At the beginning of the project, the first three tests performed by the Contractor. Thereafter, a minimum of 20% of total tests required of the Contractor will be performed per plant, which will include a minimum of one test per mix design.
	Hardened Visual Stability Index ^{2/}	As determined by the Engineer.
	Dynamic Segregation Index ^{2/}	As determined by the Engineer.
	Strength ^{2/}	At the beginning of the project, the first test performed by the Contractor. Thereafter, a minimum of 20% of total tests required of the Contractor will be performed per plant, which will include a minimum of one test per mix design.
	Flow, Air Content, and Strength (28-day) for Controlled Low-Strength Material (CLSM)	As determined by the Engineer.

1/ The Engineer will perform the testing throughout the period of quality control testing by the Contractor.

- 2/ The Engineer will witness and take immediate possession of or otherwise secure the Department's split sample obtained by the Contractor.
- 3/ Before transport by pump or conveyor, a minimum of 20 percent of total tests required of the Contractor will be performed per mix design and per plant. After transport by pump or conveyor, a minimum of 20 percent of total tests required of the Contractor will be performed per mix design and per plant.

SCHEDULE D

CONCRETE QUALITY CONTROL AND QUALITY ASSURANCE DOCUMENTS

- (a) Model Quality Control Plan for Concrete Production (*)
- (b) Qualifications and Duties of Concrete Quality Control Personnel (*)
- (c) Development of Gradation Bands on Incoming Aggregate at Mix Plants (*)
- (d) Required Sampling and Testing Equipment for Concrete (*)
- (e) Method for Obtaining Random Samples for Concrete (*)
- (f) Calibration of Concrete Testing Equipment (BMPR PCCQ01 through BMPR PCCQ09) (*)
- (g) Water/Cement Ratio Worksheet (BMPR PCCW01) (*)
- (h) Field/Lab Gradations (MI 504M) (*)
- (i) Concrete Air, Slump and Quantity (BMPR MI654) (*)
- (j) P.C. Concrete Strengths (BMPR MI655) (*)
- (k) Aggregate Technician Course or Mixture Aggregate Technician Course (*)
- (l) Portland Cement Concrete Tester Course (*)
- (m) Portland Cement Concrete Level I Technician Course - Manual of Instructions for Concrete Testing (*)
- (n) Portland Cement Concrete Level II Technician Course - Manual of Instructions for Concrete Proportioning (*)
- (o) Portland Cement Concrete Level III Technician Course - Manual of Instructions for Design of Concrete Mixtures (*)
- (p) Manual of Test Procedures for Materials

* Refer to Appendix C of the Manual of Test Procedures for Materials for more information."

Designer Note: Insert into all contracts with HMA items.

RECLAIMED ASPHALT PAVEMENT AND RECLAIMED ASPHALT SHINGLES (BDE)

Effective: November 1, 2012

Revise: January 1, 2013

Revise Section 1031 of the Standard Specifications to read:

"SECTION 1031. RECLAIMED ASPHALT PAVEMENT AND RECLAIMED ASPHALT SHINGLES

1031.01 Description. Reclaimed asphalt pavement and reclaimed asphalt shingles shall be according to the following.

- (a) Reclaimed Asphalt Pavement (RAP). RAP is the material produced by cold milling or crushing an existing hot-mix asphalt (HMA) pavement. The Contractor shall supply written documentation that the RAP originated from routes or airfields under federal, state, or local agency jurisdiction.
- (b) Reclaimed Asphalt Shingles (RAS). Reclaimed asphalt shingles (RAS). RAS is from the processing and grinding of preconsumer or post-consumer shingles. RAS shall be a clean and uniform material with a maximum of 0.5 percent unacceptable material, as defined in Bureau of Materials and Physical Research Policy Memorandum "Reclaimed Asphalt Shingle (RAS) Sources", by weight of RAS. All RAS used shall come from a Bureau of Materials and Physical Research approved processing facility where it shall be ground and processed to 100 percent passing the 3/8 in. (9.5 mm) sieve and 93 percent passing the #4 (4.75 mm) sieve based on a dry shake gradation. RAS shall be uniform in gradation and asphalt binder content and shall meet the testing requirements specified herein. In addition, RAS shall meet the following Type 1 or Type 2 requirements.
 - (1) Type 1. Type 1 RAS shall be processed, preconsumer asphalt shingles salvaged from the manufacture of residential asphalt roofing shingles.
 - (2) Type 2. Type 2 RAS shall be processed post-consumer shingles only, salvaged from residential, or four unit or less dwellings not subject to the National Emission Standards for Hazardous Air Pollutants (NESHAP).

1031.02 Stockpiles. RAP and RAS stockpiles shall be according to the following.

- (a) RAP Stockpiles. The Contractor shall construct individual, sealed RAP stockpiles meeting one of the following definitions. No additional RAP shall be added to the pile after the pile has been sealed. Stockpiles shall be sufficiently separated to prevent intermingling at the base. Stockpiles shall be identified by signs indicating the type as listed below (i.e. "Homogeneous Surface").

Prior to milling, the Contractor shall request the District provide documentation on the quality of the RAP to clarify the appropriate stockpile.

- (1) Fractionated RAP (FRAP). FRAP shall consist of RAP from Class I, HMA (High and Low ESAL) mixtures. The coarse aggregate in FRAP shall be crushed aggregate and may represent more than one aggregate type and/or quality but shall be at least C quality. All FRAP shall be fractionated prior to testing by screening into a minimum of two size fractions with the separation occurring on or between the #4 (4.75 mm) and 1/2 in. (12.5 mm) sieves. Agglomerations shall be minimized such that 100 percent of the RAP shall pass the sieve size specified below for the mix the FRAP will be incorporated.

Mixture FRAP will be used in:	Sieve Size that 100% of FRAP Shall Pass
IL-25.0	2 in. (50 mm)
IL-19.0	1 1/2 in. (40 mm)
IL-12.5	1 in. (25 mm)
IL-9.5	3/4 in. (20 mm)
IL-4.75	1/2 in. (13 mm)

- (2) Homogeneous. Homogeneous RAP stockpiles shall consist of RAP from Class I, HMA (High and Low ESAL) mixtures and represent: 1) the same aggregate quality, but shall be at least C quality; 2) the same type of crushed aggregate (either crushed natural aggregate, ACBF slag, or steel slag); 3) similar gradation; and 4) similar asphalt binder content. If approved by the Engineer, combined single pass surface/binder millings may be considered "homogenous" with a quality rating dictated by the lowest coarse aggregate quality present in the mixture.
- (3) Conglomerate. Conglomerate RAP stockpiles shall consist of RAP from Class I, HMA (High and Low ESAL) mixtures. The coarse aggregate in this RAP shall be crushed aggregate and may represent more than one aggregate type and/or quality but shall be at least C quality. This RAP may have an inconsistent gradation and/or asphalt binder content prior to processing. All conglomerate RAP shall be processed prior to testing by crushing to where all RAP shall pass the 5/8 in. (16 mm) or smaller screen. Conglomerate RAP stockpiles shall not contain steel slag.
- (4) Conglomerate "D" Quality (DQ). Conglomerate DQ RAP stockpiles shall consist of RAP from Class I, HMA (High or Low ESAL), or "All Other" (as defined by Article 1030.04(a)(3)) mixtures. The coarse aggregate in this RAP may be crushed or round but shall be at least D quality. This RAP may have an inconsistent gradation and/or asphalt binder content. Conglomerate DQ RAP stockpiles shall not contain steel slag.
- (5) Non-Quality. RAP stockpiles that do not meet the requirements of the stockpile categories listed above shall be classified as "Non-Quality".

RAP/FRAP containing contaminants, such as earth, brick, sand, concrete, sheet asphalt, bituminous surface treatment (i.e. chip seal), pavement fabric, joint sealants, etc., will be unacceptable unless the contaminants are removed to the satisfaction of the Engineer. Sheet asphalt shall be stockpiled separately.

- (b) RAS Stockpiles. Type 1 and Type 2 RAS shall be stockpiled separately and shall not be intermingled. Each stockpile shall be signed indicating what type of RAS is present.

Unless otherwise approved by the Engineer, mechanically blending manufactured sand (FM 20 or FM 22) up to an equal weight of RAS with the processed RAS will be

permitted to improve workability. The sand shall be "B Quality" or better from an approved Aggregate Gradation Control System source. The sand shall be accounted for in the mix design and during HMA production.

Records identifying the shingle processing facility supplying the RAS, RAS type and lot number shall be maintained by project contract number and kept for a minimum of three years.

1031.03 Testing. RAP/FRAP and RAS testing shall be according to the following.

(a) **RAP/FRAP Testing.** When used in HMA, the RAP/FRAP shall be sampled and tested either during or after stockpiling.

(1) **During Stockpiling.** For testing during stockpiling, washed extraction samples shall be run at the minimum frequency of one sample per 500 tons (450 metric tons) for the first 2000 tons (1800 metric tons) and one sample per 2000 tons (1800 metric tons) thereafter. A minimum of five tests shall be required for stockpiles less than 4000 tons (3600 metric tons).

(2) **After Stockpiling.** For testing after stockpiling, the Contractor shall submit a plan for approval to the District proposing a satisfactory method of sampling and testing the RAP/FRAP pile either in-situ or by restockpiling. The sampling plan shall meet the minimum frequency required above and detail the procedure used to obtain representative samples throughout the pile for testing.

Each sample shall be split to obtain two equal samples of test sample size. One of the two test samples from the final split shall be labeled and stored for Department use. The Contractor shall extract the other test sample according to Department procedure. The Engineer reserves the right to test any sample (split or Department-taken) to verify Contractor test results.

(b) **RAS Testing.** RAS or RAS blended with manufactured sand shall be sampled and tested during stockpiling according to Illinois Department of Transportation Policy Memorandum, "Reclaimed Asphalt Shingle (RAS) Source".

Samples shall be collected during stockpiling at the minimum frequency of one sample per 200 tons (180 metric tons) for the first 1000 tons (900 metric tons) and one sample per 250 tons (225 metric tons) thereafter. A minimum of five samples are required for stockpiles less than 1000 tons (900 metric tons). Once a ≤ 1000 ton (900 metric ton), five-sample/test stockpile has been established it shall be sealed. Additional incoming RAS or RAS blended with manufactured sand shall be stockpiled in a separate working pile as designated in the Quality Control plan and only added to the sealed stockpile when the test results of the working pile are complete and are found to meet the tolerances specified herein for the original sealed RAS stockpile.

Before testing, each sample shall be split to obtain two test samples. One of the two test samples from the final split shall be labeled and stored for Department use. The Contractor shall perform a washed extraction and test for unacceptable materials on the other test sample according to Department procedures. The Engineer reserves the right to test any sample (split or Department-taken) to verify Contractor test results.

If the sampling and testing was performed at the shingle processing facility in accordance with the QC Plan, the Contractor shall obtain and make available all of the test results from start of the initial stockpile.

1031.04 Evaluation of Tests. Evaluation of tests results shall be according to the following.

- (a) Evaluation of RAP/FRAP Test Results. All of the extraction results shall be compiled and averaged for asphalt binder content and gradation and, when applicable G_{mm} . Individual extraction test results, when compared to the averages, will be accepted if within the tolerances listed below.

Parameter	FRAP/Homogeneous /Conglomerate	Conglomerate "D" Quality
1 in. (25 mm)		± 5 %
1/2 in. (12.5 mm)	± 8 %	± 15 %
No. 4 (4.75 mm)	± 6 %	± 13 %
No. 8 (2.36 mm)	± 5 %	
No. 16 (1.18 mm)		± 15 %
No. 30 (600 μm)	± 5 %	
No. 200 (75 μm)	± 2.0 %	± 4.0 %
Asphalt Binder	± 0.4 % ^{1/}	± 0.5 %
G_{mm}	± 0.03	

1/ The tolerance for FRAP shall be ± 0.3 %.

If more than 20 percent of the individual sieves and/or asphalt binder content tests are out of the above tolerances, the RAP/FRAP shall not be used in HMA unless the RAP/FRAP representing the failing tests is removed from the stockpile. All test data and acceptance ranges shall be sent to the District for evaluation.

With the approval of the Engineer, the ignition oven may be substituted for extractions according to the Illinois Test Procedure, "Calibration of the Ignition Oven for the Purpose of Characterizing Reclaimed Asphalt Pavement (RAP)".

- (b) Evaluation of RAS and RAS Blended with Manufactured Sand Test Results. All of the test results, with the exception of percent unacceptable materials, shall be compiled and averaged for asphalt binder content and gradation. Individual test results, when compared to the averages, will be accepted if within the tolerances listed below.

Parameter	RAS
No. 8 (2.36 mm)	± 5 %
No. 16 (1.18 mm)	± 5 %
No. 30 (600 μm)	± 4 %
No. 200 (75 μm)	± 2.0 %
Asphalt Binder Content	± 1.5 %

If more than 20 percent of the individual sieves and/or asphalt binder content tests are out of the above tolerances, or if the percent unacceptable material exceeds 0.5 percent by weight of material retained on the # 4 (4.75 mm) sieve, the RAS or RAS blend shall not be used in Department projects. All test data and acceptance ranges shall be sent to the District for evaluation.

1031.05 Quality Designation of Aggregate in RAP/FRAP.

- (a) RAP. The aggregate quality of the RAP for homogenous, conglomerate, and conglomerate "D" quality stockpiles shall be set by the lowest quality of coarse aggregate in the RAP stockpile and are designated as follows.
- (1) RAP from Class I, Superpave/HMA (High ESAL), or (Low ESAL) IL-9.5L surface mixtures are designated as containing Class B quality coarse aggregate.
 - (2) RAP from Superpave/HMA (Low ESAL) IL-19.0L binder mixture is designated as Class D quality coarse aggregate.
 - (3) RAP from Class I, Superpave/HMA (High ESAL) binder mixtures, bituminous base course mixtures, and bituminous base course widening mixtures are designated as containing Class C quality coarse aggregate.
 - (4) RAP from bituminous stabilized subbase and BAM shoulders are designated as containing Class D quality coarse aggregate.
- (b) FRAP. If the Engineer has documentation of the quality of the FRAP aggregate, the Contractor shall use the assigned quality provided by the Engineer.

If the quality is not known, the quality shall be determined as follows. Coarse and fine FRAP stockpiles containing plus #4 (4.75 mm) sieve coarse aggregate shall have a maximum tonnage of 5,000 tons (4,500 metric tons). The Contractor shall obtain a representative sample witnessed by the Engineer. The sample shall be a minimum of 50 lb (25 kg). The sample shall be extracted according to Illinois Modified AASHTO T 164 by a consultant prequalified by the Department for the specified testing. The consultant shall submit the test results along with the recovered aggregate to the District Office. The cost for this testing shall be paid by the Contractor. The District will forward the sample to the BMPR Aggregate Lab for MicroDeval Testing, according to Illinois Modified AASHTO T 327. A maximum loss of 15.0 percent will be applied for all HMA applications.

1031.06 Use of RAP/FRAP and/or RAS in HMA. The use of RAP/FRAP and/or RAS shall be a Contractor's option when constructing HMA in all contracts.

- (a) RAP/FRAP. The use of RAP/FRAP in HMA shall be as follows.
- (1) Coarse Aggregate Size. The coarse aggregate in all RAP shall be equal to or less than the nominal maximum size requirement for the HMA mixture to be produced.
 - (2) Steel Slag Stockpiles. Homogeneous RAP stockpiles containing steel slag will be approved for use in all HMA (High ESAL and Low ESAL) Surface and Binder Mixture applications.
 - (3) Use in HMA Surface Mixtures (High and Low ESAL). RAP/FRAP stockpiles for use in HMA surface mixtures (High and Low ESAL) shall be FRAP or homogeneous in which the coarse aggregate is Class B quality or better. RAP/FRAP from Conglomerate stockpiles shall be considered equivalent to limestone for frictional considerations. Known frictional contributions from plus #4 (4.75 mm) homogeneous RAP and FRAP stockpiles will be accounted for in meeting frictional requirements in the specified mixture.

- (4) Use in HMA Binder Mixtures (High and Low ESAL), HMA Base Course, and HMA Base Course Widening. RAP/FRAP stockpiles for use in HMA binder mixtures (High and Low ESAL), HMA base course, and HMA base course widening shall be FRAP, homogeneous, or conglomerate, in which the coarse aggregate is Class C quality or better.
 - (5) Use in Shoulders and Subbase. RAP/FRAP stockpiles for use in HMA shoulders and stabilized subbase (HMA) shall be FRAP, homogeneous, conglomerate, or conglomerate DQ.
 - (6) When the Contractor chooses the RAP option, the percentage of RAP shall not exceed the amounts indicated in Article 1031.06(c)(1) below for a given N Design.
- (b) RAS. RAS meeting Type 1 or Type 2 requirements will be permitted in all HMA applications as specified herein.
- (c) RAP/FRAP and/or RAS Usage Limits. Type 1 or Type 2 RAS may be used alone or in conjunction with RAP or FRAP in HMA mixtures up to a maximum of 5.0% by weight of the total mix.
- (1) RAP/RAS. When RAP is used alone or RAP is used in conjunction with RAS, the percentage of virgin asphalt binder replacement shall not exceed the amounts listed in the Max RAP/RAS ABR table listed below for the given N design.

RAP/RAS Maximum Asphalt Binder Replacement (ABR) Percentage

HMA Mixtures ^{1/, 2/}	RAP/RAS Maximum ABR %		
	Binder/Leveling Binder	Surface	Polymer Modified
30	30	30	10
50	25	15	10
70	15	10	10
90	10	10	10
105	10	10	10

1/ For HMA "All Other" (shoulder and stabilized subbase) N-30, the RAP/RAS ABR shall not exceed 50 percent of the mixture.

2/ When RAP/RAS ABR exceeds 20 percent, the high and low virgin asphalt binder grades shall each be reduced by one grade (i.e. 25 percent ABR would require a virgin asphalt binder grade of PG64-22 to be reduced to a PG58-28). If warm mix asphalt (WMA) technology is utilized, and production temperatures do not exceed 275 °F (135 °C) the high and low virgin asphalt binder grades shall each be reduced by one grade when RAP/RAS ABR exceeds 25 percent (i.e. 26 percent RAP/RAS ABR would require a virgin asphalt binder grade of PG64-22 to be reduced to a PG58-28).

(2) FRAP/RAS. When FRAP is used alone or FRAP is used in conjunction with RAS, the percentage of virgin asphalt binder replacement shall not exceed the amounts listed in the FRAP/RAS tables listed below for the given N design.

Level 1 - FRAP/RAS Maximum Asphalt Binder Replacement (ABR) Percentage

HMA Mixtures <i>1/, 2/</i>	Level 1 - FRAP/RAS Maximum ABR %		
Ndesign	Binder/Leveling Binder	Surface	Polymer Modified <i>3/, 4/</i>
30	35	35	10
50	30	25	10
70	25	20	10
90	20	15	10
105	10	10	10

1/ For HMA "All Other" (shoulder and stabilized subbase) N30, the FRAP/RAS ABR shall not exceed 50 percent of the mixture.

2/ When FRAP/RAS ABR exceeds 20 percent for all mixes the high and low virgin asphalt binder grades shall each be reduced by one grade (i.e. 25 percent ABR would require a virgin asphalt binder grade of PG64-22 to be reduced to a PG58-28). If warm mix asphalt (WMA) technology is utilized, and production temperatures do not exceed 275 °F (135 °C) the high and low virgin asphalt binder grades shall each be reduced by one grade when FRAP/RAS ABR exceeds 25 percent (i.e. 26 percent ABR would require a virgin asphalt binder grade of PG64-22 to be reduced to a PG58-28).

3/ For SMA the FRAP/RAS ABR shall not exceed 20 percent.

4/ For IL-4.75 mix the FRAP/RAS ABR shall not exceed 20 percent.

Level 2 – FRAP/RAS Maximum Asphalt Binder Replacement (ABR) Percentage

HMA Mixtures <i>1/, 2/</i>	Level 2 – FRAP/RAS Maximum ABR %		
Ndesign	Binder/Leveling Binder	Surface	Polymer Modified <i>3/, 4/</i>
30	40	40	10
50	40	30	10
70	30	20	10
90	30	20	10
105	30	15	10

1/ For HMA "All Other" (shoulder and stabilized subbase) N30, the FRAP/RAS ABR shall not exceed 50 percent of the mixture.

2/ When FRAP/RAS ABR exceeds 20 percent for all mixes the high and low virgin asphalt binder grades shall each be reduced by one grade (i.e. 25 percent ABR would require a virgin asphalt binder grade of PG64-22 to be reduced to a PG58-28). If warm mix asphalt (WMA) technology is utilized, and production temperatures do not exceed 275 °F (135 °C) the high and low virgin asphalt binder grades shall each be reduced by one grade when FRAP/RAS ABR exceeds 25 percent (i.e. 26 percent ABR would require a virgin asphalt binder grade of PG64-22 to be reduced to a PG58-28).

3/ For SMA the FRAP/RAS ABR shall not exceed 20 percent.

4/ For IL-4.75 mix the FRAP/RAS ABR shall not exceed 30 percent.

1031.07 HMA Mix Designs. At the Contractor's option, HMA mixtures may be constructed utilizing RAP/FRAP and/or RAS material meeting the above detailed requirements.

FRAP/RAS mix designs exceeding the Level 1 FRAP/RAS Maximum ABR percentages shall be tested prior to submittal for verification, according to Illinois Modified AASHTO T 324 (Hamburg Wheel) and shall meet the following requirements.

Asphalt Binder Grade	# Repetitions	Max. Rut Depth in. (mm)
PG76-XX	20,000	1/2 (12.5)
PG70-XX	15,000	1/2 (12.5)
PG64-XX	7,500	1/2 (12.5)
PG58-XX	5,000	1/2 (12.5)

- (a) RAP/FRAP and/or RAS. RAP/FRAP and/or RAS designs shall be submitted for volumetric verification. If additional RAP/FRAP stockpiles are tested and found that no more than 20 percent of the results, as defined under "Testing" herein, are outside of the control tolerances set for the original RAP/FRAP stockpile and HMA mix design, and meets all of the requirements herein, the additional RAP/FRAP stockpiles may be used in the original mix design at the percent previously verified.
- (b) RAS. Type 1 and Type 2 RAS are not interchangeable in a mix design. A RAS stone bulk specific gravity (Gsb) of 2.500 shall be used for mix design purposes.

1031.08 HMA Production. Mixture production where the FRAP/RAS ABR percentage exceeds the Level 1 limits, shall be sampled within the first 500 tons (450 metric tons) on the first day of production with a split reserved for the Department. The mix sample shall be tested according to the Illinois Modified AASHTO T 324 and shall meet the requirements specified herein. Mix production shall not exceed 1500 tons (1350 metric tons) or one day's production, whichever comes first, until the testing is completed and the mixture is found to be in conformance. The requirement to cease mix production may be waived if the plant produced mixture conformance is demonstrated prior to start of mix production for a State contract.

- (a) RAP/FRAP. The coarse aggregate in all RAP/FRAP used shall be equal to or less than the nominal maximum size requirement for the HMA mixture being produced.

To remove or reduce agglomerated material, a scalping screen, gator, crushing unit, or comparable sizing device approved by the Engineer shall be used in the RAP feed system to remove or reduce oversized material. If material passing the sizing device adversely affects the mix production or quality of the mix, the sizing device shall be set at a size specified by the Engineer.

If the RAP/FRAP control tolerances or QC/QA test results require corrective action, the Contractor shall cease production of the mixture containing RAP/FRAP and either switch to the virgin aggregate design or submit a new RAP/FRAP design.

- (b) RAS. RAS shall be incorporated into the HMA mixture either by a separate weight depletion system or by using the RAP weigh belt. Either feed system shall be interlocked with the aggregate feed or weigh system to maintain correct proportions for all rates of production and batch sizes. The portion of RAS shall be controlled accurately to within ± 0.5 percent of the amount of RAS utilized. When using the weight

depletion system, flow indicators or sensing devices shall be provided and interlocked with the plant controls such that the mixture production is halted when RAS flow is interrupted.

When producing HMA containing RAS, a positive dust control system shall be utilized.

(c) RAP/FRAP and/or RAS. HMA plants utilizing RAP/FRAP and/or RAS shall be capable of automatically recording and printing the following information.

(1) Dryer Drum Plants.

- a. Date, month, year, and time to the nearest minute for each print.
- b. HMA mix number assigned by the Department.
- c. Accumulated weight of dry aggregate (combined or individual) in tons (metric tons) to the nearest 0.1 ton (0.1 metric ton).
- d. Accumulated dry weight of RAP/FRAP/RAS in tons (metric tons) to the nearest 0.1 ton (0.1 metric ton).
- e. Accumulated mineral filler in revolutions, tons (metric tons), etc. to the nearest 0.1 unit.
- f. Accumulated asphalt binder in gallons (liters), tons (metric tons), etc. to the nearest 0.1 unit.
- g. Residual asphalt binder in the RAP/FRAP material as a percent of the total mix to the nearest 0.1 percent.
- h. Aggregate and RAP/FRAP moisture compensators in percent as set on the control panel. (Required when accumulated or individual aggregate and RAP/FRAP are printed in wet condition.)

(2) Batch Plants.

- a. Date, month, year, and time to the nearest minute for each print.
- b. HMA mix number assigned by the Department.
- c. Individual virgin aggregate hot bin batch weights to the nearest pound (kilogram).
- d. Mineral filler weight to the nearest pound (kilogram).
- f. RAP/FRAP/RAS weight to the nearest pound (kilogram).
- g. Virgin asphalt binder weight to the nearest pound (kilogram).
- h. Residual asphalt binder in the RAP/FRAP/RAS material as a percent of the total mix to the nearest 0.1 percent.

The printouts shall be maintained in a file at the plant for a minimum of one year or as directed by the Engineer and shall be made available upon request. The printing system

will be inspected by the Engineer prior to production and verified at the beginning of each construction season thereafter.

1031.09 RAP in Aggregate Surface Course and Aggregate Shoulders. The use of RAP in aggregate surface course (temporary access entrances only) and aggregate wedge shoulders Type B shall be as follows.

- (a) Stockpiles and Testing. RAP stockpiles may be any of those listed in Article 1031.02, except "Non-Quality" and "FRAP". The testing requirements of Article 1031.03 shall not apply. RAP used to construct aggregate surface course and aggregate shoulders shall be according to the current Bureau of Materials and Physical Research's Policy Memorandum, "Reclaimed Asphalt Pavement (RAP) for Aggregate Applications".
- (b) Gradation. One hundred percent of the RAP material shall pass the 1 1/2 in. (37.5 mm) sieve. The RAP material shall be reasonably well graded from coarse to fine. RAP material that is gap-graded or single sized will not be accepted."

Designer Note: Insert into contracts utilizing drain pipe, tile, drainage mat, or wall drain.

DRAIN PIPE, TILE, DRAINAGE MAT, AND WALL DRAIN (BDE)

Effective: January 1, 2013

Add the following to Article 101.01 of the Standard Specifications.

“NTPEP National Transportation Product Evaluation Program”

Revise Article 1040.03(f) of the Standard Specifications to read:

“(f) Profile Wall Pipe-304. The manufacturer shall be listed as compliant through the NTPEP program and the pipe shall be according to AASHTO M 304.”

Revise the first sentence of the first paragraph of Article 1040.04(a) of the Standard Specifications to read:

“The manufacturer shall be listed as compliant through the NTPEP program and the pipe shall be according to AASHTO M 252 (nominal size – 3 to 10 in. (75 to 250 mm)).”

Revise Article 1040.04(b) of the Standard Specifications to read:

“(b) Corrugated PE Pipe with a Smooth Interior. The manufacturer shall be listed as compliant through the NTPEP program and the pipe shall be according to AASHTO M 294 (nominal size – 12 to 48 in. (300 to 1200 mm)). The pipe shall be Type S or D.”

Designer Note: Insert into contracts using fabric bearing pads.

FABRIC BEARING PADS (BDE)

Effective: January 1, 2013

Revise the second sentence of the fifth paragraph of Article 1082.01 of the Standard Specifications to read:

“The thickness of the fabric bearing pads shall be as shown on the plans within a tolerance of $\pm 10\%$.”

Designer Note: Insert into contracts using Highway Standards 701321, 701402, or 701423 at the district's discretion.

Use of this special provision should be limited to cases where temporary concrete barrier is not feasible due to lane closure time restrictions that require the barrier to be deployed or removed on a daily basis. Use of this barrier system should also be limited to work areas where larger barrier deflection from an impact event is acceptable. This BDE special was formerly named "Movable Traffic Barrier System (BDE)." When using this special provision also include BDE Special "Impact Attenuators, Temporary" and Recurring Special Provision Check Sheet #20 "Guardrail and Barrier Wall Delineation."

MOVABLE TRAFFIC BARRIER (BDE)

Effective: January 1, 2010

Revised: January 1, 2013

Description. This work shall consist of furnishing, installing, maintaining, relocating, and removing a movable traffic barrier at locations shown on the plans.

Materials.

Add the following to Article 1106.02 of the Standard Specifications:

- "(l) Movable Traffic Barrier. The movable traffic barrier shall meet the requirements of NCHRP Test Level 3 or AASHTO Manual for Assessing Safety Hardware (MASH) and be on the Department's approved list.

Shop drawings shall be furnished by the manufacturer and shall indicate the deflection of the barrier as determined by acceptance testing, the configuration of the barrier in that test, and the vehicle weight, velocity, and angle of impact of the deflection test. The Engineer shall be provided one copy of the shop drawings. The barrier shall be capable of being moved on and off the roadway on a daily basis."

CONSTRUCTION REQUIREMENTS

Add the following to Article 701.15 of the Standard Specifications:

- "(m) Movable Traffic Barrier. The movable traffic barrier shall be assembled and installed according to the manufacturer's specifications.

The approach end of the movable traffic barrier shall be protected with an impact attenuator which is capable of being moved with the movable barrier system.

When not in use, the device shall be stored longitudinally along the far edge of the shoulder or adjacent to concrete median barrier. The approach end shall be protected with the impact attenuator.

The barrier shall include nighttime delineation consisting of either barrier wall markers or corrugated retroreflective panels. The panels shall consist of one 6 x 36 in. (150 x

900 mm) panel per barrier unit and shall be yellow when on center line or left lane line and white when on edge line.”

Method of Measurement.

Add the following to Article 701.19 of the Standard Specifications:

“(h) Movable traffic barrier will be measured for payment in feet (meters) in place, along the centerline of the movable barrier.”

Basis of Payment.

Add the following to Article 701.20 of the Standard Specifications:

“(l) Movable Traffic Barrier will be paid for at the contract unit price per foot (meter) for MOVABLE TRAFFIC BARRIER.

Movement of the barrier will not be paid for separately, but shall be included in the contract unit price per foot (meter) for MOVABLE TRAFFIC BARRIER.”

Temporary impact attenuators will be paid for separately.

Designer Note: Use at the district's discretion when using Highway Standards 701321, 701402, or 701423.

Use of this special provision should be limited to cases where temporary concrete barrier is not feasible due to lane closure time restrictions that require the barrier to be deployed or removed within four hours. Use of this barrier system should also be limited to work areas where larger barrier deflection from an impact event is acceptable. When using this special also use BDE special "Impact Attenuators, Temporary" and Recurring Special Provision Check Sheet #20, "Guardrail and Barrier Wall Delineation."

TEMPORARY WATER FILLED BARRIER (BDE)

Effective: January 1, 2010

Revised: January 1, 2013

Description. This work shall consist of furnishing, installing, maintaining, relocating, and removing a temporary water filled barrier at locations shown on the plans.

Materials.

Add the following to Article 1106.02 of the Standard Specifications:

- "(k) Temporary Water Filled Barrier. The water filled barrier shall be a lightweight plastic shell designed to accept water ballast. The barrier shall meet the requirements of NCHRP Test Level 3 or AASHTO Manual for Assessing Safety Hardware (MASH) and be on the Department's approved list.

Shop drawings shall be furnished by the manufacturer and shall indicate the deflection of the barrier as determined acceptance testing, the configuration of the barrier in that test, and the vehicle weight, velocity, and angle of impact of the deflection test. The Engineer shall be provided one copy of the shop drawings."

CONSTRUCTION REQUIREMENTS

Add the following to Article 701.15 of the Standard Specifications:

- "(l) Temporary Water Filled Barrier. The temporary water filled barrier shall be assembled, installed, and maintained according to the manufacturer's specifications and be capable of withstanding below freezing temperatures. The barrier shall be installed with orange and white alternating units.

When not in use, the device shall be stored longitudinally along the far edge of the shoulder or adjacent to concrete median barrier.

The approach end of the barrier shall be protected with an impact attenuator unless the barrier can serve as its own crashworthy end treatment, as indicated in the Department's list of approved Temporary Longitudinal Traffic Barrier.

The barrier shall include nighttime delineation consisting of either barrier wall markers or corrugated retroreflective panels. The panels shall consist of one 6 x 36 in. (150 x 900 mm) panel per barrier unit and shall be yellow when on center line or left lane line and white when on edge line."

Method of Measurement.

Add the following to Article 701.19 of the Standard Specifications:

"(g) Temporary water filled barrier will be measured for payment in feet (meters) in place, along the centerline of the barrier."

Basis of Payment.

Add the following to Article 701.20 of the Standard Specifications:

"(k) This work will be paid for at the contract unit price per foot (meter) for TEMPORARY WATER FILLED BARRIER.

Movement of the barrier will not be paid for separately, but shall be included in the contract unit price per foot (meter) for TEMPORARY WATER FILLED BARRIER."

Temporary impact attenuators will be paid for separately.

Designer Note: Insert into contracts utilizing coated galvanized steel conduit in electrical installations.

COATED GALVANIZED STEEL CONDUIT (BDE)

Effective: January 1, 2013

Revise Article 1088.01(a)(3) of the Standard Specifications to read:

“(3) Coated Galvanized Steel Conduit. The conduit prior to coating shall meet the requirements for rigid metal conduit and be manufactured according to NEMA Standard No. RN1.

The coating shall have the following characteristics.

Hardness	85+ Shore A Durometer
Dielectric Strength	400 V/mil @ 60 Hz
Aging	1,000 Hours Atlas Weatherometer
Brittleness Temperature	0 °F (-18 °C) when tested according to ASTM D 746
Elongation	200 percent

The exterior galvanized surfaces shall be coated with a primer before the coating to ensure a bond between the zinc substrate and the coating. The bond strength created shall be greater than the tensile strength of the plastic coating. The nominal thickness of the coating shall be 40 mils (1 mm). The coating shall pass the following bonding test.

Two parallel cuts 1/2 in. (13 mm) apart and 1 1/2 in. (38 mm) in length shall be made with a sharp knife along the longitudinal axis. A third cut shall be made perpendicular to and crossing the longitudinal cuts at one end. The knife shall then be worked under the coating for 1/2 in. (13 mm) to free the coating from the metal.

Using pliers, the freed tab shall be pulled with a force applied vertically and away from the conduit. The tab shall tear rather than cause any additional coating to separate from the substrate.

A two part urethane coating shall be applied to the interior of the conduit. The internal coating shall have a nominal thickness of 2 mils (50 µm). The interior coating shall be applied in a manner so there are no runs, drips, or pinholes at any point. The coating shall not peel, flake, or chip off after a cut is made in the conduit or a scratch is made in the coating. The urethane interior coating applied shall afford sufficient flexibility to permit field bending without cracking or flaking of the interior coating.

All conduit fittings and couplings shall be as specified and recommended by the conduit manufacturer. All conduit fitting covers shall be furnished with stainless steel screws which have been encapsulated with a polyester material on the head to ensure maximum corrosion protection.”

District Special Provisions

Numeric Index

SECTION 100

District Special Provisions

<u>Standard Specifications</u>	<u>Item/Description</u>	<u>Doc. #</u>
105.00	CONSTRUCTION STATION LAYOUT	10500
105.06	PRESTAGE SITE CONSTRUCTION MEETINGS	10506
105.07	REMOVAL OF ABANDONED UNDERGROUND UTILITIES	10507
105.07a	STATUS OF UTILITIES/UTILITIES TO BE ADJUSTED	10507a
107.00a	NATIONWIDE 404 PERMIT REQUIREMENTS	10700a
107.31	LOCATION OF UNDERGROUND STATE MAINTAINED FACILITIES	10731
107.32	RIGHT-OF-WAY RESTRICTIONS	10732
108.03	DELAYED START OF MULTIPLE CONTRACTS	10803
108.05a	DATE OF COMPLETION	10805a
108.05b	DATE OF COMPLETION (PLUS WORKING DAYS)	10805b

SECTION 200

District Special Provisions

<u>Standard Specifications</u>	<u>Item/Description</u>	<u>Doc. #</u>
204.00	BORROW AND FURNISHED EXCAVATION	20400
205.00	GEOTECHNICAL REINFORCEMENT	20500
205.05	EMBANKMENT	20505
205.04	EMBANKMENT (RESTRICTIONS)	20504
205.05a	EMBANKMENT (SMALL EMBANKMENTS)	20505a
250.00	SEEDING, MINOR AREAS	25000
250.06a	MOWING	25006a
250.06b	MOWING	250.06b
253.00	TREE WHIP MIXTURE	25300
253.00b	SEEDLING MIXTURE A	25300b
281.00	GROUT FOR USE WITH RIPRAP	28100
281.04	STONE DUMPED RIPRAP *	28104
281.06	STONE RIPRAP	28106
283.03	AGGREGATE DITCH	28303

October 4, 2012

SECTION 300

District Special Provisions

<u>Standard Specifications</u>	<u>Item/Description</u>	<u>Doc. #</u>
301.01	PROOF ROLLING	30101
301.03	SUBGRADE TREATMENT	30103
302.00	SOIL MODIFICATION	30200
311.00	ROCKFILL	31100
311.01	SUBBASE GRANULAR MATERIAL	31101
355.00	TEMPORARY PAVEMENT	35500

SECTION 400

District Special Provisions

<u>Standard Specifications</u>	<u>Item/Description</u>	<u>Doc. #</u>
406.00	CLEAN EXISTING PAVEMENT EDGE JOINT	40600
406.01	ANTI-STRIP ADDITIVE FOR HOT-MIX ASPHALT	40601
406.04a	HOT-MIX ASPHALT SURFACE COURSE SURFACE TESTS	40604a
406.02	HOT-MIX ASPHALT – PRIME COAT	40602
406.13	PAYMNET FOR USE OF MATERIAL TRANSFER DEVICE	40613
407.06	BITUMINOUS PRIME COAT FOR HOT-MIX ASPHALT PAVEMENT (FULL DEPTH)	40706
407.13	GROOVED-IN RUMBLE STRIP	40713
420.20	RAILROAD APPROACH PAVEMENT	42020
424.01	SIDEWALK DRAINS	42401
424.02	TEMPORARY SIDEWALKS	42402
440.01	BRIDGE WEARING SURFACE REMOVAL	44001
440.03	PROTECTION OF FRAMES AND LIDS OF UTILITY STRUCTURES	44003
440.03c	CENTER JOINT REPAIR SYSTEM	44003c
440.03a	HOT-MIX ASPHALT SURFACE REMOVAL, *** (** MM)	44003a
440.03b	HOT-MIX ASPHALT SURFACE REMOVAL, *** (** MM)	44003b
440.03d	PAVEMENT DRAINAGE AFTER COLD MILLING	44003d
440.03e	PAVEMENT PATCHING WITH HOT-MIX ASPHALT SURFACE REMOVAL	44003e
440.03f	HOT-MIX ASPHALT CONCRETE MILLING MATERIAL	44003f
442.00	CLASS (*) PATCHES, TYPE (**), (***)	44200
443.00	REFLECTIVE CRACK CONTROL TREATMENT	44300
451.00	CRACK AND JOINT SEALING	45100
482.05	HOT-MIX ASPHALT SHOULDER RESURFACING REQUIRED TO BE CONSTRUCTED SIMULTANEOUSLY WITH MAINLINE PAVING	48205
482.06	HOT-MIX ASPHALT SHOULDER RESURFACING CONSTRUCTED SIMULTANEOUSLY WITH MAINLINE PAVING	48206

SECTION 500

District Special Provisions

<u>Standard Specifications</u>	<u>Item/Description</u>	<u>Doc. #</u>
501.03	CONCRETE HEADWALL REMOVAL	50103
501.04	CONCRETE HANDRAIL REMOVAL	50104
503.00	BIN-TYPE RETAINING WALL	50300
503.01	CONCRETE WEARING SURFACE	50301
503.02	SURFACE FILLER, SPECIAL (GALLON)	50302
503.12a	FLOOR DRAIN EXTENSIONS	50312a
503.12	PLUG EXISTING DRAINS	50312
503.17	BRIDGE FLOOR FINISHING MACHINE	50317
503.19	PROTECTING COAT, SPECIAL	50319
521.00b	JACK AND REPOSITION BEARINGS	52100b
521.00c	JACKING AND CRIBBING	52100c
542.00	SEEPAGE COLLAR	54200
542.01	REMOVE AND RELAY PIPE CULVERTS	54201
542.04	PIPE CULVERTS	54204
542.04e	BACKFILL - PIPE CULVERTS	54204e
550.00	STORM SEWER (WATER MAIN QUALITY PIPE)	55000
550.02	STORM SEWER (SPECIAL)	55002
550.07	BACKFILL, BUILDING REMOVAL	55007
552.00	STEEL PIPE CULVERT, SPECIAL (JACKED) ** (* MM)	55200
552.01	(*STORM SEWER/PIPE CULVERT) JACKED IN PLACE, ** (* MM)	55201
561.00	STEEL CASINGS (***) INCHES	56100
561.01	STEEL CASINGS (***) INCHES	56101

SECTION 600

District Special Provisions

<u>Standard Specifications</u>	<u>Item/Description</u>	<u>Doc. #</u>
601.01	PIPE UNDERDRAIN	60101
602.00d	INLET-MANHOLE, TYPE G-1, 4' (1.2 M) DIAMETER	60200d
602.00f	INLET-MANHOLE, TYPE G-1, 5' (1.5 M) DIAMETER	60200f
602.00h	INLET-MANHOLE, TYPE G-1, 5' (1.5 M) DIAMETER, DOUBLE, SPECIAL	60200h
602.00i	INLET-MANHOLE, TYPE G-1, 8' (2.4 M) DIAMETER, DOUBLE, SPECIAL	60200i
602.00e	INLET-MANHOLE, TYPE G-1, 4' (1.2 M) DIAMETER, SPECIAL	60200e
602.00g	INLET-MANHOLE, TYPE G-1, 5' (1.5 M) DIAMETER, SPECIAL	60200g
602.00a	INLETS, TYPE G-1	60200a
602.00c	INLETS, TYPE G-1, DOUBLE, SPECIAL	60200c
602.00b	INLETS, TYPE G-1, SPECIAL	60200b
602.00j	MANHOLE TO BE ADJUSTED WITH NEW TYPE G-1 FRAME AND GRATE	60200j
602.00k	TEMPORARY INLET DRAINAGE TREATMENT	60200k
602.00l	INLETS, TYPE G-2	60200l
602.00m	INLETS, TYPE G-1, DOUBLE	60200m
605.04a	FILLING EXISTING CULVERTS	60504a
605.04b	FILLING EXISTING DRAINAGE STRUCTURES	60504b
605.04	FILLING EXISTING INLETS	60504
606.08	ISLAND PAVEMENT CONSTRUCTED ON EXISTING PAVEMENT	60608
606.12	DRAINAGE HOLES	60612
630.00	EROSION CONTROL CURB	63000
630.01	GUARDRAIL AGGREGATE EROSION CONTROL	63001
630.08	STEEL PLATE BEAM GUARDRAIL, TYPE A, 6.75 FOOT POSTS	63008

SECTION 600

District Special Provisions

<u>Standard Specifications</u>	<u>Item/Description</u>	<u>Doc. #</u>
631.04	TRAFFIC BARRIER TERMINAL, TYPE 1, SPECIAL (FLARED) OR (TANGENT)	63104
631.07	TRAFFIC BARRIER TERMINALS, TYPE 6	63107
631.11c	TRAFFIC BARRIER TERMINALS	63111c
631.14	TRAFFIC BARRIER TERMINALS, TYPE 2	63114
632.00	GUARD POST REMOVAL	63200
635.00	FLEXIBLE DELINEATOR MAINTENANCE	63500
635.01	FLEXIBLE DELINEATORS	63501
667.04	PERMANENT SURVEY MARKER, TYPE I, BRIDGE PLACEMENT	66704
668.02	PERMANENT SURVEY TIES	66802
670.05	EQUIPMENT VAULT FOR NUCLEAR TESTING EQUIPMENT	67005
680.00a	RAILROAD TIES REMOVAL AND DISPOSAL	68000a
680.00	RAILROAD TRACK RAIL REMOVAL	68000
683.00	MORTARED STONE WALL	68300

SECTION 700

District Special Provisions

<u>Standard Specifications</u>	<u>Item/Description</u>	<u>Doc. #</u>
701.00	TRAFFIC CONTROL PLAN	70100
701.06	SPEEDING PENALTY	70106
701.08b	TRAFFIC CONTROL AND PROTECTION STANDARD 701331 (SPECIAL)	70108b
701.14	WIDTH RESTRICTION SIGNING	70114
701.20	TRAFFIC CONTROL AND PROTECTION STANDARD BLR 21 AND BLR 21 (SPECIAL)	70120
701.21	TRAFFIC CONTROL AND PROTECTION STANDARD BLR 22 AND BLR 22 (SPECIAL)	70121
701.22	TRAFFIC CONTROL AND PROTECTION STANDARD 701606 (SPECIAL)	70122
703.00	PAVEMENT MARKING REMOVAL/WORK ZONE PAVEMENT MARKING REMOVAL	70300
704.00a	TEMPORARY CONCRETE BARRIER REFLECTORS	70400a
704.00	TEMPORARY CONCRETE BARRIER, STATE OWNED AND TEMPORARY CONCRETE BARRIER TERMINAL SECTIONS, STATE OWNED	70400
780.00	THERMOPLASTIC PAVEMENT MARKING EQUIPMENT	78000
780.07	PREFORMED PLASTIC PAVEMENT MARKINGS	78007
781.00	TEMPORARY RAISED REFLECTIVE PAVEMENT MARKER	78100

SECTION 800

District Special Provisions

<u>Standard Specifications</u>	<u>Item/Description</u>	<u>Doc. #</u>
810.00	CONDUIT, PUSHED OR TRENCHED	81000
815.00	TRENCH & BACKFILL, SPECIAL FOR CONDUIT INSTALLATION BENEATH BITUMINOUS SHOULDERS	81500
863.00	TERMINAL FACILITY	86300
873.00	ELECTRIC CABLE CONDUIT NO. 18	87300
886.00	DETECTOR LOOP, SPECIAL FOR TRAFFIC COUNTERS	88600
886.00a	DETECTOR LOOPS, TYPE 1	88600a

October 4, 2012

SECTION 900

District Special Provisions

Standard
Specifications

Item/Description

Doc. #

SECTION 1000

District Special Provisions

<u>Standard Specifications</u>	<u>Item/Description</u>	<u>Doc. #</u>
1004.00	AGGREGATE OPTIMIZATION OF CLASS PV MIX FOR SLIPFORM PAVING	100400
1004.01	COARSE AGGREGATE FILL	100401
1004.02	CONCRETE SUPERSTRUCTURE AGGREGATE OPTIMIZATION	100402
1004.03b	COARSE AGGREGATE FOR BITUMINOUS COURSES, CLASS A	d100403b
1004.04	AGGREGATE QUALITY	d100404
1030.04	HOT-MIX ASPHALT – MIXTURE DESIGN VERIFICATION AND PRODUCTION	103004
1103.03	PCC AUTOMATIC BATCHING EQUIPMENT	110303

District Special Provisions

Alphabetic Index

ALPHABETIC INDEX OF DISTRICT SPECIAL PROVISIONS

<u>Item/Description</u>	<u>Standard Specification</u>	<u>Filename</u>
AGGREGATE DITCH	283.03	28303
AGGREGATE OPTIMIZATION OF CLASS PV MIX FOR SLIPFORM PAVING	1004.00	100400
AGGREGATE QUALITY	1004.04	100404
ANTI-STRIP ADDITIVE FOR HOT-MIX ASPHALT	406.01	40601
BACKFILL - PIPE CULVERTS	542.04e	54204e
BACKFILL, BUILDING REMOVAL	550.07	55007
BIN-TYPE RETAINING WALL	503.00	50300
BITUMINOUS PRIME COATE FOR HOT-MIX ASPHALT PAVEMENT (FULL DEPTH)	407.06	40706
BORROW AND FURNISHED EXCAVATION	204.00	20400
BRIDGE FLOOR FINISHING MACHINE	503.17	50317
BRIDGE WEARING SURFACE REMOVAL	440.01	44001
CENTER JOINT REPAIR SYSTEM	440.03c	44003c
CLASS (*) PATCHES, TYPE (**), (***)	442.00	44200
CLEAN EXISTING PAVEMENT EDGE JOINT	406.00	40600
COARSE AGGREGATE FILL	1004.01	100401
COARSE AGGREGATE FOR BITUMINOUS COURSES, CLASS A	1004.03b	100403b
CONCRETE HANDRAIL REMOVAL	501.04	50104
CONCRETE HEADWALL REMOVAL	501.03	50103
CONCRETE SUPERSTRUCTURE AGGREGATE OPTIMIZATION	1004.02	100402
CONCRETE WEARING SURFACE	503.01	50301
CONDUIT, PUSHED OR TRENCHED	810.00	81000
CONSTRUCTION STATION LAYOUT	105.00	10500
CRACK AND JOINT SEALING`	451.00	45100
DATE OF COMPLETION	108.05a	10805a
DATE OF COMPLETION (PLUS WORKING DAYS)	108.05b	10805b

ALPHABETIC INDEX OF DISTRICT SPECIAL PROVISIONS

<u>Item/Description</u>	<u>Standard Specification</u>	<u>Filename</u>
DELAYED START OF MULTIPLE CONTRACTS	108.03	10803
DETECTOR LOOP, SPECIAL FOR TRAFFIC COUNTERS	886.00	88600
DETECTOR LOOPS, TYPE 1	886.00a	88600a
DRAINAGE HOLES	606.12	60612
ELECTRIC CABLE CONDUIT, LEAD-IN, NO. 18	873.00	87300
EMBANKMENT	205.05	20505
EMBANKMENT (RESTRICTIONS)	205.04	205.04
EMBANKMENT (SMALL EMBANKMENTS)	205.05a	20505a
EQUIPMENT VAULT FOR NUCLEAR TESTING EQUIPMENT	670.05	67005
EROSION CONTROL CURB	630.00	63000
FILLING EXISTING CULVERTS	605.04a	60504a
FILLING EXISTING DRAINAGE STRUCTURES	605.04b	60504b
FILLING EXISTING INLETS	605.04d	60504d
FLEXIBLE DELINEATOR MAINTENANCE	635.00	63500
FLEXIBLE DELINEATORS	635.01	63501
FLOOR DRAIN EXTENSION	503.12a	50312a
GEOTECHNICAL REINFORCEMENT	205.00	20500
GROOVED-IN RUMBLE STRIP	407.13	40713
GROUT FOR USE WITH RIPRAP	281.00	28100
GUARD POST REMOVAL	632.00	63200
GUARDRAIL AGGREGATE EROSION CONTROL	630.01	63001
HOT-MIX ASPHALT CONCRETE MILLING MATERIAL	440.03f	44003f
HOT-MIX ASPHALT – MIXTURE DESIGN VERIFICATION AND PRODUCTION	1030.04	103004
HOT-MIX ASPHALT – PRIME COAT	406.02	40602
HOT-MIX ASPHALT SHOULDER RESURFACING CONSTRUCTED SIMULTANEOUSLY WITH MAINLINE PAVING	482.06	48206

ALPHABETIC INDEX OF DISTRICT SPECIAL PROVISIONS

<u>Item/Description</u>	<u>Standard Specification</u>	<u>Filename</u>
HOT-MIX ASPHALT SHOULDER RESURFACING REQUIRED TO BE CONSTRUCTED SIMULTANEOUSLY WITH MAINLINE PAVING	482.05	48205
HOT-MIX ASPHALT SURFACE COURSE SURFACE TESTS	406.04a	40604a
HOT-MIX ASPHALT SURFACE REMOVAL, *** (** MM)	440.03a	44003a
HOT-MIX ASPHALT SURFACE REMOVAL, *** (** MM)	440.03b	44003b
INLET-MANHOLE, TYPE G-1, 4' (1.2 M) DIAMETER	602.00d	60200d
INLET-MANHOLE, TYPE G-1, 4' (1.2 M) DIAMETER, SPECIAL	602.00e	60200e
INLET-MANHOLE, TYPE G-1, 5' (1.5 M) DIAMETER	602.00f	60200f
INLET-MANHOLE, TYPE G-1, 5' (1.5 M) DIAMETER, DOUBLE, SPECIAL	602.00h	60200h
INLET-MANHOLE, TYPE G-1, 5' (1.5 M) DIAMETER, SPECIAL	602.00g	60200g
INLET-MANHOLE, TYPE G-1, 8' (2.4 M) DIAMETER, DOUBLE, SPECIAL	602.00i	60200i
INLETS, TYPE G-1	602.00a	60200a
INLETS, TYPE G-1, DOUBLE	602.00m	60200m
INLETS, TYPE G-1, DOUBLE, SPECIAL	602.00c	60200c
INLETS, TYPE G-1, SPECIAL	602.00b	60200b
INLETS, TYPE G-2	602.00l	60200l
ISLAND PAVEMENT CONSTRUCTED ON EXISTING PAVEMENT	606.08	60608
JACK AND REPOSITION BEARINGS	521.00b	52100b
JACKING AND CRIBBING	521.00c	52100c
LOCATION OF UNDERGROUND STATE MAINTAINED FACILITIES	107.31	10731
MANHOLE TO BE ADJUSTED WITH NEW TYPE G-1 FRAME AND GRATE	602.00j	60200j
MORTARED STONE WALL	683.00	68300
MOWING	250.06a	250.06a
MOWING	250.06b	250.06b
NATIONWIDE 404 PERMIT REQUIREMENTS	107.00a	10700a
PAVEMENT DRAINAGE AFTER COLD MILLING	440.03c	44003c

ALPHABETIC INDEX OF DISTRICT SPECIAL PROVISIONS

<u>Item/Description</u>	<u>Standard Specification</u>	<u>Filename</u>
PAVEMENT MARKING REMOVAL/WORK ZONE PAVEMENT MARKING REMOVAL	703.00	70300
PAVEMENT PATCHING WITH HOT-MIX ASPHALT SURFACE REMOVAL	440.03e	44003e
PAYMENT FOR USE OF MATERIAL TRANSFER DEVICE	406.13	40613
PCC AUTOMATIC BATCHING EQUIPMENT	1103.03	110303
PERMANENT SURVEY MARKER, TYPE I, BRIDGE PLACEMENT	667.04	66704
PERMANENT SURVEY TIES	668.02	66802
PIPE CULVERTS	542.04	54204
PIPE UNDERDRAIN	601.00	60100
PLUG EXISTING DRAINS	503.12	50312
PREFORMED PLASTIC PAVEMENT MARKINGS	780.07	78007
PRESTAGE SITE CONSTRUCTION MEETINGS	105.06	10506
PROOF ROLLING	301.01	30101
PROTECTION OF FRAMES AND LIDS OF UTILITY STRUCTURES	440.03	44003
PROTECTIVE COAT, SPECIAL	503.19	50319
RAILROAD APPROACH PAVEMENT	420.20	42020
RAILROAD TIES REMOVAL AND DISPOSAL	680.00a	68000a
RAILROAD TRACK RAIL REMOVAL	680.00	68000
REFLECTIVE CRACK CONTROL TREATMENT	443.00	44300
REMOVAL OF ABANDONED UNDERGROUND UTILITIES	105.07	10507
REMOVE AND RELAY PIPE CULVERTS	542.01	54201
RIGHT-OF-WAY RESTRICTIONS	107.32	10732
ROCKFILL	311.00	31100
RUMBLE STRIP	407.14	40714
SEEDING, MINOR AREAS	250.00	25000
SEEDLING MIXTURE A	253.00b	15300b

ALPHABETIC INDEX OF DISTRICT SPECIAL PROVISIONS

<u>Item/Description</u>	<u>Standard Specification</u>	<u>Filename</u>
SEEPAGE COLLAR	542.00	54200
SIDEWALK DRAINS	424.01	42401
SOIL MODIFICATION	302.00	30200
SPEEDING PENALTY	701.06	70106
STATUS OF UTILITIES/UTILITIES TO BE ADJUSTED	105.07	10507
STEEL CASINGS (***) INCHES	561.00	56100
STEEL CASINGS (***) INCHES	561.01	56101
STEEL PIPE CULVERT, SPECIAL (JACKED) *** (* MM)	552.00	55200
STEEL PLATE BEAM GUARDRAIL, TYPE A, 6.75 FOOT POSTS	630.08	63008
STONE DUMPED RIPRAP*	281.04	28104
STONE RIPRAP	281.06	28106
STORM SEWER (SPECIAL)	550.02	55002
STORM SEWER/PIPE CULVERT) JACKED IN PLACE *** (** MM)	552.01	55201
STORM SEWER (WATER MAIN QUALITY PIPE)	550.00	55000
SUBBASE GRANULAR MATERIAL	311.01	31101
SUBGRADE TREATMENT	301.03	30103
SURFACE FILLER, SPECIAL (GALLON)	503.02	50302
TEMPORARY CONCRETE BARRIER REFLECTORS	704.00a	70400a
TEMPORARY CONCRETE BARRIER, STATE OWNED & TEMPORARY CONCRETE BARRIER TERMINAL SECTIONS, STATE OWNED	704.00d	70400d
TEMPORARY INLET DRAINAGE TREATMENT	602.00k	60200k
TEMPORARY PAVEMENT	355.00	35500
TEMPORARY RAISED REFLECTIVE PAVEMENT MARKER, TYPE II	781.00	78100
TEMPORARY SIDEWALKS	424.02	42402
TERMINAL FACILITY	863.00	86300

ALPHABETIC INDEX OF DISTRICT SPECIAL PROVISIONS

<u>Item/Description</u>	<u>Standard Specification</u>	<u>Filename</u>
THERMOPLASTIC PAVEMENT MARKING EQUIPMENT	780.00	78000
TRAFFIC BARRIER TERMINALS	631.11c	63111c
TRAFFIC BARRIER TERMINALS, TYPE 1, SPECIAL (FLAMED) OR (TANGENT)	631.04	631.04
TRAFFIC BARRIER TERMINALS, TYPE 2	631.14	63114
TRAFFIC BARRIER TERMINALS, TYPE 6	631.07	63107
TRAFFIC CONTROL AND PROTECTION STANDARD 701331 (SPECIAL)	701.08b	70108b
TRAFFIC CONTROL AND PROTECTION STANDARD BLR 21 AND BLR 21 (SPECIAL)	701.20	70120
TRAFFIC CONTROL AND PROTECTION STANDARD BLR 22 AND BLR 22 (SPECIAL)	701.21	701.21
TRAFFIC CONTROL AND PROTECTION STANDARD 701606 (SPECIAL)	701.22	70122
TRAFFIC CONTROL PLAN	701.00	70100
TREE WHIP MIXTURE	253.00	25300
TRENCH & BACKFILL, SPECIAL FOR CONDUIT INSTALLATION BENEATH BITUMINOUS SHOULDERS	815.00	81500
WIDTH RESTRICTION SIGNING	701.14	70114

District Special Provisions

Designer Note: Use when proposed water mains are to be located under new pavement structures or services requiring casing pipe that is less than 12" in diameter. Check with Utilities/Project Engineer for inclusion. ASTM A53 required for pipe to be ordered by NPS (nominal pipe size, I.D.) and weight class or schedule number, or both; or by outside diameter (O.D.) and nominal wall thickness. This provision has been written to conform with the I.D. ordering requirements. If an outside diameter is needed then the Designer must revise this provision and so reflect the provisions of A53. *Insert diameter ____* inches.

STEEL CASINGS ____ INCHES

Effective July 1, 1990

Revised January 1, 2013

This work shall consist of furnishing a Schedule 40 Steel Pipe, ____ I.D. to A.S.T.M. Specification A-53 and using it to encase the water main at the location shown on the plans. All joints are to be field welded in a manner approved by the Engineer.

This work will be paid for at the contract unit price per Foot for STEEL CASINGS, ____ inches, which price shall include all material, equipment, and labor necessary to complete the work.

Designer Note: Use when proposed water mains requiring a casing pipe that is 12" ± or larger in diameter are to be located under new pavement structures. Check with Utilities/Project Engineer for inclusion. The specification for the pipe is manufactured to is A.S.T.M. A-252, Grade 2. If an inside diameter is needed then the Designer must revise. *Insert diameter * inches and wall thickness ** inches.

An industry contact person is Mark Lible at Pittsburgh Pipe in St. Louis, MO; Phone # (800) 325-2653.

STEEL CASINGS (*) INCHES

Effective July 1, 1990

Revised January 1, 2013

This work shall consist of furnishing a all equipment, materials, and labor to install a Steel Pipe, * O.D. to A.S.T.M. Specification A-252, Grade 2 in accordance with Section 542 of the Standard Specifications for watermain encasement at the location shown on the plans. All joints are to be field welded in a manner approved by the Engineer and in accordance with the Standard Specifications.

The inside and outside of the pipe shall be coated with a bituminous based paint system such as BB-99 or approved equivalent.

The Contractor shall furnish mill test reports for the pipe used. Wall thickness shall be a minimum of (**).

Each end of the casing shall be capped with concrete block and mortar to the satisfaction of the Engineer.

This work will be paid for at the contract unit price per Foot for STEEL CASINGS, INCHES, which price shall include all material, equipment, and labor necessary to complete the work.