STATE OF ILLINOIS DEPARTMENT OF TRANSPORTATION



NOTES

Bar splicer assemblies shall be of an approved type and shall develop in tension at least 125 percent of the yield strength of the lapped reinforcement bars.

Splicer rods shall be of minimum 60 ksi yield strength, threaded or coiled full length. All reinforcement bars shall be lapped and tied to the splicer rods or dowel bars.

Bar splicer assemblies shall be epoxy coated according to the requirements for reinforcement bars.

Other systems of similar design may be submitted to the Engineer for approval. Approval shall be based on certified test results from an approved testing laboratory that the proposed bar splicer assembly satisfies the following requirements:

Minimum Capacity (Tension in kips) = 1.25 x fy x A_t


Minimum *Pull-out Strength = 1.25 x fs_{allow} x A_t (Tension in kips)

Where fy = Yield strength of lapped reinforcement bars in ksi.

fs_{allow}= Allowable tensile stress in lapped reinforcement bars in ksi (Service Load) A_f = Tensile stress area of lapped reinforcement bars. * = 28 day concrete


	BAR SPLIC	CER ASSEMBLI	ES		
Bar Size to be Spliced	Splicer Rod or Dowel Bar Length	Strength Requirements			
			Min. Pull-Out Strength kips - tension		
#4	1'-8''	14.7	5.9		
#5	2'-0''	23.0	9.2		
#6	2′-7′′	33.1	13.3		
#7	3′-5″	45.1	18.0		
#8	4'-6"	58.9	23.6		
#9	5′-9′′	75.0	30.0		
#10	7'-3''	95.0	38.0		
#11	9'-0''	117.4	46.8		

Bar splicer assemblies shall be according to Section 508 of the Standard Specifications, except as noted. The furnishing and installation of bar splicer assemblies will be measured and paid for at the contract unit price each for "BAR SPLICERS."



Bar Size	No. Assemblies Required	Location		
#4	69	Deck		
#6	2	S. Abut. Backwall		


BAR SPLICER ASSEMBLY DETAILS F.A.S. 221 (IL RTE 94) OVER MILL CREEK SECTION (19B-1)M ROCK ISLAND COUNTY STR. NO. 081-0137



** ONE PIECE -Wire Connector WELDED SECTIONS


BAR SPLICER ASSEMBLY ALTERNATIVES

** Heavy Hex Nuts conforming to ASTM A 563, Grade C, D or DH may be used.




INSTALLATION AND SETTING METHODS


"A": Set bar splicer assembly by means of a template bolt. "B" : Set bar splicer assembly by nailing to wood forms or cementing to steel forms. (E): Indicates epoxy coating.



FOR INTEGRAL OR SEMI-INTEGRAL ABUTMENTS

Bar Splicer for #5 bar	
Dai Spilder For #5 Dai	
Min. Capacity = 23.0 kips - tension	
Min. Pull-out Strength = 9.2 kips - tension	วก
No. Required =	





	Bar	Splicer	for #	5 bar		
Min.	Capacity	= 23.0	kips -	tensi	on	
Min.	Pull-out	Strength	= 9.2	kips	-	tension
No.	Required	=			_	

10-22-04