



DECK POURING SEQUENCE NOTES

Deck pours shall be stopped at the Transverse Bonded Construction Joints in the deck Pouring Sequence as shown. The next pour shall not be made until requirements 1 & 2 below are met:

1. At least 72 hours shall have elapsed from the end of the previous pour.
2. The concrete strength shall have attained a minimum flexural strength of 650 p.s.i. or a minimum compressive strength of 3,500 p.s.i.
3. Deflections indicated in the Dead Load Deflection Diagram and in the Top of Slab Elevation Tables account for composite sections during the deck pouring sequence.

If the contractor wishes to change the sequence, plan revisions and design computations shall be submitted to the Engineer for review and approval. The calculations shall be prepared and sealed by a licensed structural engineer in Illinois.

NOTES:
Work this sheet with Sheets 4 and 5 of 25

