Joint Size	"C" at 50°F	"D" at 50°F
2"	2"	1½" Min.
212"	212"	1 <sup>3</sup> 4′′ Min.
4''	3′′	2 <sup>1</sup> 2" Min.

### INSTALLATION NOTES

- Install continuous seal in roadway, parapet, curb, and sidewalk.
- (2) Install anchor blocks as indicated.

Note A

Maximum spacing of anchor bolts shall be 12" centers.


### SKEW LIMITATIONS

The details of the anchor blocks and the elastomeric membrane in the parapet, as shown, are for up to 50° skews. For skews greater than 50°, the anchor blocks and the elastomeric membrane, installed according to dimension "D", might require modifications to insure a minimum clearance of  $1^{l}_{2}$ " from centerline of anchor studs to edge of parapet opening. The anchor blocks and the elastomeric membrane shall also be installed to the top of the parapet with the anchor studs spaced at ±12" cts.

Std. Anchor Bolts

Cast in place

AT CURB




FORMING BLOCKOUT
SKETCH

# Steel reinforced elastomeric anchor blocks | 'a'' Min. steel plate | 'a'' Max. | 'typ. | | 'a'' Min. fabric reinforced elastomeric membrane or 'a'' Min. non-reinforced elastomeric membrane. | Sealant | Cast in place | Cast in place | | Cast in place | Cast in place | | Steel | Reinforcement | Reinforcement | | Cast | Reinforcement | Reinforcement | | Cast | Reinforcement | Reinforcement | | Cast | Reinforcement | |

CROSS SECTION

STATE OF ILLINOIS

ANCHOR BLOCK WITH ASPHALT SURFACE



\* (5VB, 5HB, 1-2HB)M

Contract #64A88

### GENERAL NOTES


Continuous Seal Neoprene Expansion Joint shall consist of molded anchor blocks of elastomer and steel, field assembled over continuous lengths of elastomeric membrane.

The elastomeric membrane shall be premolded with a single or a double upward convolution that will have a "memory" to return to its molded position upon joint closure.


The convolution length shall be such that the extended length will not be greater than the manufactured length when the joint is fully expanded in its design range and will not protrude above the anchor blocks when the joint is fully compressed.

Joint openings shall be adjusted according to Article 503.10(c) of the Standard Specifications when the deck is poured at an ambient temperature other than  $50^\circ$  F.


The parapet and roadway membrane shall be made continuous by an approved vulcanizing process. Lapping will not be permitted.









AT PARAPET



AT SIDEWALK OR MEDIAN



AT SIDEWALK OR MEDIAN
TYPICAL END TREATMENTS



Asphait

surface


AT WALL

Std. Anchor Bolts Cast in place

Note A and Note 1

Threaded Anchor Studs with Washers

AT WALL



NEOPRENE EXPANSION JOINTS
Forest Hills Road Ramp Over
F.A.P. 303 & F.A.P. 738 (IL 251)
SECTION (5VB,5HB,1-2HB)M
WINNEBAGO COUNTY
SN 101-0123

CONTINUOUS SEAL TYPE

## Countersunk hole for top nut Temporary Wood Blockout Bottom Clamping Nut Formed Joint Opening Note: Stud needs to be threaded lower to allow for use of clamping nut. Anchor studs should be stainless

## RECOMMENDED BLOCKOUT DETAIL

### BILL OF MATERIAL

ITEM	UNIT	TOTAL
Neoprene Exp. Jt., 2"	Foot	63
Neoprene Exp. Jt, 4"	Foot	58

DESIGNED SB. DP

CHECKED SB

DRAWN BH. BS

CHECKED SB

Threaded Anchor
Studs with Washers

**EJ-CS** 10-22-04